

NORDSTROM RACK – TURNKEY PROTOTYPE

SECTION 033536 – POLISHED CONCRETE FINISHING

PART 1 - GENERAL

1.1 SUMMARY

- A. Section includes:
 - 1. Existing and new concrete polishing systems.
- B. Drawings, the provisions of the Agreement, the General Conditions, and Division 01 specification sections apply to the work of this Section.
- C. Substitutions: Substitute products will be considered only under the terms and conditions of Section 016000.

1.2 REFERENCES

- A. American Society for Testing and Materials (ASTM):
 - 1. C171 - Standard Specification for Sheet Materials for Curing Concrete.
 - 2. D523 - Standard Test Method for Specular Gloss.
 - 3. D1455 - Standard Test Method for 60-deg Specular Gloss of Emulsion Floor Polish.
 - 4. D2240 - Standard Test Method for Rubber Property - Durometer Hardness.
 - 5. D5767 - Standard Test Method for Instrumental Measurement of Distinctness-of-Image (DOI) Gloss of Coated Surfaces.
 - 6. E1155 - Standard Test Method for Determining FF Floor Flatness and FL Floor Levelness Numbers.
 - 7. F1869 - Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride.
 - 8. F2170 - Standard Test Method for Determining Relative Humidity in Concrete Floor Slabs Using in situ Probes.
- B. American National Standards Institute (ANSI) / National Floor Safety Institute (NFSI):
 - 1. ANSI A326.3 Test Method for Measuring Dynamic Coefficient of Friction of Hard Surface Flooring Materials.
 - 2. ANSI/NFSI B101.3 Test Method for Measuring Wet DCOF of Common Hard Surface Floor Materials.
- C. Concrete Polishing Council (CPC), a specialty council for the American Society of Concrete Contractors (ASCC), (www.asconline.org).
- D. International Concrete Repair Institute (ICRI):
 - 1. CSP 3 – Light shotblast (for coating 9-13 mils thick).
 - 2. CSP 4 – Light Scarification (for coating 13-17 mils thick).
 - 3. CSP 5 – Medium- shotblast (for coating 14-18 mils thick).

1.3 SYSTEM DESCRIPTION

- A. Multistep mechanical processes and accessories as specified herein or required by the polishing system manufacturer to provide a complete system and achieve the specified finish.
- B. Mechanical bonded abrasive grinding and polishing equipment, concrete repair and topping materials, concrete treatment densifiers.

1.4 SUBMITTALS

- A. Make submittals in accordance with Section 013300.
- B. Submit manufacturer's product data and application instructions for all products proposed for use.
- C. Written certification, signed by manufacturer's representative, stating applicator as trained and qualified to perform work of this Section using proposed manufacturer's products, including qualification criteria.