

NORDSTROM RACK – TURNKEY PROTOTYPE

SECTION 033536 – POLISHED CONCRETE FINISHING

- B. Perform finish polishing of concrete floor slab using diamond polishing equipment to achieve uniform final finish, matching mock-up.
- C. Provide the system manufacturer's optional topical agent to seal the surface until the densifier can develop to its full potential.
- D. Final Polish: Using high-speed burnishing equipment and finest grit burnishing pads, burnish to uniform final sheen matching approved mock-up.
- E. Finish:
 - 1. Final Concrete Floor Finish: Conform to finish sheen and treatment as accepted by mock-up.
 - 2. Provide appearance similar to gloss sheen working up to a Level 3 – 800 grit diamond polish.
 - a. Reflective Clarity Reading: Between 50 and 65 according to ASTM D5767.
 - b. Reflective Sheen Reading: Not less than 35 according to ASTM D523.
 - c. After testing, notify Architect if values are less than specified.
 - 3. Color: Provide system free of dyes, with only the natural color of the concrete in all areas indicated on the Drawings.

3.10 CLEANING

- A. Leave area clean, free from spillage, overspray, tracking, and other residue resulting from work of this Section.

3.11 FIELD QUALITY CONTROL

- A. Field Testing: Engage a qualified walkway auditor to perform field testing to determine if in-place floor finish complies with specified coefficient of friction.

3.12 PROTECTION

- A. Cover to protect concrete slab with clean, unwrinkled kraft curing paper during curing, as instructed by manufacturer.
- B. Do not lay non-permeable films, membranes, or covers, including polyethylene, over finished floor.
- C. Protect finished floor from traffic for the duration required by the polishing system manufacturer.

3.13 MAINTENANCE

- A. Instruct the Owner's/Tenant's (Nordstrom's) maintenance personnel on the avoidance of cleaners that are acidic or otherwise incompatible with the surface and cause a residual stain.

END OF SECTION