








Technical Information

Mazda Rhodium White Met, Color 51K for Basecoat



Application Process

Demonstrated on a door.

Preparation	70-45 Cleaner	 1x	 wipe dry	Use compressed air to remove any dust from the panel and wipe it with an anti-static cloth.			
Basecoat Step 1 Spray coat 1	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 2.0 bar	 1 normal coat	 Flash off until mat	
Basecoat Step 1 Spray coat 2	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 2.0 bar	 1 full coat	 Flash off until mat	
A uniform film build can be achieved by light coats in step 2.							
Basecoat Step 2 Spray coat 1	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 1.5-2.0 bar	 1 light coat	 Flash off until mat	
Basecoat Step 2 Spray coat 2	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 1.5-2.0 bar	 1 light coat	 Flash off until mat*	
*The flash off process can be forced with a suitable Venturi system.							
Basecoat Step 2 Effect coat 1	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 1.5-2.0 bar	 1 effect coat	 Flash off until mat*	
*The flash off process can be forced with a suitable Venturi system.							
Basecoat Step 2 Effect coat 2	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 1.5-2.0 bar	 1 effect coat	 10-15 min before clear coat application	

Note: Repeat "Step 2 Effect coat 2" until the number of spray coats of the initially selected spray out card is reached.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Technical Information

Mazda Rhodium White Met, Color 51K for Basecoat



Safety instructions:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany

03/2025