

40-100



A brand of
BASF - We create chemistry

40-100 High Speed 2K Clear VOC

Application HS VOC clear for basecoat.

- Key Features**
- Time savings during drying and great performance at lower temperatures.
 - Designed for user-friendliness: premixed clear coat and easy to use.
 - Good finishing.
 - Select hardener according to ambient temperature and size of object to be painted. Choose right hardener from temperature chart.

Mixing Ratio

2:1



Mixing Ratio

100 % by volume

40-100 - High Speed 2K Clear VOC



Hardener

50 % by volume

50-415 - 2K Clear Hardener VOC fast
50-420 - 2K Clear Hardener VOC normal
50-430 - 2K Clear Hardener VOC slow
50-430 only in very hot conditions

Spray Viscosity



at 20°C

DIN 4: 17-19 s

Potlife at 20°C

30 min

Application	 Compliant Gravity Spray Gun
Application Pressure	2 bar
Nozzle Size	1.2 -1.3
Number of Coats	2
Flash Off at 20°C	At least 3 min between spray coats
Film thickness	40 -50 µm
Remarks	Alternative application: ½ + 1, half coat followed by full coat without intermediate flash off.

40-100



A brand of
BASF - We create chemistry

40-100 High Speed 2K Clear VOC

Drying



Drying at 20°C

50-415: 3 h
50-420: 3 h
50-430: 3 h



Drying at 40°C

50-415: 20 min
50-420: 25 min
50-430: 30 min



Drying at 60°C

50-415: 10 min
50-420: 15 min
50-430: 20 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety Advice

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/II B(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany