

# 45 Line

## 45 Line variant 49-

|                     |                                                                                                                                                                                                                                                                                              |
|---------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Application</b>  | 49- pigments are rarely used pigments for basecoat / clearcoat finishes                                                                                                                                                                                                                      |
| <b>Key Features</b> | <ul style="list-style-type: none"> <li>• These rarely used pigments are not available as a mixing base for the mixing machine</li> <li>• Special color finishes that can only be reproduced with these rarely used pigments</li> </ul>                                                       |
| <b>Remarks</b>      | <p>Shake well before using</p> <p><b>Step 1:</b> Please search color database for the color code to check whether a specific ground coat color is required for "Step 1" to reproduce the desired color</p> <p><b>Pot life:</b> 45 line ready for use: 1 week in sealed plastic container</p> |

|                                                                                     |                                                                                            |                 |                                                               |
|-------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------|-----------------|---------------------------------------------------------------|
| <b>Mixing Ratio</b>                                                                 | Stir immediately after completion of 45 Line tinters, then again after addition of 45-R45. |                 |                                                               |
|   | <b>Mixing Ratio</b>                                                                        | 100 % by volume | includes 49- basecoat and additional mixing bases if required |
|  | <b>Reducer</b>                                                                             | 70 % by volume  | 45-R45 - Reducer                                              |

|                        |                                                                                     |                |                  |
|------------------------|-------------------------------------------------------------------------------------|----------------|------------------|
| <b>Spray Viscosity</b> |  | <b>at 20°C</b> | DIN 4: 16 - 22 s |
|------------------------|-------------------------------------------------------------------------------------|----------------|------------------|

|                        |         |
|------------------------|---------|
| <b>Potlife at 20°C</b> | 1 weeks |
|------------------------|---------|

| Application          |  |  |
|----------------------|--|-------------------------------------------------------------------------------------|
|                      |  | HVLP Spray Gun                                                                      |
| Application Pressure |  | 2 bar                                                                               |
| Nozzle Pressure      |  | 0.7 bar                                                                             |
| Nozzle Size          |  | 1.4                                                                                 |
| Number of Coats      |  | 2<br>+ ½                                                                            |
| Flash Off at 20°C    |  | until mat                                                                           |
| Film thickness       |  | 10 - 15 µm                                                                          |



A brand of  
BASF - We create chemistry

# 45 Line

45 Line variant 49-

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

---

## Safety Advice

It cannot be ruled out that this product contains particles  $< 0.1 \mu\text{m}$ . The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

**2004/42/IIB(d)(420)419:** The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany