

Technical Information

45 Line



45 Line variant 50-45

Activator for waterborne basecoats

- For special applications recommended by car manufactures, the usage of 2K Activator could be necessary in 45 Line basecoats
- Additive for solid-color 45 Line and for use in solid-color basecoats applied as a ground coat in 45 Line 3-layer systems to improve tape resistance and hardness.
- Mixing formulas that contain 45-W1012 cannot be used with 50-45.

The drying time depends on climatic conditions and equipment used.

Application

	Mixing Ratio	100 % by volume 5 % by volume 50-45 70 % by volume 45-R45 1. Mix the 45 Line basecoat formula and stir carefully. 2. Add 2K Activator and thoroughly stir 3. Add 45-R45 and thoroughly stir again 4. Strain before application. 50-45 cannot be added in formulas which contains already 45-R45.
	Spray viscosity at 20°C	DIN 4: 18-25 s
	Potlife at 20°C	2 h
	HVLP spray gun	
	Nozzle size	1.4 mm
	Application pressure	2 bar
	Nozzle pressure	0.7 bar
	Number of spray coats	2 -3
	Film thickness	20-25 µm
	Application Remark	Solid color or ground coat

Safety advice:

Safety instructions:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Technical Information

45 Line



45 Line variant 50-45

Drying

	Drying at 20°C	15 min
	Drying at 60°C	10 min + cooling
	Infrared (medium wave)	10-15 min (1st spraycoat: Flash off until mat 10 – 15 min.; 2nd spraycoat: 40 – 50°C (max 70°C) surface temperature to mat surface + cooling)

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

Safety instructions:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.