


Technical Information

Mazda Rhodium White Met, Color 51K for Basecoat



Blend in repair process on the panel being repaired
Demonstrated on a partly primed fender.

Preparation	 Sand the primer filler and mat the old paintwork of the fender.	70-45 Cleaner	 1x	 wipe dry			
Optional Blending Clear	45-W10 3 Stage Additive and Blending Clear	45-R45 Reducer	 100:70	 HVLP 1.4 2.0 bar	 1-2 full coats	 No flash off, apply basecoat step 1 directly.	
Basecoat Step 1 Spray coat 1	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 1.0-1.5 bar	 2 coats	 Flash off until mat	
Blending Clear	45-W10 3 Stage Additive and Blending Clear	45-R45 Reducer	 100:70	 HVLP 1.4 2.0 bar	 1-2 full coats	 No flash off, apply basecoat step 2 directly.	
Basecoat Step 2 Spray coat 1	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 1.5-2.0 bar	 1 light coat	 Flash off until mat	
Basecoat Step 2 Spray coat 2	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 1.5-2.0 bar	 1 light coat	 Flash off until mat	

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Technical Information

Mazda Rhodium White Met, Color 51K for Basecoat



Blend in repair process on the panel being repaired
Demonstrated on a partly primed fender.

Basecoat Step 2 Effect coat 1	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 1.5-2.0 bar	 1 effect coat	 Flash off until mat	
Basecoat Step 2 Effect coat 2	45 Line Basecoat	45-R45 Reducer	 100:70	 HVLP 1.4 1.5-2.0 bar	 1 effect coat	 10-15 min Flash off until mat before clear coat*	

*Use blow equipment (venturi) or briefly increase the temperature up to 50°C (plus cooling down).

Note: Repeat the application of Basecoat Step 2 of mixing formula (effect coat 2 incl. flash off) until the number of spray coats of the initially selected spray out card is reached. This is likely to be at least 2 to 4 coats.

Safety instructions:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany

03/2025