

ONYX EASY BLENDER

A 2520 Additive for blending repairs



by Surventis

Application Water-based additive for refinishing with ONYX HD using a BLEND'ART process.
For use in BLEND'ART processes either as a transparent pre coat or as an additive in ONYX HD.

Remarks

- Shake well before use.

Handling



Cleaning

See process described in BLEND'ART ONYX HD.

Mixing Ratio



Mixing Ratio

100 part(s) by vol

A 2520 - Additive for blending repairs



Thinner

60 part(s) by vol

HB 032
HB 034 - HYDROMIX slow

Potlife at 20°C

7 days

Application



HVLP Spray Gun

Nozzle Pressure	0.7 bar
Nozzle Size	1.4 -1.5
Number of Coats	See process described in BLEND'ART ONYX HD.
Remarks	Minijet HVLP 1.0 mm 0.7 bar at the nozzle. Select spraygun according to size of area to be refinished.

Drying

Drying Remark See process described in BLEND'ART ONYX HD.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

ONYX EASY BLENDER

A 2520 Additive for blending repairs



by Surventis

Safety Advice

It cannot be ruled out that this product contains particles $< 0.1 \mu\text{m}$. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France