

TEXTURE Tune-R

A 2P80 eSense texture additive



by Surventis

Application	Pioneer Series - eSense texture additive for Pioneer Series clear coats.
Key Features	Add 25 to 50% of A 2P80 to produce the desired texture or as per published mixing formula.
Remarks	Mixing ratio / Application: As specified in the technical data sheet of the product in which texture additive A 2P80 is being used. Flash off until mat between spray coats and before stoving.

Drying



Drying at 60°C

30 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety Advice

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(e)(840)839: The EU limit value for this product (product category: IIB.e) in ready-for-use form is max 840 g/l. The VOC content of this product is 839 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France