

GlossTOP+

C 2A64 Clear coat, superior gloss



by Surventis

Application	Advance Series - Clear coat especially for ONYX HD basecoat.
Key Features	Clear coat for superior gloss and high end result.
Remarks	Select hardener and thinner according to ambient temperature and size of object to be painted.

Mixing Ratio	2:1 + 10%		
	Mixing Ratio	100 % by volume	C 2A64 - Clear coat, superior gloss
	Hardener	50 % by volume	H 2A14 - Topcoat hardener, fast H 2A24 - Topcoat hardener, medium H 2A34 - Topcoat hardener, slow
	Thinner	10 % by volume	R 2A14 - Thinner, fast R 2A24 - Thinner, medium R 2A34 - Thinner, slow

Spray Viscosity		at 20°C	DIN 4: 19-23 s ISO 4: 45-60 s
------------------------	---	----------------	----------------------------------

Potlife at 20°C	2 h
------------------------	-----

Application			
		Compliant Gravity Spray Gun	HVLP Spray Gun
Application Pressure	2 bar		
Nozzle Pressure		0.7 bar	
Nozzle Size	1.3 -1.4	1.3 -1.5	
Number of Coats	2		
Flash Off at 20°C	3 - 5 min. intermediate flash off between the spray coats. No flash off before drying.		
Film thickness	40-60 µm		
Remarks	Alternatively: 1 ½ spray coats (no flash off between coats required).		

GlossTOP+

C 2A64 Clear coat, superior gloss



by Surventis

Drying



Drying at 20°C 10 h



Drying at 60°C 30 min



Infrared (short wave) 8 min

Drying Remark

Drying times can be influenced by the selection of hardener, thinner and application. Additive A 2A14 SpeedADD can reduce drying times.

Remarks

Polishing after specified drying time and cooling.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety Advice

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France