

UV Finish-R

C 2P30 UV Finish-R



by Surventis

Application Pioneer Series - eSense clear coat for R-M waterborne basecoats.

Key Features Eco effectiveness UVA curing clear coat - ultra low VOC. Specially designed for BLEND'ART with best in class process time.

Mixing Ratio

1:1



Mixing Ratio

100 % by weight

C 2P30 - UV Finish-R



Thinner

100 % by weight

R 2P30 - PIONEER Series Thinner

Spray Viscosity



at 20°C

DIN 4: 19 s

ISO 4: 45 s

Potlife at 20°C

8 h

Application	
 Compliant Gravity Spray Gun	
Application Pressure	1.5 -2 bar
Nozzle Size	1
Number of Coats	½ + 1
Flash Off at 20°C	No flash off required between coats or before curing.
Remarks	Do not over apply. Allow a few seconds after application for clear coat levelling before applying further material, if appearance is not as required.

Drying

Drying Remark Positioning and distance of lamp to painted surface is critical for required curing result.

Remarks

Ensure the energy output of the UV curing equipment is checked regularly. The performance of the light source will deteriorate over time and also with use.
Please follow the recommendations of the equipment supplier in regards of operation hours and UV-measurement, to ensure that the needed UV-energy is being provided.

UV Finish-R

C 2P30 UV Finish-R



by Surventis

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety Advice

It cannot be ruled out that this product contains particles $< 0.1 \mu\text{m}$. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(d)(420)270: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 g/l. The VOC content of this product is 270 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France