

SATIN Finish-R

C 2P96 eSense clear coat, silk mat



by Surventis

Application	Pioneer Series - eSense clear coat for R-M basecoats.
Key Features	Eco effectiveness clear coat - silk mat. Suitable for the repair of mat OEM finishes.
Remarks	Mix with MAT Finish-R C 2P91 eSense clear coat in order to achieve desired gloss level. Stir well before use. SATIN Finish-R C 2P96 must not be used in mixing shelves. When using H 2P96 this will decrease the gloss level. Stagger overlaps on the first and second coat. If necessary, up to 10% R 2P25 / R 2P35 can be added. (By adding additional thinner this can lower the gloss level). By using H 2P95 the flash off time should not be more than 25 min.

Mixing Ratio	2:1	
	Mixing Ratio	200 % by volume C 2P96 - eSense clear coat, silk mat
	Hardener	100 % by volume H 2P95 - eSense topcoat hardener, mat H 2P96 - eSense topcoat hardener, mat slow

Spray Viscosity		at 20°C	DIN 4: 16-19 s ISO 4: 32-36 s
------------------------	---	----------------	----------------------------------

Potlife at 20°C	2 h
------------------------	-----

SATIN Finish-R

C 2P96 eSense clear coat, silk mat



by Surventis

Application			
	Compliant Gravity Spray Gun		HVLP Spray Gun
Application Pressure	2 bar		
Nozzle Pressure			0.7 bar
Nozzle Size	1.2 -1.3		1.3
Number of Coats	2		
Flash Off at 20°C	Flash off until mat between spray coats and before drying.		
Film thickness	40-50 µm		

Drying



Drying at 20°C 8 h



Drying at 60°C 30 min



Infrared (short wave) 10 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



SATIN Finish-R

C 2P96 eSense clear coat, silk mat



by Surventis

Safety Advice

It cannot be ruled out that this product contains particles $< 0.1 \mu\text{m}$. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(e)(840)629: The EU limit value for this product (product category: IIB.e) in ready-for-use form is max 840 g/l. The VOC content of this product is 629 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France