


GHD CLEAR

C 5450 GRAPHITE HD CLEAR



by Surventis

Application



busses, sign writing, metallic coating (line ONYX HD), boxes, busses (repair)

Key Features

- suitable for large areas / surfaces
- good leveling
- excellent UV resistance
- outstanding application characteristics
- excellent gloss level

Remarks

The substrate must be clean, free of dust, rust, oil and grease.

Solid Content

~61% (RFU~56%)

Spreading Rate

505 m²/l at 1 µm

Mixing Ratio

300:100:100



Main product

300 % by volume

C 5450 - GRAPHITE HD CLEAR



Hardener

100 % by volume

H 750 - Topcoat hardener, normal
H 700 - Topcoat hardener, fast
H 770 - Topcoat hardener, slow premium



Thinner

100 % by volume

GV 300 - Thinner, slow
GV 400 - Thinner, very slow
GV 200 - Thinner, medium

Spray Viscosity



at 20°C

DIN 4: 18-22 s

Potlife at 20°C

2 h

GHD CLEAR

C 5450 GRAPHITE HD CLEAR



by Surventis

Application	 Compliant Gravity Spray Gun	 Suction Cup	 Pressure pot dbl.-pump
Application Pressure	2.2 -2.5 bar	2.5 bar	2.5 bar
Material Pressure			0.8 -1.5 bar
Nozzle Size	1.3 -1.4	1.7	1 -1.1
Number of Coats	1.5		
Flash Off at 20°C	without		
Film thickness	40-60 µm		

Drying	Overcoatable	Tack-Free	Ready for Masking	Ready to Assemble	Sandable
 20°C	max. 16 h	2 h	16 h	12 h	16 h
 60°C	30 min	30 min	30 min	30 min	30 min

Remarks

Application: Pre-spray 1 light coat, then apply 1 wet coat for flow.
Recoatable with itself for up to 16 hours after application (drying at room temperature).

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety Advice

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 g/l. The VOC content of this product is 419 g/l.

GHD CLEAR

C 5450 GRAPHITE HD CLEAR



by Surventis

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France