


GHD TOPCOAT

Glossy



by Surventis

Application



all applications

Key Features

- suitable on all R-M CV primer filler and filler
- suitable for large areas / surfaces
- very good leveling and appearance
- excellent UV resistance
- fast drying
- excellent surface hardness
- good hiding power

Remarks

The substrate must be clean, free of dust, rust, oil and grease
The complete color range for CV application is covered.
Best topcoat finish in combination with H 770 slow Premium

Substrates

Steel	Blasted Steel	Galvanized Steel	Stainless Steel	Aluminium / Anodized Aluminium
-	-	-	-	-
OEM / Old Paintwork	Powder coated / Coil coated	GRP / SMC	CV Primer	CV Filler / CV Primer Filler
▲	-	-	-	●●

●● very well suited, ● well suited, ▲ suited in some cases, - not suited

Solid Content

~69%

Spreading Rate

536 m²/l at 1 µm

GHD TOPCOAT

Glossy



by Surventis

Mixing Ratio

100:25:25


Main product

100 % by volume

GHD TOPCOAT



Hardener

25 % by volume

H 750 - Topcoat hardener, normal
H 770 - Topcoat hardener, slow premium
H 700 - Topcoat hardener, fast



Thinner

25 % by volume

GV 300 - Thinner, slow
GV 400 - Thinner, very slow
GV 200 - Thinner, medium

Spray Viscosity



at 20°C

DIN 4: 20-23 s

Potlife at 20°C

1.5 h

Application	 Compliant Gravity Spray Gun	 Suction Cup	 Airless / Airmix	 Pressure pot dbl.-pump
Application Pressure	2.2 -2.2 bar	2.5 bar	2 bar	2.5 bar
Material Pressure			120 -180 bar	0.8 -1.5 bar
Nozzle Size	1.3 -1.4	1.7	0.23 -0.28	1 -1.1
Voltage			50 -80 kV	
Electric Resistance			700 -1500 Ω	
Number of Coats	1.5			
Flash Off at 20°C	without			
Film thickness	40-60 µm			

GHD TOPCOAT

Glossy



by Surventis

Drying	Overcoatable	Tack-Free	Ready for Masking	Ready to Assemble	Sandable
 20°C	max. 16 h	2.5 h	16 h	12 h	16 h
 60°C	30 min	30 min	30 min	30 min	30 min

Remarks

Application: Pre-spray 1 thin grip coat with the finishing coat following immediately.
 Process time: ~ 45 Min. with H 700 / ~ 1h with H 750 and ~ 2h mit H 770.
 Drying: 30 Min. 60°C with H 750; 45 - 60 Min. at 60°C with H 770.
 Recoatable with itself without intermediate sanding for up to 16 hours after application of first coat.
 Pre-spray adhesion promoter TRANSPARENT SEALER CP prior to multi-colour finishing if painted surface was baked or flashed-off for 16 h. For Airless or Airmix application use CV 38M instead of CV 70M.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety Advice

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France