

Primer filler, grey

P 2E23 Primer filler, grey



by Surventis

Application 2-component filler based on polyurethane.

Key Features Filler featuring good sanding and filling properties.

Handling



Product suitable on

- Sheet steel
- Aluminium
- OEM parts with e-coat
- Old paintwork
- GRP / SMC

Mixing Ratio

4:1:1



Mixing Ratio

100 % by volume

P 2E23 - Primer filler, grey



Hardener

25 % by volume

H 2E23 - Filler hardener



Thinner

25 % by volume

R 2E10 - Thinner, fast
R 2E20 - Thinner, medium
R 2E30 - Thinner, slow

Spray Viscosity



at 20°C

DIN 4: 20-24 s
ISO 4: 50-65 s

Potlife at 20°C

1 h

Primer filler, grey

P 2E23 Primer filler, grey



by Surventis

Application		
	Compliant Gravity Spray Gun	HVLP Spray Gun
Application Pressure	2 bar	
Nozzle Pressure		0.7 bar
Nozzle Size	1.6 -1.8	1.7 -1.9
Number of Coats	2	
Flash Off at 20°C	Flash off between spray coats until mat, no flash off before drying.	
Film thickness	50-70 µm	

Drying


Drying at 20°C 3 h

Drying at 60°C 30 min

Infrared (short wave) 10 min

Sanding


Orbital sanding, dry P400 - P500

Remarks

Use Guide Coat for a better sanding result.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety Advice

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(ci)(540)539: The EU limit value for this product (product category: IIB.ci) in ready-for-use form is max 540 g/l. The VOC content of this product is 539 g/l.

Primer filler, grey

P 2E23 Primer filler, grey



by Surventis

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France