

SANDING Fill-R+ White

P 2P51 eSense primer filler, white



by Surventis

Application Pioneer Series - eSense undercoat solutions.

Key Features Eco effectiveness - primer filler and filler.
For outstanding productivity due to excellent sanding properties and finish, good corrosion protection and weathering resistance.

Remarks Can be mixed with SANDING Fill-R+ Black at any ratio to produce different shades of grey.

Handling



Product is suitable on

- OEM parts with e-coat
- Old paintwork
- GRP / SMC

If bare metal areas are primed, the product can be used on

- Sheet steel
- Galvanized sheet steel
- Aluminium

Mixing Ratio

4:1:1



Mixing Ratio

100 % by volume

P 2P51 - eSense primer filler, white



Hardener

25 % by volume

H 2P84 - eSense Fill-R hardener



Thinner

25 % by volume

R 2P20 - eSense undercoat thinner, medium
R 2P15 - eSense thinner, fast
R 2P25 - eSense thinner, medium
R 2P35 - eSense thinner, slow

Spray Viscosity



at 20°C

DIN 4: 18-23 s
ISO 4: 40-68 s

Potlife at 20°C

60 min

SANDING Fill-R+ White

P 2P51 eSense primer filler, white



by Surventis

Application	 Compliant Gravity Spray Gun	 HVLP Spray Gun
Application Pressure	2 bar	
Nozzle Pressure		0.7 bar
Nozzle Size	1.6 -1.8	1.7 -1.9
Number of Coats	2	
Flash Off at 20°C	Flash off between spray coats until mat, no flash off before drying.	
Film thickness	50-70 µm	

Drying



Drying at 20°C 3 h



Drying at 60°C 20 min



Infrared (short wave) 9 min

Sanding



Orbital sanding, dry P400 - P600

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



SANDING Fill-R+ White

P 2P51 eSense primer filler, white



by Surventis

Safety Advice

It cannot be ruled out that this product contains particles $< 0.1 \mu\text{m}$. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(ci)(540)539: The EU limit value for this product (product category: IIB.ci) in ready-for-use form is max 540 g/l. The VOC content of this product is 539 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France