

Race WET Fill-R White

P 2P81 eSense wet-on-wet filler, white



by Surventis

Application	Pioneer Series - eSense undercoat solutions.
Key Features	Eco effectiveness - wet-on-wet filler. For very fast repair of new panels due to no sanding and no drying times, with only 5 min flash off. No need to sand new e-coated parts.
Remarks	P 2P81 can be mixed with P 2P85 to achieve different grey shades. See temperature chart for choosing right thinner in combination with H 2P80 (please refer to the info R-M module "Temperature table for R-M undercoat products").

Handling



Product is suitable on

- OEM parts with e-coat
- Old paintwork
- GRP / SMC

If bare metal areas are primed, the product can be used on

- Sheet steel
- Galvanized sheet steel
- Aluminium

Mixing Ratio

3:1:1



Mixing Ratio

100 % by volume

P 2P81 - eSense wet-on-wet filler, white



Hardener

33 % by volume

H 2P80 - eSense filler hardener



Thinner

33 % by volume

R 2P25 - eSense thinner, medium
R 2P35 - eSense thinner, slow
R 2P45 - eSense thinner, extra slow

Spray Viscosity



at 20°C

DIN 4: 14-16 s
ISO 4: 25-30 s

Potlife at 20°C

60 min

Race WET Fill-R White

P 2P81 eSense wet-on-wet filler, white



by Surventis

Application		
	Compliant Gravity Spray Gun	HVLP Spray Gun
Application Pressure	2 bar	
Nozzle Pressure		0.7 bar
Nozzle Size	1.3 -1.4	
Number of Coats	1 One additional thin spray coat can be applied over breakthrough areas first.	
Flash Off at 20°C	5 min	
Film thickness	20-35 µm	

Remarks

Apply topcoat wet on wet.
Parts coated with P 2P81 can be over coated without intermediate sanding within 3 hours.
Intermediate sanding with P800 – P1200 is required when flash off time exceeds 3 hours.

Please note: For automotive refinishing, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety Advice

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(ci)(540)539: The EU limit value for this product (product category: IIB.ci) in ready-for-use form is max 540 g/l. The VOC content of this product is 539 g/l.

Race WET Fill-R White

P 2P81 eSense wet-on-wet filler, white



by Surventis

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France