

GHD UNIVERSAL EPOXY

P 5480 GHD UNIVERSAL EPOXY



by Surventis

Application



busses, fire-fighting vehicle, boxes, bulk loading vehicles, boxes (aluminum)

Key Features

- suitable on many metal substrates
- very good levelling
- good filling properties
- all-purpose
- outstanding corrosion protection
- tintable with GHD TINTING PASTE
- overcoating with GRAPHITE HD, ONYX HD, DIAMONT *

Remarks

The substrate must be clean, free of dust, rust, oil and grease.

* For overcoating with ONYX HD or DIAMONT flash off of 1h at 20°C is mandatory.

Because of the variety of metal alloys and manufacturing processes, it is recommended to carry out a preliminary adhesion test before application.

A 5480 GHD ADDITIVE for UNIVERSAL EP 15 - 30°C

Substrates

Steel	Blasted Steel	Galvanized Steel	Stainless Steel	Aluminium / Anodized Aluminium
••	••	••	••	••
OEM / Old Paintwork	Powder coated / Coil coated	GRP / SMC	CV Primer	CV Filler / CV Primer Filler
•	••	••	-	-

•• very well suited, • well suited, ▲ suited in some cases, - not suited

Solid Content

~ 77% (RFU~63%)

Spreading Rate

430 m²/l at 1 µm

GHD UNIVERSAL EPOXY

P 5480 GHD UNIVERSAL EPOXY



by Surventis

Mixing Ratio

100:25:25



Main product

100 % by volume

P 5480 - GHD UNIVERSAL EPOXY



Hardener

25 % by volume

H 5480 - GHD UNIVERSAL EP
HARDENER



Thinner

25 % by volume

A 5480 - GHD ADDITIVE for
UNIVERSAL EP

Spray Viscosity



at 20°C

DIN 4: 19-22 s

Potlife at 20°C

8 h

Application	 Compliant Gravity Spray Gun	 Suction Cup	 Airless / Airmix	 Pressure pot dbl.-pump
Application Pressure	2.2 -2.5 bar	2.5 bar	2 bar	2.5 bar
Material Pressure			120 -150 bar	0.8 -1.5 bar
Nozzle Size	1.4 -1.6	1.7	0.28 -0.33	1 -1.1
Voltage			50 -80 kV	
Electric Resistance			600 -900 Ω	
Number of Coats	1.5 - 2			
Flash Off at 20°C	10 -15 min			
Film thickness	50-70 µm			

GHD UNIVERSAL EPOXY

P 5480 GHD UNIVERSAL EPOXY



by Surventis

Drying	Overcoatable	Tack-Free	Ready for Masking	Ready to Assemble	Sandable
 20°C	1-72 h	3 h	16 h	16 h	
 60°C	30 min	30 min	30 min	30 min	50 - 60 min

Remarks

Minimum ambient temperature during application and drying: +15°C .
 For overcoating with ONYX HD or DIAMONT flash off at least at 1 h 20°C mandatory, maximum flash off time: within one working day (for over coating with GRAPHITE HD 72 h).
 Do not adjust P 5480 with reducer GV, only with A 5480 GHD ADDITIVE for UNIVERSAL EP!
 The first coat has to be a light closed coat followed after flash off by a second full wet coat.
 On blasted substrates take care of the roughness depth.
 There is no need to sand P 5480 because of the very good levelling. If sanding is required: Drying of 50 - 60 min at 60°C object temperature or 16 h at 20°C is necessary.
 For tinting see variant with GHD TINTING PASTE.
 Before applying polyester products P 5480 has to be dried for at least 45 min 60°C (object temperature). The adhesion on hot dipped galvanized steel has to be checked before.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety Advice

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(ci)(540)493: The EU limit value for this product (product category: IIB.ci) in ready-for-use form is max 540 g/l. The VOC content of this product is 493 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France