

GHD UNI WASH

P 5530 GHD UNI WASH, beige



by Surventis

Application



busses, fire fighting truck, flatbeds (aluminum), boxes, bulk loading vehicles (aluminum)

Key Features

- good levelling and flow
- suitable for large areas / surfaces
- quick drying
- very good corrosion protection
- tintable with max. 3% GHD TINTING PASTE
- 2-layer directly with GRAPHITE HD TOPCOAT

Remarks

The substrate must be clean, free of dust, rust, oil and grease

Substrates

Steel	Blasted Steel	Galvanized Steel	Stainless Steel	Aluminium / Anodized Aluminium
••	-	••	••	••
OEM / Old Paintwork	Powder coated / Coil coated	GRP / SMC	CV Primer	CV Filler / CV Primer Filler
▲	▲	▲	-	-

•• very well suited, • well suited, ▲ suited in some cases, - not suited

Solid Content

~34% (RFU ~22%)

Spreading Rate

~ 196 (124) m² / l / 1µm

Mixing Ratio

100:25:25



Main product

100 % by volume

P 5530 - GHD UNI WASH, beige



Hardener

25 % by volume

H 5430 - GHD SLOW ACTIVATOR



Thinner

25 % by volume

GV 300 - Thinner, slow

GV 400 - Thinner, very slow

GHD UNI WASH

P 5530 GHD UNI WASH, beige



by Surventis

Spray Viscosity



at 20°C

DIN 4: 22-24 s

Potlife at 20°C

8 h

Application	 Compliant Gravity Spray Gun	 Suction Cup	 Airless / Airmix	 Pressure pot dbl.-pump
Application Pressure	2.2 -2.5 bar	2.5 bar	2 bar	2.5 bar
Material Pressure			120 -150 bar	0.8 -1.5 bar
Nozzle Size	1.4 -1.8	1.7	0.28	1 -1.1
Number of Coats	2 -2.5			
Flash Off at 20°C	until mat			
Film thickness	20-25 µm			

Drying	Overcoatable	Tack-Free	Ready for Masking	Ready to Assemble	Sandable
 20°C	30-480 min				
 60°C	10 min				

Remarks

Do not overcoat P 5530 directly with solventborne or waterborne basecoats, GHD CV12 (RAL 9006), polyester or epoxy products.

2 - 2,5 spray coats (20 - 25µm) for 2-layer system with topcoat.

Apply topcoat on UNI WASH within one working day (8 hours). Do not use on blasted substrates.

On anodized alu and hot-dip galvanized steel, adhesion must be tested beforehand.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

GHD UNI WASH

P 5530 GHD UNI WASH, beige



by Surventis

Safety Advice

It cannot be ruled out that this product contains particles $< 0.1 \mu\text{m}$. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIB(ciii)(780)729: The EU limit value for this product (product category: IIB.ciii) in ready-for-use form is max 780 g/l. The VOC content of this product is 729 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Refinish Coatings by Surventis Z.I de Breuil-le-Sec, rue AndréPommery, 60840 Breuil-le-Sec, France