

VARNISH 1500 FR

FIRE RETARDANT FINISHES FOR CABIN INTERIORS | AkzoNobel / Mapaero

1 / 3 - Product information

Product information

Three-component polyurethane varnish with high solid content, designed to protect aircraft cabin interiors. This varnish provides topcoat ranging from matt to gloss in cabin interiors.

Components

Base 1500 FR; Hardener / Catalyst 1500 FR; Thinner FRSL.

Specifications

Qualified in accordance with Pilatus PMS0600-52-02. Meets JAR / FAR Part 25 §25.853 (a), (c/d), Change 14 / Amendment 25-83.

Physical properties

Theoretical coverage: 9 m²/L for 50 µm dry, base and hardener undiluted. Dry film weight: 1.1. VOC: 497 g/L base + hardener; 560 g/L at 24% dilution. Shelf life: 48 months for gloss base and thinner; 12 months for base and hardener, stored between 5 °C and 35 °C in sealed original packaging. Gloss levels: gloss, semi-gloss and matt.

Surface preparation

Apply on FRS40 polyurethane top coat. Slightly sand FRS40 with P400 abrasive.

VARNISH 1500 FR

FIRE RETARDANT FINISHES FOR CABIN INTERIORS | AkzoNobel / Mapaero

2 / 3 - Instructions for use

Mixing ratio

By weight: Base 100; Hardener/Catalyst 50; Thinner 0 to 50. By volume: Base 2 V; Hardener/Catalyst 1 V; Thinner 0 to 1 V.

Mixing procedure

Store unmixed products between 18 °C and 25 °C for 24 hours before use. Mix semi-gloss and matt base for 10 minutes. Mix base and hardener until homogeneous, then add thinner. Make the mixture between 15 °C and 35 °C. Sieve with an 80 to 150 µm filter.

Application data

Induction time: none. Spraying viscosity at 20 °C: CA 4, 22 s ± 5 s at 0% dilution. Pot life: 3 hours. Application temperature: 15 °C to 35 °C. Relative humidity: 30% to 75%. Gravity compressed air gun nozzle: 1.2 to 1.8 mm. Dry film thickness: 40 to 60 µm. Wet film thickness: 90 to 130 µm.

Number of coats

Apply a crossed coat, allow 30 minutes flash-off, then apply another crossed coat to obtain 40 to 60 µm dry thickness. Clean equipment with Mapaero FRSL or another appropriate solvent. Spray with dry, oil-free air.

VARNISH 1500 FR

FIRE RETARDANT FINISHES FOR CABIN INTERIORS | AkzoNobel / Mapaero

3 / 3 - Drying times and safety

Drying at 23 °C

Dust free: 1 hour. Dry to tape: 6 hours. Recoatable: not applicable. Fully cured: 7 days / 168 hours.

Drying at 60 °C

Dust free: not applicable. Dry to tape: 2 hours. Recoatable: not applicable. Fully cured: 12 hours.

Notes

Drying times were determined using test pieces less than 2 mm thick with 50 µm dry film. For defects, contact the Quality Department.
See product safety data sheets for health and safety.

Packing