

**FLEXSOL 3000® INTERIOR LINING**

- A. All interior surfaces shall be grit blasted to white metal condition with a 3-4 mil profile. Blasted surfaces shall be cleaned of all dust or blast residue. Lining shall be applied as soon as is practical on the same day blasting is done.
- B. Flexsol 3000® shall be a urethane, 100% solid plural component lining. Hardness shall be 75 durometer on the shore D scale. Break tensile strength shall be 4000 psi with elongation of less than 10%. Adhesion shall be greater than 2500 psi.
- C. Application of Flexsol 3000® lining shall be done by experienced applicators using a high pressure, high temperature plural component system. All wetted surfaces including flange faces, manway rings and manway covers shall be lined to 100 mils +/- 10 mils WFT.
- D. Hardness shall be verified after curing to ASTM D 2240 standard.
- E. Manufacturer shall submit for approval a sample piece of coated steel to determine flexibility, abrasion tolerance and adhesion integrity.
- F. Flexsol 3000® lining shall meet the NSF toxicity standard unconditionally and shall be approved for use with the NSF approved filter.
- G. Flexsol 3000® lined vessels shall carry a ten-(10) year limited non-prorated warranty against tank leaks.
- H. The filter manufacturer shall bear the responsibility for suitability of lining and shall be the sole source for the specified warranty.