

Week 8


Light Emitters 1

OLED Basics

Quantifying Efficiency for Displays and Lighting


Chapter 6.1 – 6.3

Concepts in Organic Electronics
Stephen R. Forrest




Objectives

- Learn about vision: what makes a good display or lighting fixture?
- Gain a knowledge of how fundamental properties of organics leads to arguably the most important organic electronic device: OLEDs
- Learn about challenges yet to be met before OLEDs completely dominate the display market
- Learn about the challenges for lighting





OLEDs


- Basic concepts
- Displays and Lighting
 - R-G-B pixelation
 - WOLEDs
 - TOLEDs
- Getting light out
- Intensity roll-off and annihilation
- Device reliability




Organic Light Emitting Diode (OLED)



$$\eta_{\text{EQE}} = 1\%$$






electrons and holes form excitons (bound e⁻-h⁺ pairs)



Concepts in Organic Electronics
Stephen R. Forrest


First Polymer OLED




Recombination zone not well-defined

Burroughes, et al. *Nature*, **347**, 539 (1990).

Organic Electronics
Stephen R. Forrest




Benefits of OLEDs




- Can be prepared on any substrate - active materials are amorphous
- Low cost materials and fabrication methods, scalable to large area
- Readily tuned color and electronic properties *via* chemistry
- Can be transparent when off
- Device characteristics
 - Efficiency $\sim 100\%$ demonstrated, white $> 150 \text{ lm/W}$
 - $> 1,000,000$ hour (100 years) lifetime
 - Can be very bright: 10^6 cd/m^2 , CRT = 100 cd/m^2 , fluorescent panel = 800 cd/m^2
 - Turn-on voltages as low as 3 V

Concepts in Organic Electronics
Stephen R. Forrest



Transparent OLED (TOLED)




- Devices can be > 90% transparent
- Thin metal or electron injection layer is capped with ITO
- Transparent cathode can also be used to prepare top emitting structures
 - OLEDs on metal sheets
 - OLEDs on Si backplanes in AMOLED displays


Bulovic, V., et al. Nature, **380**, 29 (1996).



Concepts in Organic Electronics
Stephen R. Forrest




OLED vs. Liquid Crystal Displays (LCDs)



Display Technologies


Color Mixing




LCD

OLED
Plasma
CRT


Concepts in Organic Electronics
Stephen R. Forrest





LCD/LED Displays





1 Organic Electronics
Stephen R. Forrest




Two Types of OLED Displays




- RGB pixels
- Top emitting
- Dominates mobile (Samsung)



- WOLED pixels + Color filters
- Top emitting
- Dominates TVs (LG)



How We See Color: Tri-Stimulus Curves and Chromaticity



Tri-stimulus values

$$X = \int I(\lambda) \bar{x}(\lambda) d\lambda$$

$$Y = \int I(\lambda) \bar{y}(\lambda) d\lambda$$

$$Z = \int I(\lambda) \bar{z}(\lambda) d\lambda$$

$I(\lambda)$ = un-normalized spectral intensity

CIE Coordinates

$$x = \frac{X}{X+Y+Z}; y = \frac{Y}{X+Y+Z}; z = \frac{Z}{X+Y+Z}$$

$$x + y + z = 1 \Rightarrow z = 1 - x - y$$




Scotopic vs. Photopic Vision Response



How things appear at night


Scotopic vision due to the rod cells
– only sense luminosity (brightness)
but not color

(simulation)





How things actually are at night

Photopic, or daytime vision senses color from
cone cells – but not capable at sensing low light
levels



North wall, Yosemite Valley, CA in March


Color spaces




Transforming between 1931 and 1976 spaces

$$u = \frac{4x}{-2x + 12y + 3}; \quad v = \frac{6y}{-2x + 12y + 3}$$

$$u' = u; \quad v' = \frac{3}{2} v.$$




Organic Electronics
Stephen R. Forrest




Planck's law of black body radiation


$$B(\lambda, T) = \frac{2hc^2}{\lambda^5} \left[\frac{1}{\exp(E_{ph}/k_B T) - 1} \right]$$



Concepts in Organic Electronics
Stephen R. Forrest



Limits to color perception




MacAdams Ellipses:


Define the amount of change in color that can be perceived

Each ellipse magnified 10X


Concepts in Organic Electronics
Stephen R. Forrest



Various Display Color Gamuts



Organic Electronics
Stephen R. Forrest



Light source definitions

$$\text{External quantum efficiency} = \frac{\text{No. photons viewed}}{\text{No. of electrons injected}} = \frac{q\lambda P_{\text{meas}}}{(hc) I_{\text{OLED}}}$$

$$\text{Internal quantum efficiency} = \frac{\text{No. photons emitted}}{\text{No. of electrons injected}} = \frac{q\lambda P_{\text{meas}}}{\eta_{\text{out}} (hc) I_{\text{OLED}}}$$


$$\text{Power efficiency} = \frac{\text{Optical power emitted}}{\text{Elect. power injected}} = \frac{P_{\text{meas}}}{I_{\text{OLED}} V_{\text{OLED}}} \quad [\text{W/W}]$$

$$\text{Luminance power efficiency} = \frac{\text{Luminance}}{\text{Elect. power injected}} = \frac{L_{\text{meas}}}{I_{\text{OLED}} V_{\text{OLED}}} \quad [\text{lm/W}]$$

$$\text{Luminance efficiency} = \frac{\text{Luminance}}{\text{Current injected}} = \frac{L_{\text{meas}}}{I_{\text{OLED}}} \quad [\text{cd/A}]$$

Luminance units: $\text{cd/m}^2 = \text{nits}$; $\text{cd} = \text{lumens}/\pi$ (for a Lambertian source)


Concepts in Organic Electronics
Stephen R. Forrest



Radiometric and Photometric Quantities

Radiometric units				Photometric units			
Quantity	Symbol	Expression	Unit	Quantity	Symbol	Expression	Unit
Radiant flux	Φ_e		W	Luminous flux	Φ		lm
External quantum efficiency	η_{ext}	$\eta_{int}\eta_{out}$	%	Luminous efficiency	η_L	$\frac{L}{j}$	cd/A
Power efficiency	η_P	$\frac{1}{jV} \frac{d\Phi_e}{dS} = \frac{E_e}{jV}$	%, or W/W	Luminous power efficiency	η_{LP}	$\frac{1}{jV} \frac{d\Phi}{dS} = \frac{E}{jV}$	lm/W
Radiant intensity	I_e	$\frac{d\Phi_e}{d\Omega}$	W/sr	Luminous intensity	L_Ω	$\frac{d\Phi}{d\Omega}$	lm/sr
Radiance	L_e	$\frac{d\Phi_e}{dS d\Omega \cos\theta}$	W/sr-m ²	Luminance	L	$\frac{d\Phi}{dS d\Omega \cos\theta}$	cd/m ² = lm/sr-m ²
Irradiance	E_e	$\frac{d\Phi_e}{dS}$	W/m ²	Illuminance	E	$\frac{d\Phi}{dS}$	lm/m ² = lux
Radiant exitance	M_e	$\frac{d\Phi_e}{dS}$	W/m ²	Luminous exitance	M	$\frac{d\Phi}{dS}$	lm/m ²

Concepts in Organic Electronics
Stephen R. Forrest



Radiometric: Light source properties quantified using standard scientific units


Photometric: Light source properties quantified by visual *perceptive* units

What is a Lambertian Source?

Lambert's cosine law: The radiant or luminous intensity from a diffuse radiator is proportional to the cosine of the angle, θ , of observation relative to the source.


$$\text{Thus } I = I_0 \cos \theta$$

Also called the **cosine emission law**



OLEDs are *approximately* Lambertian sources

Concepts in Organic Electronics
Stephen R. Forrest



Quantifying White Light

- Color rendering index (CRI)
 - Effect of an illuminant on the appearance of objects compared to that of a reference source (typically a black-body at a *correlated color temperature, CCT*)
 - CRI for white light sources should be >80 (i.e. <20% difference in integrated spectrum compared to black-body)


High CRI




Low CRI



Note dull reds




White light color space





Test color samples

Looking at white


Electronics
n R. Forrest



An example data set for an OLED




Concepts in Organic Electronics
Stephen R. Forrest




Measuring Quantum Efficiency

External QE



- Measure in forward (viewing) direction only
- Mask waveguided and scattered light
- Place OLED on detector for max. accuracy

Internal QE



- Measure using integrating sphere
- Must correct for losses in structure

Concepts in Organic Electronics
Stephen R. Forrest

