

(a)
load
(b)
torque
measured change / predicted change
1.0
0.8
0.6
0.4
filled: against the film function
open: against the rule
$\varepsilon = 0.3$
$\varepsilon = 0.6$
concentric
$K = 3$
$K = 1$
$K = 0.5$
2
4
8
16
32
narrowest gap / ℓ
narrowest gap / ℓ