



Test
TS EN ISO/IEC 17025
AB-0342-T

AB-0342-T

144384310

05/23

TÜV Rheinland
Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.
Saniye Ermutlu Sokak Çolakoğlu Plaza B Blok No :12 Kozyatağı-İSTANBUL

Page 1 of 8

Test Report

YAVUZÇEHRE TEKSTİL SAN. VE TİC. A.Ş

ALİ RIZA ÖZTÜRK CADDESİ., NO: 27., OSB 2. BÖLGE., DENİZLİ, Türkiye

Report No. 144384310
Buyer INDITEX
Test Item. : SAMPLE 1
Lot No. : "1.PARTİ"
Manufacturer : /
Fiber Content. : /
Colour Name. : "Mürdüm T-shirt"
Article No. : /
End Use. : /

Applicant's Provided -
Care Instruction/Label:

Sample Receiving date: 2023-05-29
Testing Period: 2023-05-29 to 2023-05-31
Report Date: 2023-05-31
Test Result: No Comment

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş. accredited by TÜRKAK under registration number AB-0342-T for ISO/IEC 17025-2017 as test laboratory

The Turkish Accreditation Agency (TÜRKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of the test reports.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following, pages which are part of this report

For and on behalf of
TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş

Tomris Hasançebi / Customer
Relations Manager

Kivanc Karatas / Chemical
Laboratory Manager

Abdullah Akil / Physical
Laboratory Manager

/ 2014-07-02

Version No / Date: 1.0

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.

Kozyatagi Mah. Saniye Ermutlu Sok. No:12
Colakoglu Plaza B Blok 34742 Kadikoy Istanbul,
Tel. +902166653200, Fax +902166653299, e-mail: info@tr.tuv.com

The results given in this report belong to the received sample by vendor.

This test report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid.

This test report is signed by digital signature.

TÜV Rheinland testing laboratories apply the Zero Guard band rule for statement of conformity evaluation, unless other decision rule is required by the customer.

1. Photo



2. List of Materials

Material List:

Material No.	Material	Color	Location
M001	Textile	-	SAMPLE 1

Conclusion:

TEST PROPERTY

M001

Colour Fastness To Water	#
Colour Fastness To Perspiration	#
Colour Fastness To Rubbing	#
Colour Fastness To Saliva	#
pH value	#
Colour Fastness To Light	#

AB-0342-T
144384310
05/23

1.Colour Fastness To Water

Test Method: Colour Fastness To Water (ISO 10966; ISO 105-E01)

	<u>M001</u>	<u>Requirement</u>
Colour change	4-5	-
Colour staining		-
- Acetate	4-5	-
- Cotton	4-5	-
- Polyamide	4-5	-
- Polyester	4-5	-
- Acrylic	4-5	-
- Wool	4-5	-

AB-0342-T
144384310
05/23

2.Colour Fastness To Perspiration

Test method : Colour Fastness To Perspiration (BS/DIN/EN/ISO 105-E04)

	<u>M001</u>		<u>Requirement</u>
	<u>Acid</u>	<u>Alkaline</u>	
Colour change	4-5	4-5	-
Colour staining			-
- Acetate	5	5	-
- Cotton	4-5	4-5	-
- Polyamide	5	5	-
- Polyester	5	5	-
- Acrylic	5	5	-
- Wool	5	5	-

AB-0342-T
144384310
05/23

3.Colour Fastness To Rubbing

Test method : Colour Fastness To Rubbing, Dry, Wet (BS/DIN/EN/ISO 105-X12)

	<u>M001</u>	<u>Requirement</u>
<u>Dry</u>	4-5	-
<u>Wet</u>	3	-

Remark : N/A = Not applicable due to limited sample dimension

AB-0342-T
144384310
05/23

4.Colour Fastness To Saliva

Test method : GB/T 18886-2019

	<u>M001</u>	<u>Requirement</u>
Colour change	4-5	-
Colour staining		-
- Acetate	5	-
- Cotton	4-5	-
- Polyamide	5	-
- Polyester	5	-
- Acrylic	5	-
- Wool	5	-

AB-0342-T
144384310
05/23

5.pH value

Test Method: ISO 3071:2020

Test Result:

Test No.	Material No.	Temperature of KCl°C	Average pH of KCL extract	Client Requirement	Conclusion
T001	M001	20.2	5.8	-	No Comment

AB-0342-T
144384310
05/23

6.Colour Fastness To Light

Test method : Colour Fastness To Light (BS/DIN/EN/ISO 105-B02)

Apparatus : Xenon-arc lamp

M001Requirement

Grade 3-4

-

Remark : Up to grade

- END -