



BTRA POWERLOOM SERVICE CENTRE

Linked to : THE MINISTRY OF TEXTILES, GOVERNMENT OF INDIA


Ref. BTRA-PSC/Test Report No. 448 to 451
Material Description : Dyed Terry Towel Fabric Sample.

Coded:-T.Blue

Submitted by :
Type of Test : Fabric Particulars (Page no. 1)

TEST RESULTS

Sr. No.	TYPE OF TESTS	RESULTS	METHOD OF TEST
1	Ends Per Inch	68.00	IS:1963/1981
	Ground Ends	34.00	
	Pile Ends	34.00	
2	Picks Per Inch	36.00	IS:1963/1981
3	G.S.M.	409.60	IS:1964/2006
4	Pile Warp Count (With dyed mat.add on)	15.98 Ne	IS:3442/1980
5	Ground Warp Count (With dyed mat.add on)	10.14 Ne	IS:3442/1980
6	Weft Count (With dyed mat.add on)	14.38 Ne	IS:3442/1980
7	Pile Ratio	1 : 4.25	Annex B of IS 7056
8	Pile Height	5.00 mm	
9	Fiber Composition	100 % Cotton	IS:667/RA 2015
10	Absorbency of Fabric	1.92 Seconds	IS:2349/RA 2016



Officer - incharge

N.B. The test results relate only to the items tested • Samples are not to be used for litigation/evidence/advertisement. The test report cannot be reproduced except in full without prior permission • The information contained in this letter and/or enclosed Report is/are purely meant for your guidance and should not be used for litigation/evidence/advertisement.

THE BOMBAY TEXTILE RESEARCH ASSOCIATION

LAL BAHADUR SHASTRI MARG, GHATKOPAR (WEST), MUMBAI - 400 086.

TEL. : 022-62023636 • Fax : 022- 25000459 • Email : info@btraindia.com • Website:www.btraindia.com

TEL : 022-62023636 • Fax : 022- 25000459 • Email : info@btraindia.com • Website: www.btraindia.com