Moisture Content Test Report

Client: QuickPack Industries · Material: 5-ply & 3-ply corrugated board, kraft liner
Method: oven-dry (IS 1060) · Samples tested: 12 · Result: 7.6% mean moisture (limit 9%)
Test date: 2026-10-20 · Lab: Southern Packaging Test Laboratory