

Non-additive Strain–Dopant Energetics in Quasi-Hexagonal C₆₀ Graphullerene

Xingqiang Chen and Qixing Wang

Department of Physics

Xiamen University

Xiamen 361005, China

(Dated: August 17, 2026)

Under mechanically constrained loading on quasi-hexagonal (qHP) C₆₀ graphullerene, measurable deviations from additive strain–dopant energetics arise because frozen elastic incompatibility introduces a bilinear strain–composition interaction that can reach magnitudes comparable to high-throughput screening margins—not because a finite-difference estimator is merely nonzero. The additive approximation in sequential workflows corresponds to neglecting the mixed second derivative $\partial^2 E / \partial \epsilon \partial \delta$ in the total-energy functional. Matched four-corner audits on periodic $n \times \text{C}_{60}$ supercells ($n = 1\text{--}8$, PBE+D3, affine biaxial strain with locked dopant sites) show that this term is large enough to change stability rankings for size-mismatched phosphorus ($|\mathcal{S}| = 31.9 \pm 2$ meV/atom at $n=1$, $\eta \approx 8\%$ at $n=4$). Cluster tetramer “strain” grids do not affine-scale the molecular coordinates and are not used as strain-physics evidence. The four-corner difference $\mathcal{S}$ estimates that coupling on the audited grid and is not a new thermodynamic observable. Only the size-mismatched substituent resolves clearly against the protocol floor— $|\mathcal{S}|$ reaches 12–16 times the 2 meV/atom reporting band for P at every audited size, against 1–6 for B and ~ 1 for N—so the coupling is set by covalent-radius mismatch rather than donor/acceptor character, in both sign and rank. Ionic relaxation of the periodic $n=1$ P four-corner recovers additivity to the reporting floor ($|\mathcal{S}_{\text{relaxed}}| < 10^{-3}$ meV/atom), consistent with a dominant elastic-work contribution under constrained load rather than a partitioned claim of intrinsic electronic cross-coupling. The audit signals when sequential additive workflows should be replaced by explicit coupled evaluations on the $E(\epsilon, \delta)$ landscape.

I. INTRODUCTION

Substitutional doping and mechanical strain are widely used to tune stability and electronic structure in covalent molecular networks [1, 2]. Sequential screens often add separate strain-only and substitution-only increments, dropping the mixed derivative $\partial^2 E / \partial \epsilon \partial \delta$ [1, 3, 4]. Cluster-expansion Hamiltonians already include composition–strain cross terms through constituent-strain and configurational interactions [5, 6]; what has been missing for soft fullerene networks is a matched four-corner total-energy audit under simultaneous load. Expanding the energy per atom $e(\epsilon, x) = E(\epsilon, \delta) / N_{\text{atoms}}$ about the pristine reference gives

$$e(\epsilon, x) \approx e_0 + a\epsilon + bx + c\epsilon x + \mathcal{O}(\epsilon^2, x^2, \epsilon^2 x, \epsilon x^2), \quad (1)$$

where $c = \partial^2 e / \partial \epsilon \partial x$ is the lowest-order bilinear coupling. The continuum coefficient $\gamma \equiv \partial^2 E / \partial \epsilon \partial \delta$ characterizes the intrinsic mixed response; the four-corner estimator $\mathcal{S}$ (Sec. II C) samples that response at +3% biaxial load and is a diagnostic, not a new thermodynamic observable (Supplemental Material, Sec. I).

We study quasi-hexagonal (qHP) C₆₀ graphullerene [7–9] as an elastically soft, experimentally accessible host. Substitutional B, N, and P form a donor, acceptor, and size-mismatch triad spanning both signs of covalent-radius mismatch relative to C ($\Delta r_{\text{cov}} = +7, -6$, and +30 pm; Table V). Prior DFT work maps strain and doping on separate grids or reports nonlinear electronic response without matched four-corner *total-energy* audits [3, 4, 8, 10–14]; a positioning table is in Supplemental Material, Table I. A substitutional defect on

a pre-strained cage, together with global biaxial load, can store elastic incompatibility that linear α does not capture. Here we test whether additive totals fail under joint (ϵ, δ) load, whether the omitted term matters under mechanically constrained configurations, and whether failure tracks covalent-radius mismatch rather than π -electron descriptors alone. The protocol is reported for one host; transferring it requires repeating the same (ϵ, δ, n) grid.

II. COMPUTATIONAL METHODS

A. Electronic structure method

All total-energy calculations use CP2K [15] with Goedecker–Teter–Hutter (GTH) pseudopotentials, the DZVP-MOLOPT-SR-GTH atom-centered basis, and the Gaussian and plane waves (GPW) scheme.

a. Exchange-correlation and dispersion. We use PBE [16] with Grimme DFT-D3 (Becke–Johnson damping) [17] for the production dataset. Hybrids or meta-GGAs (SCAN, r²SCAN) can shift absolute totals by tens of meV per atom in carbon networks; production rankings are therefore framed as *within-PBE+D3* comparisons of $\mathcal{S}$ among B, N, and P under matched load. The four-corner construction [Sec. II C] subtracts totals computed with identical XC, basis, dispersion, and numerical settings, so systematic shifts largely cancel when *ranking* dopants at fixed protocol—but cancellation is not assumed without audit: on the isolated-cage tetramer P grid (not a strained covalent network), Grimme-D3

non-additivity is $\mathcal{S}_{\text{vdW}} \approx +0.33$ meV/atom (Table I)—a cluster-protocol bound, not a strain-physics decomposition of periodic $\mathcal{S}$. No meta-GGA $\mathcal{S}$ values are reported (Table I; Limitations).

b. Plane-wave mesh and Brillouin-zone sampling. Plane-wave cutoffs are 400 Ry for $n \leq 4$ and 350 Ry for $n \geq 6$ (REL_CUTOFF 50 Ry; QS_EPS_DEFAULT $10^{-10} E_h$). Comparisons at fixed n always use the same cutoff. Production supercells contain 60–480 atoms with in-plane lattice constants up to ~ 44 Å at $n=8$; inputs use Γ -only sampling. Because $\mathcal{S}$ is a second-order difference on the *same* supercell, uniform k -point or cutoff shifts that co-drifts all four corners largely cancel in the four-corner estimator; sensitivity must be audited on $\mathcal{S}(\text{cutoff})$ and $\mathcal{S}(k)$, not on bare totals alone. A partial cutoff audit at $6 \times C_{60}$ N and +3% shifts one corner by only ~ 0.057 meV/atom between 350 and 400 Ry, implying $|\Delta\mathcal{S}| < 0.2$ meV/atom when only the mesh drifts (Table I). Dense- k ($2 \times 2 \times 1$) four-corner benchmarks on $n=1$ B/N/P at +3% are not included in the production set (Table I; Limitations); the smallest reported $|\mathcal{S}|$ values (2.3–3.0 meV/atom for N and B at $n=1$) are therefore interpreted with explicit Γ -only caution.

c. SCF convergence and four-corner precision. Unless noted otherwise, the SCF threshold is EPS_SCF = $10^{-6} E_h$ in inner and outer orbital-transformation loops (MAX_SCF 300; OUTER_SCF MAX 30). The $2 \times C_{60}$ cells are the exception: they cycled at 10^{-6} and were converged at $10^{-5} E_h$, which is why their pristine reference lies off the size-converged plateau and why we flag that row as reference-limited (Table I; Sec. IIIB). Charged-state workflows in the Supplemental Material tighten this to $10^{-7} E_h$; selected stiff tetramer corners may use $10^{-5} E_h$ when outer SCF cycling persists at 10^{-6} , which stays inside the ~ 2 meV/atom reporting floor of Table I. Because $\mathcal{S}$ is built from four independently converged totals [Eq. (2)], uncertainty is propagated as $\sigma_{\mathcal{S}} = 2\sigma_e$ for uncorrelated per-atom corner errors σ_e [Eq. (5); Supplemental Material, Sec. IE] (Table I). We use $\sigma_{\mathcal{S}} \lesssim 2$ meV/atom as the conservative reporting band on the $n \leq 4$ production grid.

d. Spin, charge, and mechanical boundary conditions. Substitutional periodic cells are charge-neutral closed-shell Kohn–Sham calculations (no spin polarization in the production $\mathcal{S}$ grid); Hirshfeld strain-path audits on $n=1$ B/N/P use spin-polarized KS only where odd electron counts require it (Sec. IID 3). We do not apply compensating background charge or charged supercells in the $\mathcal{S}$ audit: doping is modeled as neutral substitution.

B. Strain and doping models

Biaxial strain is $\epsilon = (a - a_0)/a_0 \times 100\%$, with a (a_0) the strained (equilibrium) in-plane lattice constant; $\delta \in \{\text{B, N, P}\}$. $\mathcal{S}$ is defined in Sec. IIC; π -projected densities of states are written π -DOS. Periodic $n \times C_{60}$ cells place one substituent per cage (~ 1.67 at.%) and affine-

scale both lattice vectors and Cartesian coordinates; that protocol supplies every $\mathcal{S}(n)$ value in this paper. Isolated-cage tetramer clusters ($4 \times C_{60}$, ~ 5 at.% substitution) are not a covalently networked monolayer: labeled tetramer “strain” grids change only the vacuum box and do not affine-scale the molecular coordinates, so they are not used as strain-physics evidence. The substitution energy $\Delta E_{\text{sub}} = (E_{\text{doped}} - E_{\text{pristine}})/n_{\text{dopants}}$ is not a formation enthalpy (no elemental chemical potentials).

a. Rigid vs. relaxed protocols. *Rigid strain* on periodic cells scales lattice vectors at fixed fractional coordinates and is the production protocol for $\mathcal{S}(n)$. It is an upper bound on $|\mathcal{S}|$ when internal stress cannot relax (epitaxial clamp, strong adhesion, or ultrafast load), not an equilibrium free-energy difference. *Relaxed strain* uses fixed-cell BFGS at each bilinear corner on the periodic $n=1$ P cell before evaluating $\mathcal{S}$ [Fig. 2(b)]. Force thresholds are 4.5×10^{-4} and 3.0×10^{-4} Ha/bohr (~ 0.023 and ~ 0.015 eV/Å) at $\epsilon=0$ and +3%, tighter than typical 0.02 eV/Å defaults so that near-zero relaxed $|\mathcal{S}|$ is resolved. Table II records a tetramer protocol diagnostic that is not a strain scan; Table III records a tetramer seed diagnostic that is likewise not strain physics. The physically interpreted ionic-relaxation and placement tests are the periodic $n=1$ P four-corner set and the periodic $n=4$ three-seed set (seeds 42, 137, and 271).

C. Strain–dopant coupling energy

$\mathcal{S}$ is the symmetric four-corner finite-difference estimator of $\gamma \equiv \partial^2 E / \partial \epsilon \partial \delta$ at +3% load—not an order parameter and not interchangeable with γ unless higher-order remainders are negligible (Supplemental Material, Table II and Sec. I).

$$\mathcal{S}(\epsilon, \delta) = \Delta E(\epsilon, \delta) - [\Delta E(\epsilon, 0) + \Delta E(0, \delta)], \quad (2)$$

with $\Delta E(\epsilon, \delta) = [E(\epsilon, \delta) - E(0, \text{pristine})]/N_{\text{atoms}}$ and $\delta=0$ denoting the pristine reference at the same supercell size $n \times C_{60}$. Equivalently, on corners $(0, 0)$, $(\Delta\epsilon, 0)$, $(0, \Delta\delta)$, $(\Delta\epsilon, \Delta\delta)$,

$$\mathcal{S}(\epsilon, \delta) = \frac{E(\epsilon, \delta) - E(\epsilon, 0) - E(0, \delta) + E(0, 0)}{N_{\text{atoms}}}, \quad (3)$$

which depends only on the four corner totals (reference independence).

a. Why a four-point stencil? Eqs. (2)–(3) are the minimal rectangular stencil that uses four DFT totals, is second-order accurate in the bilinear term, cancels first-order increments and a shared offset, and equals the additive-screening bias by construction. Asymmetric three-point schemes retain linear contamination; other estimators are compared in Supplemental Material, Sec. IC.

b. Finite-difference link to the mixed derivative. Expanding each corner total to second order and forming Eq. (3) cancels $E_\epsilon \Delta\epsilon$ and $E_\delta \Delta\delta$ identically (Supplemental Material, Sec. IB), yielding

$$\mathcal{S}(\epsilon, \delta) \approx \frac{\partial^2 E}{\partial \epsilon \partial \delta} \frac{\Delta\epsilon \Delta\delta}{N_{\text{atoms}}} + \mathcal{O}(\Delta\epsilon^2, \Delta\delta^2, \Delta\epsilon^2 \delta, \epsilon \delta^2), \quad (4)$$

so $\mathcal{S}$ reports the discrete mixed second derivative of total energy on the audited (ϵ, δ) grid. At finite +3% biaxial load and discrete B/N/P labels, higher-order terms in Eq. (4) are not separately resolved on the production periodic map; multi-amplitude strain audits ($\epsilon = 1\text{--}3\%$) are targeted sensitivity tests (Limitations). Throughout the main text, “nonlinear coupling” refers to a nonzero mixed response estimated by $\mathcal{S}$, not to $\mathcal{S}$ itself as a fundamental constant.

$\mathcal{S}$ is reported in meV per atom and is invariant under a uniform energy offset shared by all four corners (Supplemental Material, Sec. ID).

c. Error propagation. If each corner carries uncorrelated equal per-atom uncertainty σ_e ,

$$\sigma_{\mathcal{S}}^2 = 4\sigma_e^2, \quad \sigma_{\mathcal{S}} = 2\sigma_e, \quad (5)$$

from the four-term difference in Eq. (3) (derivation: Supplemental Material, Sec. IE). Table I lists contributions to the reporting band; we use $\sigma_{\mathcal{S}} \lesssim 2$ meV/atom as a conservative protocol floor on the $n \leq 4$ grid. $\mathcal{S} < 0$ (> 0) means the coupled corner is more (less) stable than the additive estimate. Additive-failure magnitude is

$$\eta \equiv \frac{|\mathcal{S}|}{|\Delta E_{\text{coupled}}|}, \quad (6)$$

where $\Delta E_{\text{coupled}} = (E(\epsilon, \delta) - E(0, 0))/N_{\text{atoms}}$.

D. Validation benchmarks

Interpretation rests on four checks: numerical hygiene (Table I); ionic relaxation of periodic $n=1$ P (Fig. 2(b)), the only valid large- $|\mathcal{S}|$ relaxation test; a cluster/vacuum-box diagnostic for tetramer P that does not strain the molecules (Table II); and periodic $n=4$ placement seeds 42, 137, and 271 (Table IV). Table III is a cluster configuration diagnostic, not a strain grid. Periodic $n=4$ P relaxation, B/N periodic relaxations, dense- k / meta-GGA four-corner checks, and two-body image tests beyond $n=8$ are not reported (Table I; Limitations). A calculation-group inventory is given only in the Supplemental Material.

1. Alternate-placement benchmark

An independent dopant configuration at the same nominal ~ 5 at.% loading repeats the B/N/P cluster map under PBE+D3 (Table III); that map does not affine-scale molecular coordinates. Main-text quantitative $\mathcal{S}(n)$

uses the periodic four-corner grid (Table IV); tetramer α and $\mathcal{S}_{+3\%}^{\text{tet}}$ are cluster diagnostics and are not mixed with those periodic values. At periodic $n=4$, two independent site maps repeat the four-corner Eq. (2) audit; the $|\mathcal{S}|$ ranking at +3% matches the production map in Table IV.

2. Ionic-relaxation benchmark

The tetramer pristine/ P four-corner BFGS grid does *not* affine-scale molecular coordinates (only the vacuum box changes), so Table II is an invalid cluster/vacuum-box diagnostic, not a strain-physics retention ratio. The valid ionic-relaxation test is the periodic $n=1$ P four-corner fixed-cell BFGS protocol (force thresholds 4.5×10^{-4} and 3.0×10^{-4} Ha/bohr, ~ 0.023 and ~ 0.015 eV/Å; displacement thresholds 3.0×10^{-3} and 1.5×10^{-3} bohr), reported in Fig. 2(b). These thresholds are tighter than typical 0.02 eV/Å defaults because relaxation can drive $|\mathcal{S}|$ toward zero and must be resolved at sub-meV/atom scale.

3. Hirshfeld population along strain

Hirshfeld atomic charges are computed along $\epsilon \in \{-5, -2.5, 0, +2.5, +3, +5\}\%$ on periodic $n=1$ B/N/P cells (spin-polarized KS for odd electron counts). They complement geometric $\bar{d}$ in Table V.

TABLE I. Error budget for four-corner $\mathcal{S}$ [Eq. (3)]. $\sigma_{\mathcal{S}} \approx 2\sigma_e$ when per-atom corner errors σ_e are uncorrelated and equal [Eq. (5)]; shared XC, k , and cell settings induce partial cancellation. Rows marked “not reported” are targeted sensitivity tests (Limitations); no meta-GGA or dense- k numbers appear without converged outputs. The reference-test rows use the fact that the pristine +3% strain cost per atom must be independent of supercell size: its deviation from the converged $n=1, 4, 6$ plateau is a measured systematic uncertainty on that row of $\mathcal{S}$, since $\mathcal{S}$ contains the pristine strain term with a negative sign. The ± 2 meV/atom band is a conservative protocol floor for the converged rows, not a quadrature sum, and does not cover the two reference-limited sizes.

Source	$ \Delta\mathcal{S} $ or $\sigma_{\mathcal{S}}$ (meV/atom)	Status
SCF (EPS_SCF = 10^{-6})	$\lesssim 2$ ($\sigma_{\mathcal{S}} \approx 2\sigma_e$)	Analytic bound
Pristine reference, $n=1, 4, 6$	≤ 0.06	Measured (reference test)
Pristine reference, $n=2$ (EPS_SCF = 10^{-5})	4.2	Measured (reference-limited row)
Pristine reference, $n=8$	5.4	Measured (reference-limited row)
Cutoff (350 vs 400 Ry)	< 0.2	Partial ($6 \times C_{60}$ N, +3%)
D3 cross term	$ \mathcal{S}_{\text{vdW}} \approx 0.33$	Tetramer P
D3 (B/N periodic)	—	Not reported
Ionic relaxation (periodic $n=1$ P ; $\mathcal{S}_{\text{rigid}} \rightarrow 0$)	$\gg 2$	Fig. 2(b)
k mesh (Γ vs $2 \times 2 \times 1$)	—	Not reported
XC (PBE+D3 vs SCAN / r ² SCAN)	—	Not reported
<i>Adopted reporting band ($n \leq 4$): ± 2 meV/atom.</i>		

TABLE II. Invalid cluster/vacuum-box diagnostic (not strain physics). The tetramer four-corner grid does not affine-scale molecular coordinates; the tabulated +1.19 meV/atom rigid value and ≈ 1.9 matched-functional ratio therefore do not bound monolayer $\mathcal{S}$. The valid large- $|\mathcal{S}|$ test is periodic $n=1$ P (PBE+D3, fixed-cell): $\mathcal{S}_{\text{rigid}} = -31.9$ meV/atom $\rightarrow \mathcal{S}_{\text{relaxed}} \approx 0$. Numbers below are retained only as a protocol diagnostic.

Quantity	Rigid (PBE+D3 matched)	Relaxed (geometry opt.)
$E(\text{pristine}, \epsilon=0)$ (E_h)	-1363.8769	-1363.9551
$E(\text{pristine}, \epsilon=3\%)$ (E_h)	-1363.8768	-1363.9550
$E(P, \epsilon=0)$ (E_h)	-1370.8552	-1374.4415
$E(P, \epsilon=3\%)$ (E_h)	-1370.8446	-1374.4615
$\mathcal{S}$ (meV/atom)	+1.19	-2.28
Sign of $\mathcal{S}$ vs. rigid	+	— (not preserved)

TABLE III. Alternate-placement tetramer cluster map (PBE+D3 rigid; seed 137; six vacuum-box labels per dopant). Cartesian coordinates are *not* affinely scaled, so this table is a configuration diagnostic, not a strain-physics grid. Not used for main-text figures or for the quantitative $\mathcal{S}(n)$ claims; periodic $\mathcal{S}(n)$ is in Table IV. Periodic $n=4$ placement (seeds 42, 137, and 271) is the valid generality test (ranking $P > B > N$ in all three maps). The cluster $|\alpha|$ vs. $|\mathcal{S}|_{n=4}$ comparison in Fig. 3(d) is qualitative only. Linear-fit standard errors on six-point cluster maps are of order 10^2 meV/%, so α entries are not resolved monolayer strain coefficients.

Dopant	Placement	α (meV/%)	$\mathcal{S}_{+3\%}^{\text{tet}}$ (meV/atom)
B	seed 137	-45	+1.9
N	seed 137	-60	+0.3
P	seed 137	+1028	-32.3

III. RESULTS

Total-energy audits use matched periodic supercells and the reference tetramer map (Sec. II C). Mechanism is deferred to Sec. IV.

A. Electronic structure under strain and doping

Figure 1(a) shows the reference tetramer: pristine and B/N/P-substituted cages at $\epsilon=0$ with highlighted substituent sites (covalent-radius excess in Table V). Panels (b)–(d) are archived cluster-map / vacuum-box slices, not monolayer biaxial-strain screens: the N π -DOS waterfall is stacked by the vacuum-box label; the frontier HOMO–LUMO separation E_{H-L} separates pristine, which retains 1.0–1.5 eV over the archived labels $\epsilon = -5$ to $+5\%$, from all three substituted cages, which close to $|E_{H-L}| \lesssim 0.2$ eV and are mutually indistinguishable at the $\epsilon=0$ snapshot within that window ($+0.03$, -0.14 , and $+0.05$ eV for B, N, and P); panel (d) is the pristine cluster-map ΔE path, not a monolayer mechanical α . The negative entries mark inverted frontier-level ordering (gap closure), not a physical negative gap, and PBE underestimates gaps, so only the pristine-vs.-substituted contrast is interpreted. Supplemental Material gives full π -DOS stacks and periodic VBM/CBM iso-surfaces (N size series; P $n=4$): frontier density remains cage-localized for $n = 2-6$.




FIG. 1. Archived tetramer cluster map (PBE+D3). Cartesian coordinates are *not* affinely scaled; labeled ϵ points change only the vacuum box. (a) qHP C_{60} tetramers at the archived $\epsilon=0$ snapshot: pristine (top left), B (top right), N (bottom left), P (bottom right), with substituent sites highlighted (covalent-radius excess in Table V). Heteroatoms and the key below the mosaic use CPK colors, which differ from the trajectory palette of panels (c) and (d). (b) N π -DOS vs. energy, stacked by the archived vacuum-box label ($E_F=0$). (c) Frontier HOMO-LUMO separation E_{H-L} from the archived π -DOS spectra. Pristine keeps a 1.0–1.5 eV gap; all three substituted cages close it to $|E_{H-L}| \lesssim 0.2$ eV, and the residual separation changes sign because the frontier levels cross—a gap-closure indicator, not a negative gap. PBE underestimates gaps, so only the pristine-vs.-substituted contrast is interpreted. These spectra are not monolayer biaxial-strain paths. (d) Pristine cluster-map ΔE vs. vacuum-box label (not a monolayer mechanical α). Periodic joint-load four-corner audits are in Fig. 2.

B. Non-additive strain-doping coupling

Figure 2 is the central audit. Panel (c) defines the test: strain-only and substitution-only increments are summed and compared with the coupled four-corner total; $\mathcal{S}$ [Eq. (3)] is that signed gap. Panel (a) and Table IV report the fifteen periodic +3% $\mathcal{S}(n, \delta)$ values. $|\mathcal{S}|$ shows no $1/n$ dilution: P remains large and negative through $n=8$ (23.7–31.9 meV/atom), B stays negative (2.2–11.3 meV/atom), and N stays at the reporting floor at every size that shares the plateau reference. The apparent n dependence must, however, be read against a reference test that the four-corner construction makes available at no extra cost. The pristine +3% strain cost per atom is the same physical quantity in every supercell, so its spread across n measures protocol reproducibility

directly. It is 2.99, 3.05, and 3.10 meV/atom at $n=1$, 4, and 6—reproducible to 0.06 meV/atom, two orders of magnitude tighter than the ± 2 meV/atom reporting band—but -1.18 meV/atom at $n=2$ and 8.49 meV/atom at $n=8$. Because $\mathcal{S}$ contains the pristine strain term with a negative sign, those two rows inherit systematic offsets of 4.2 and 5.4 meV/atom (Table I); the $n=2$ cells are the ones that required a relaxed EPS.SCF = 10^{-5} (Sec. II). Rescaling both references onto the converged plateau leaves $\mathcal{S}(n)$ nearly size-independent for each substituent—B -5.8 to -8.4 , N $+2.2$ to $+3.1$, P -23.7 to -32.5 meV/atom—and removes the sign change at $n=8$. We therefore report N as small and positive at all audited sizes and treat the $n=2$ and $n=8$ rows as reference-limited rather than as evidence of a size trend. At $n=4$, on the converged reference, $\mathcal{S} = -6.2 \pm 2$ (B), $+3.0 \pm 2$




FIG. 2. Additive strain-dopant screening fails under constrained load. (a) Fifteen periodic +3% $S(n, \delta)$ values vs. supercell size (markers: DFT; gray band: ± 2 meV/atom protocol floor). Error bars add the systematic offset of the pristine strain reference for that supercell, which is why the $n=2$ and $n=8$ bars are larger; pink columns mark those two reference-limited sizes (Table I). $|S|$ shows no $1/n$ dilution: P stays at ~ -24 to -32 meV/atom through $n=8$ and B stays negative at -2 to -11 . Only P lies far outside the band at every size; N sits at its edge, so the audit resolves a stratification and not a uniform failure of additivity. No S_∞ extrapolation. (b) Protocol bound, not a second size-scaling panel: periodic $n=1$ P at +3%, rigid vs. ionically relaxed S (near zero after stress release). Table II is an invalid cluster/vacuum-box diagnostic, not a strain-physics sign reversal. (c) Definition: additive sum of strain-only and substitution-only increments vs. the coupled four-corner total; S is that gap [Eq. (3)]. (d) Schematic $E(\epsilon)$ at fixed composition: the bilinear $c\epsilon\delta$ term bends the coupled path away from the additive sum (cartoon, not a DFT fit).

(N), and -23.7 ± 2 meV/atom (P), where $\pm$ is the conservative protocol floor (Table I). The three substituents are therefore not equally resolved. Referred to that floor, $|S|$ is 12–16 times the band for P at every audited size, 1–6 times for B, and ~ 1 –1.5 times for N except at $n=2$ (3.4); expressed as the additive-failure fraction of Eq. (6), $\eta = 8$ –12% for P but stays below 1% for B (0.2–0.9%) and N (0.1–0.4%). Only P is thus large enough on this grid to reorder stability, B carries a resolved but small cross term, and N sits at the detection floor—a stratification we treat as the main quantitative result rather than a uniform failure of additivity. The P extremum at $n=1$ (31.9 ± 2 meV/atom) may include enhanced periodic-image coupling at the smallest cell; it is not a separate materials constant. We do not extrapolate S_∞ . Rows with $n \geq 6$ (350 Ry) are in Supplemental Material Table S1. Negative S (B, P at $n=4$) means the coupled cor-

ner lies below the additive estimate; positive S (N) means it lies above. Panel (b) is the protocol bound on a different system from the tetramer row of Table II: periodic $n=1$ P at +3% falls from $S_{\text{rig}} \approx -31.9$ meV/atom to near zero after ionic relaxation. Table II also lists a matched-functional tetramer P grid (+1.19 vs. -2.28 meV/atom); that cluster protocol is not a strain scan and is not a retention benchmark. Both checks show that rigid $|S|$ is an upper bound, not an equilibrium free-energy difference. Panel (d) is a schematic of the bilinear $c\epsilon\delta$ term, not a DFT fit.

C. Mechanical strain sensitivity

Pristine tetramers yield $\alpha_{\text{pris}} = +1.2 \pm 0.1$ meV/% on the six-point reference grid. On the same cluster map,

TABLE IV. Periodic coupling-energy audit at +3% biaxial strain (PBE+D3 rigid protocol, reference placement; core $n \leq 4$ at 400 Ry). $\mathcal{S}$ in meV/atom from Eq. (2); conservative protocol uncertainty ± 2 meV/atom for $n \leq 4$ (Sec. IIC). Substitutional loading is one dopant per C_{60} unit (~ 1.67 at.% of total atoms in each supercell). Rows with $n \geq 6$ (350 Ry) are in Supplemental Material Table S1.

n	Dopant	ϵ (%)	at. %	$\mathcal{S}$ (meV/atom)
1	B	+3	1.67	-8.38
1	N	+3	1.67	+2.30
1	P	+3	1.67	-31.91
2	B	+3	1.67	-2.18
2	N	+3	1.67	+6.85
2	P	+3	1.67	-28.29
4	B	+3	1.67	-6.23
4	N	+3	1.67	+2.95
4	P	+3	1.67	-23.71

least-squares slopes versus the vacuum-box label are $+59 \pm 116$ (B), -297 ± 110 (N), and $+456 \pm 870$ meV/% (P) [Fig. 3(d)]. These numbers are cluster diagnostics, not monolayer strain coefficients. Only N is resolved beyond 2σ ; the B and P slopes are not statistically distinguishable from zero, so α is reported as an order-of-magnitude descriptor and the strain response of the substituted tetramers is manifestly not well described by a single linear coefficient. That poor conditioning is itself part of the argument: a descriptor this noisy cannot be the basis for the additive extrapolation that sequential screens perform. Table V reports $\bar{d}$, $\sigma(\bar{d})$, and Δr_{cov} . At +3%, P shows $\Delta \bar{d} \approx 3 \times 10^{-5}$ Å versus $\sim 8.5 \times 10^{-3}$ Å for B.

Figure 3 compares periodic Hirshfeld charges with the cluster-map geometry diagnostic. Hirshfeld $q(\epsilon)$ and $\bar{d}(\epsilon)$ [panels (a,b)] vary with dopant and strain. Local disorder $\sigma(\bar{d})(\epsilon)$ [panel (c)] broadens for B and N under tension while remaining near the $\epsilon=0$ baseline for P. Panel (d) maps reference-map $|\alpha|$ against periodic $|\mathcal{S}|_{n=4}$ (marker area $\propto |\mathcal{S}|_{n=1}$): N lies in the high- $|\alpha|$ /low- $|\mathcal{S}|_{n=4}$ quadrant and P in the high- $|\mathcal{S}|$ region—a qualitative rank inversion among three dopants, not a fitted correlation. P has the largest covalent-radius mismatch ($\Delta r_{\text{cov}} = +30$ pm; Table V) and the largest audited $|\mathcal{S}|$ under the rigid protocol.

IV. DISCUSSION

A. Main finding

Additive screening fails under constrained joint load because frozen elastic incompatibility generates a bilinear $c\epsilon x$ term [Eq. (1)] large enough to change rankings for P (Table IV), while linear α does not rank $|\mathcal{S}|$ [Fig. 3(d)]. The failure is selective rather than generic: on the audited grid only P clears both the ~ 2 meV/atom band and the $\eta > \sim 1\%$ criterion, B clears the first but not the

second, and N clears neither with margin (Sec. IIIB). That selectivity is the useful content—additive screening is safe for most substituents on this host and fails specifically where covalent-radius misfit is large. Ionic relaxation nearly extinguishes $|\mathcal{S}|$ (Table II; Fig. 2(b)), consistent with a dominant elastic-work contribution rather than a partitioned electronic claim (Sec. IVE). We treat $|\mathcal{S}| > \sim 2$ meV/atom or $\eta > \sim 1\%$ on this PBE+D3 map as a practical flag for coupled re-evaluation, not a thermodynamic boundary.

B. Mechanism

For size-mismatched P, the dominant chain is (Fig. 4): $\Delta r_{\text{cov}} = +30$ pm $\rightarrow$ frozen misfit stress $\rightarrow$ overlap with biaxial tension $\rightarrow$ bilinear elastic work $\rightarrow$ largest $|\mathcal{S}|$. Two features of the audited set are consistent with geometric misfit as the primary control (Table V; Fig. 4(b,d)). First, the *sign* tracks the sign of the mismatch: N is the only undersized substituent ($\Delta r_{\text{cov}} = -6$ pm) and the only one with $\mathcal{S} > 0$, while the oversized B and P (+7 and +30 pm) both give $\mathcal{S} < 0$. Second, the *rank* of the magnitude follows $|\Delta r_{\text{cov}}|$ at both audited sizes: $N < B < P$ for $|\Delta r_{\text{cov}}|$ ($6 < 7 < 30$ pm) and for $|\mathcal{S}|$ at $n=1$ ($2.3 < 8.4 < 31.9$ meV/atom) and $n=4$ ($3.0 < 6.2 < 23.7$ meV/atom). Radius nonetheless fails to fix the proportionality constant: $|\mathcal{S}|_{n=1}/|\Delta r_{\text{cov}}|$ is ~ 0.4 meV/atom per pm for N against ~ 1.1 – 1.2 for B and P, so a single geometric descriptor orders the three substituents without predicting their magnitudes. With three substitutional labels this is a consistency check on the misfit picture, not a fitted scaling law. Electronic redistribution is secondary and does not reproduce either pattern: the fractional Hirshfeld change $|\Delta q/q|$ over $0 \rightarrow +3\%$ is largest for N ($\sim 18\%$), intermediate for P ($\sim 10\%$), and smallest for B ($\sim 6\%$), which neither orders nor signs $\mathcal{S}$ [Fig. 4(a)]. π -DOS morphology is tertiary: the substituted cages are indistinguishable in $E_{\text{H-L}}$ at $\epsilon=0$ yet span an order of magnitude in $|\mathcal{S}|$ [Figs. 1(c) and 3(d)]. Uniform bond stretch is likewise not the controlling variable: B shows the largest $\Delta \bar{d}$ at +3% ($+8.5 \times 10^{-3}$ Å) yet an intermediate $|\mathcal{S}|$, whereas P barely stretches ($+3 \times 10^{-5}$ Å) and couples most strongly—consistent with stress that is stored rather than relieved by bond elongation. Ionic relaxation releases that stored misfit (Fig. 2(b)); Grimme D3 contributes only $\mathcal{S}_{\text{vdW}} \approx +0.33$ meV/atom at tetramer P (Table I).

C. Relation to literature

This is a periodic total-energy audit of joint (ϵ, δ) load (Table IV), not a strain-only, doping-only, or mobility/gap map [3, 4, 8, 10, 11]. Cluster expansions already encode $c\epsilon x$ [5, 6]; the increment is the matched four-corner audit on a soft, pre-strained network with rigid-vs.-relaxed and placement checks (Tables II–IV; Supple-

TABLE V. Local dopant–cage structure from archived *tetramer* XYZ ($\sim 5\%$ nominal doping; qualitative proxy for mismatch trends). Cartesian coordinates are *not* affinely scaled across labeled ϵ snapshots. Mean nearest-neighbor C distance $\bar{d}$ in Å; standard deviation $\sigma(\bar{d})$ across dopant sites; covalent-radius excess vs. C in pm. The tabulated $\Delta\bar{d} = \bar{d}(\epsilon = +3\%) - \bar{d}(\epsilon = 0)$ is a frozen-geometry cluster diagnostic, not a monolayer nearest-neighbor stretch. Distances are DFT-derived from archived tetramer XYZ; no experimental bond errors are quoted—comparison is internal across dopants and with qHP literature on intrinsic cage strain [9, 12].

Dopant	$\bar{d}(\epsilon=0)$ (Å)	$\bar{d}(\epsilon=+3\%)$ (Å)	$\Delta\bar{d}$ (Å)	$\sigma(\bar{d})$ @ +3% (Å)	Δr_{cov} (pm)
B	1.384	1.393	+0.0085	0.019	+7
N	1.393	1.402	+0.0087	0.024	−6
P	1.384	1.385	+0.00003	0.0004	+30

mental Material, Table I). Prior graphullerene studies often relaxed ions first or added separate grids [4, 8, 10], which masks constrained-load coupling.

D. Applicability and generality

The four-corner audit applies when local substitutional strain cannot fully relax on a short-range, elastically soft covalent network [9, 18]. It does not apply to fully relaxed bulk references, metallic or liquid hosts, or high- T regimes where configurational entropy dominates sub-meV differences (Sec. IV E). Uniaxial load should preserve the stencil but rescale c through elastic anisotropy; that case is not audited.

Laboratory tests need not resolve $\mathcal{S}$: cage-mode Raman/IR or substrate-bending that deviate from separate strain-plus-doping calibrations would signal additive failure, provided chemistry and strain are matched and the comparison is to a constrained, not fully relaxed, state.

E. Limitations

Main-text α and $\mathcal{S}$ use PBE+D3. Periodic production cells are affinely strained at fixed fractional coordinates; cluster tetramer grids change only the vacuum box and are not used as strain physics. Ionic relaxation of periodic $n=1$ P recovers additivity ($|\mathcal{S}_{\text{relaxed}}| < 10^{-3}$ meV/atom); Table II is an invalid cluster diagnostic. Eq. (1) and the four-corner link [Eq. (4)] assume small perturbations on a single smooth energy branch; they lose validity at large strain (e.g. $\gtrsim 10\%$) or across structural phase transitions, and the production audits intentionally remain at +3% biaxial load inside the nominally elastic regime. All totals are 0 K Born–Oppenheimer energies; finite-temperature free energies and configurational entropy remain unexplored and could reorder sub-meV competitors without restoring additivity if bilinear coupling persists at the electronic-structure level. Production periodic cells use Γ -only sampling; dense- k and SCAN/r²SCAN four-corner checks are not reported (Table I). The largest reported $|\mathcal{S}|$ is at $n=1$, the cell for which Γ -only sampling is least adequate, so that single value carries the weakest numerical support in the set even though the size-

independence of $\mathcal{S}$ does not rest on it. Two of the five supercell sizes ($n=2, 8$) have pristine references off the converged plateau by 4–5 meV/atom, so their $\mathcal{S}$ rows are reported but not used for size-trend claims; recomputing those four corners at EPS-SCF = 10^{-6} and matched cutoff is the cheapest remaining improvement to the audit. Alternate placements (Table III) bound configuration specificity; Table V geometry is a tetramer proxy (~ 5 at.%) without Mayer/Bader partitioning or matched periodic $n=4$ bond statistics. With only three substitutional labels, the α – $|\mathcal{S}|$ map [Fig. 3(d)] is a qualitative rank comparison among $n=3$ chemistries, not a fitted correlation law or predictive model for linear α . Direct elastic-vs.-electronic energetic decomposition (Mayer bond order, Bader strain partitioning, virial stress) and dispersion cross-term audits for B/N periodic cells remain open (Table I).

F. Constrained load and outlook

Rigid $|\mathcal{S}|$ bounds epitaxial clamp, adhesion, or ultra-fast load where ions cannot relax (Fig. 2(b)); fully relaxed screens are expected to recover near-additive totals and must not inherit the rigid magnitudes as free-energy differences. The tetramer P grid (Table II) is a different system and reverses sign rather than collapsing to zero. For a new host: fix or relax coordinates to the loading scenario, evaluate four-corner $\mathcal{S}$, and replace sequential screening if $|\mathcal{S}| > \sim 2$ meV/atom or $\eta > \sim 1\%$ (Fig. 2(c,d)). Larger-radius group-V substituents (As, Sb) are expected to couple more strongly than P under constrained load; that extrapolation is unverified. Follow-up: Mayer/Bader partitioning, $\mathcal{S}(\text{cutoff})$ and $\mathcal{S}(k)$, and periodic $n=4$ P relaxation.

V. CONCLUSIONS

Additive strain–dopant screening fails on qHP C₆₀ under constrained load, but selectively: stored elastic incompatibility generates a bilinear correction large enough to reorder rankings only for size-mismatched P ($|\mathcal{S}| = 31.9 \pm 2$ meV/atom at $n=1$; $\eta \approx 8\%$ at $n=4$), while B carries a resolved sub-percent cross term and N sits at the




FIG. 3. Charge vs. geometry diagnostics and a qualitative rank comparison ($n=3$ dopants). (a) Periodic Hirshfeld $q(\epsilon)$ for B/N/P on affinely strained $n=1$ cells (six-point paths; dotted guide at $+3\%$). This panel is a valid strain-path charge diagnostic. (b) Nearest-neighbor $\bar{d}$ vs. vacuum-box label from archived tetramer XYZ (not an affine monolayer strain path). (c) Local disorder $\sigma(\bar{d})$ on the same frozen cluster map. (d) Cluster-map $|\alpha|$ vs. periodic $|S|_{n=4}$ (marker area $\propto |S|_{n=1}$; horizontal bars: linear-fit standard errors on the six-point cluster map). The cluster $|\alpha|$ is a configuration diagnostic, not a monolayer strain coefficient. N inverts a naive $|\alpha| \rightarrow |S|$ expectation; with only three dopants this panel reports qualitative ranking, not Pearson, R^2 , or Spearman statistics.

reporting floor. $\mathcal{S}$ estimates that mixed derivative; it is not a new thermodynamic observable. Linear α does not rank $|\mathcal{S}|$ among B/N/P and is itself poorly conditioned on six-point tetramer grids (standard errors comparable to or exceeding the slopes), so it cannot license the additive extrapolation [Fig. 3(d)]. For P, geometric misfit is primary and ionic relaxation nearly extinguishes $|\mathcal{S}|$ (Fig. 2(b)). Coupled (ϵ, δ) evaluation is required once $|\Delta r_{\text{cov}}| \gtrsim 20$ pm, where η reaches 8–12% and $|\mathcal{S}|$ re-orders stability; for the smaller mismatches audited here it is optional, since B stays below $\eta \approx 1\%$ and N sits at the reporting floor. Other networks require their own four-corner audit before either conclusion is transferred.

ACKNOWLEDGMENTS

We acknowledge computational resources and support from Xiamen University.

DATA AVAILABILITY

The data that support the findings of this study are openly available at <https://github.com/chenxingqiang/graphullerene-strain-engineering>, including computational inputs and outputs, tabulated coupling-energy and polaron analyses, four-corner total-energy components underlying $\mathcal{S}$ (machine-readable




FIG. 4. Mechanism hierarchy for P-dominated coupling (primary: misfit strain $\rightarrow$ frozen internal stress; secondary: charge redistribution; tertiary: π -DOS morphology). (a) Response plane from 0 $\rightarrow$ +3% path endpoints; bubble area $\propto |S|_{n=4}$. Neither axis orders the coupling: B stretches most ($|\Delta \bar{d}| \approx 8.5$ mÅ) at intermediate $|S|$, N redistributes the most charge ($|\Delta q/q| \approx 18\%$) at the *smallest* $|S|$, and P couples most strongly while barely stretching. (b) $|\Delta r_{cov}|$ vs. $|S|_{n=4}$: the rank follows mismatch (N < B < P), but the three points are not proportional, so radius orders without predicting magnitude. Shading marks the $|\Delta r_{cov}| \gtrsim 20$ pm regime where coupling is largest, not a threshold below which additivity holds. (c) Linked normalized paths $q(\epsilon)/q(0)$ (solid) and $\bar{d}(\epsilon)/\bar{d}(0)$ (dashed). (d) Covalent mismatch (%) vs. $|S|_{n=1}$, same rank ordering with P at the largest mismatch. With three substituents these panels are consistency checks on the misfit picture, not fitted correlations.

synergy tables), and materials to reproduce all figures and tables in the main text. Ionic-relaxation, Hirshfeld, and size-scaling archives referenced in the main-text

tables are included in the public release. A tagged release matching the manuscript revision will be issued upon acceptance.

- [1] A. K. Katiyar and J. H. Ahn, Strain-engineered 2D materials: challenges, opportunities, and future perspectives, *Small Methods* **9**, 2401404 (2025).
- [2] R. Lv, J. Xi, M. Chen, and S. Yang, Covalent fullerene networks: preparation, properties and catalytic applications, *Rev. Mater. Res.* **2**, 100195 (2026).

- [3] F. Lee, M. Tripathi, R. S. Salas, S. P. Ogilvie, A. A. Graf, I. Jurewicz, and A. B. Dalton, Localised strain and doping of 2D materials, *Nanoscale* **15**, 7227 (2023).
- [4] R. Wang, H. Li, M. A. Shakeri, X. Cheng, Y. Hu, and L. Wang, Strain engineering of electronic structure and thermoelectric properties of quasi-hexagonal fullerene monolayer, *J. Appl. Phys.* **136**, 015101 (2024).

- [5] J. M. Sanchez, F. Ducastelle, and D. Gratias, Generalized cluster description of multicomponent systems, *Physica A* **128**, 334 (1984).
- [6] D. B. Laks, L. G. Ferreira, S. Froyen, and A. Zunger, Efficient cluster expansion for substitutional systems, *Phys. Rev. B* **46**, 12587 (1992).
- [7] L. Hou, X. Cui, B. Guan, S. Wang, R. Li, Y. Liu, D. Zhu, and J. Zheng, Synthesis of a monolayer fullerene network, *Nature* **606**, 507 (2022).
- [8] A. Capobianco, J. Wiktor, A. Landi, F. Ambrosio, and A. Peluso, Electron localization and mobility in monolayer fullerene networks, *Nano Lett.* **24**, 8335 (2024).
- [9] U. Argaman and G. Makov, Structure and properties of graphullerene: a semiconducting two-dimensional C₆₀ crystal, *npj Comput. Mater.* **9**, 211 (2023).
- [10] M. A. Khan, M. Atif, and M. N. Leuenberger, Tuning the electronic and optical properties of impurity-engineered two-dimensional graphullerene half-semiconductors, *Phys. Rev. Mater.* **9**, 034001 (2025).
- [11] B. Peng and M. Pizzochero, Monolayer C₆₀ networks: a first-principles perspective, *Chem. Commun.* **61**, 10287 (2025).
- [12] R. M. Tromer, L. A. Ribeiro, Jr., and D. S. Galvão, A DFT study of the electronic, optical, and mechanical properties of a recently synthesized monolayer fullerene network, *Chem. Phys. Lett.* **804**, 139925 (2022).
- [13] T. S. A. Cassiano, M. L. Pereira, Jr., G. M. e Silva, P. H. de Oliveira Neto, and L. A. Ribeiro, Jr., Large polarons in two-dimensional fullerene networks: the crucial role of anisotropy in charge transport, *Nanoscale* **16**, 2337 (2024).
- [14] P. Santra, S. Ghaderzadeh, M. Ghorbani-Asl, H.-P. Komsa, E. Besley, and A. V. Krashennnikov, Strain-modulated defect engineering of two-dimensional materials, *npj 2D Mater. Appl.* **8**, 33 (2024).
- [15] J. VandeVondele, M. Krack, F. Mohamed, M. Parrinello, T. Chassaing, and J. Hutter, Quickstep: Fast and accurate density functional calculations using a mixed Gaussian and plane waves approach, *Comput. Phys. Commun.* **167**, 103 (2005).
- [16] J. P. Perdew, K. Burke, and M. Ernzerhof, Generalized gradient approximation made simple, *Phys. Rev. Lett.* **77**, 3865 (1996).
- [17] S. Grimme, S. Ehrlich, and L. Goerigk, Effect of the damping function in dispersion corrected density functional theory, *J. Comput. Chem.* **32**, 1456 (2011).
- [18] M. Alihosseini and M. Neek-Amal, Strain tuning of optoelectronic properties of covalent organic framework bilayers and heterostructures, *Phys. Rev. B* **108**, 165403 (2023).