



ROCKWOOL Safe'n'Silent™ Pro

General Product Information

ROCKWOOL stone wool products are made of basalt, a volcanic stone.

ROCKWOOL stone wool products are non-combustible with a melting point of approximately 1000°C. They are particularly suitable for thermal insulation, fire protection and sound reduction/absorption.

ROCKWOOL stone wool is inorganic and contains no nutritious substance. Therefore it will not be attacked by microorganisms. Stone wool will not rot and does not attract vermin.

No CFCs, HFCs, HCFCs or asbestos are used in the manufacture of ROCKWOOL stone wool products.

Safe'n'Silent™ Pro

Recommended applications

ROCKWOOL Safe'n'Silent Pro is designed and manufactured to achieve excellent acoustic insulation performance in all types of drywall partition configurations. It is recommended to be used for drywall partition applications in hospitals, cinemas, schools, offices, residential and industrial buildings.

Safe'n'Silent Pro meets the requirements of Noise Criteria (NC) specifications developed by the ROCKWOOL company. NC comprehensively measures the noise levels of a room and with the use of NC ratings, recommends the desired acoustic comfort level of a room/space.

Facings

Optional facing with one or two sided glass tissue is available upon request for perforated wall panel.

For more information, please contact your local representatives.



Packaging and storage

ROCKWOOL Safe'n'Silent Pro is shrink-wrapped in polyethylene sheets for ease of handling, transportation, storage and identification.

Products should be stored indoors or under waterproof covering.

Technical Parameters

Product Name	Safe'n'Silent Pro330	Safe'n'Silent Pro350	Safe'n'Silent Pro370	Standards
Noise Absorption Co-efficient at 50mm (NRC)	0.90	1.00	1.00	EN ISO 354 / ASTM C 423-01
Fire Performance	Non-combustible / A1 Fire Classification	Non-combustible / A1 Fire Classification	Non-combustible / A1 Fire Classification	EN13501-1
Melting Point	More than 1000°C	More than 1000°C	More than 1000°C	ASTM E794
*Thermal Conductivity 20°C λ Value (W/mK)	0.036	0.035	0.034	ASTM C518
R-value at 50mm thickness (m ² K/W)	1.389	1.429	1.471	
Water Absorption (partial immersion)	1.0kg/m ²	0.5kg/m ²	0.5kg/m ²	EN1609.97
Water Vapor Absorption	Less than 0.04 Vol %	Less than 0.04 Vol %	Less than 0.04 Vol %	ASTM C1104/C1104M
Thickness	50, 64, 75, 90mm	50, 64, 75, 90mm	50, 64, 75, 90mm	EN 822
Applications	Recommended for commercial applications such as retail and office partition walls	Recommended for all drywall partition applications	Recommended for fire-rated partition system	

* Thermal conductivity values are based on testing conducted in external accredited laboratory in accordance to ASTM C518 : 1991. Test reports are available upon request. For design, it is recommended to use a safety factor of 20% as design value.



www.rockwoolasia.com

ROXUL-ROCKWOOL
Insulation India Pvt. Ltd.
Plot-Z/4, Dahej
SEZ, Dahej District
Bharuch-392 130
Gujarat-India
T (+91) 2641 619400
F (+91) 2641 256292

ROCKWOOL Malaysia
Sdn Bhd
Lot 4, Solok Waja 1
Bukit Raja Industrial Estate
41050 Klang, Selangor
Malaysia
T (+60) 3 3341 3444
F (+60) 3 3342 7290

ROCKWOOL Malaysia
Sdn Bhd
175 A&B
Kawasan Perindustrian
Air Keroh, Jalan Lingkungan
Usaha, 75450 Melaka
Malaysia
T (+60) 6 233 2010
F (+60) 6 233 2012

ROCKWOOL (Thailand) Limited
Hemaraj Eastern Industrial
Estate (Map Ta Phut)
1 Soi G 2, Pakornsongkrohraj
Road, Huaypong, Muang
Rayong 21150
Thailand
T (+66) 3868 5110
F (+66) 3868 4938

Disclaimer: The information contained in this data sheet is believed to be correct at the date of publication. ROCKWOOL does not accept responsibility for the consequences of using Safe'n'Silent™ Pro in applications different from those described above.

