

Data Description

Table of Content

- [Data Description](#)
 - [Table of Content](#)
 - [Overview](#)
 - [Parameter Naming Convention](#)
 - [Data Sources](#)
 - [Meta Data \(MET\)](#)
 - [Environmental Sensor \(ENV\)](#)
 - [Thermal / IR Camera \(IR\)](#)
 - [Image Processing System / Computer Vision \(CV\)](#)
 - [DataXplorer \(DXP\)](#)
 - [Temperature Control Units \(TCE/TCN\)](#)
 - [EUROMAP77 \(E77\)](#)
 - [Dosing \(DOS\) and Drying System \(DRY\)](#)
 - [Scale \(SCA\)](#)
 - [Manual Visual Defect Inspection \(LBL\)](#)
 - [Simulation data \(SIM\)](#)
 - [Machine settings \(SET\)](#)
 - [Extracted Features](#)
 - [Thermal / IR camera \(IR\)](#)
 - [Datasets](#)
 - [Structure](#)
 - [Data from December 7, 2021 \(Material: PP\)](#)
 - [Data from December 15, 2021 \(Material: ABS\)](#)
 - [Data from March 17, 2022 \(Material: PP\)](#)


Overview

The data was collected during the research project "ProBayes" conducted by SKZ (German Plastics Center) and Fraunhofer IPA in 2021/2022. An injection moulding machine (KraussMaffei 160-750PX) was equipped with peripheral devices and quality control devices, as you can see in the following figure. The part manufactured with the injection moulding machine is called 'warpage shell' (~ Verzugsschale). It is used because it allows to easily reproduce warpage and shows very well the effect of different temperatures on the geometry. It was produced with two different materials, polypropylene (Borealis HE125MO) and acrylonitrile butadiene styrene (INEOS Terluran® ECO GP-22 MR70), the latter containing 70% recyclate. The data from all different data sources were combined into one PARQUET file, where each row holds the data of one part / cycle. Each part can be identified using the unique MachineCycleID.

Hard facts:

- 564 injection moulded parts (47 experimental points with 12 parts each)
- two materials (PP and ABS)
- 9 datasources
- 334 features

The following figure shows all peripheral devices centered around the injection moulding machine:



Parameter Naming Convention

All parameters are described via a prefix and a parameter name. The prefix gives a hint at the data source as can be seen in the following table:

Data Source	Prefix	Explanation	Examples
EUROMAP77	E77	Cycle-based single values such as pressure or temperature values	E77_CusionVolume
DataXplorer	DXP	Time series data from the KraussMaffei injection molding machine, e.g. pressure curves	DXP_Inj1PrsAct
Temperature Control Unit Ejector Side	TCE	Time series data from the temperature control unit for the ejector side	TCE_TemperatureReturnLine
Temperature Control Unit Nozzle Side	TCN	Time series data from the temperature control unit for the nozzle side	TCN_TemperatureReturnLine
Drying system	DRY	A drying system is used to dry the material before the injection molding process	DRY_HT101_acTempReturnAir
Dosing system	DOS	The dosing system doses the plastic granules for the injection molding machine	DOS_acComp1DosRate
Image processing system / Computer Vision	CV	Computer Vision to detect geometrical dimensions of the plastic part	CV_Width1
Thermal / IR camera	IR	Infrared camera to detect the surface temperature of the plastic part after it is ejected	IR_Image1Name

Data Source	Prefix	Explanation	Examples
Meta data	MET	Meta information such as cycle id, experiment number, timestamp etc.	MET_JobCycleID
Scale	SCA	A Scale is used to weigh the manufactured plastic parts	SCA_PartWeight
Environmental sensor	ENV	Environmental sensor detects the air temperature and humidity	ENV_AirTemperature
Manual visual defect inspection	LBL	Surface defects of the plastic part are labels	LBL_SinkMarks

Data Sources

Meta Data (MET)

The meta data includes, for example, the injection molding cycle number or the name of the respective test series. All associated parameters are listed below.

Feature	Explanation	Unit	dtype
MET_JobCycleID	Consecutive job cycle number starting again at 1 for each test day	-	int
MET_MachineCycleID	Consecutive machine cycle number that is never reset	-	int
MET_ExperimentNumber	For all cycles with the same experiment number (e.g. A16) identical parameter settings were used	-	str
MET_Timestamp	Timestamp at which the respective injection molding cycle started	-	datetime
MET_MaterialName	Name of the plastic material used for the tests	-	str
MET_MaterialMoisture	Moisture content of the plastic material	%	float

Environmental Sensor (ENV)

The temperature and humidity sensor (type DHT22) was placed in proximity to the IR camera.

Feature	Explanation	Unit	dtype
ENV_AirTemperature	Temperature of the air in the production hall close to the injection molding machine	°C	float
ENV_AirHumidity	Relative humidity of the air in the production hall close to the injection molding machine	%	float

Thermal / IR Camera (IR)

A robot removes the finished parts from the mold and positions them in front of an infrared camera to take photos (thermographic images) of the entire part at 15 second intervals. Three images per part were taken during the December 2021 test days. During the tests in March 2022, only two images per part were taken because the cycle times were too short for further images.

Feature	Explanation	Unit	dtype
---------	-------------	------	-------

Feature	Explanation	Unit	dtype
IR_Image1Name	File name of the first thermographic image of a part	-	str
IR_Image2Name	File name of the second thermographic image of a part	-	str
IR_Image3Name	File name of the third thermographic image of a part	-	str


Image Processing System / Computer Vision (CV)

After the thermal camera has taken three photos the robot moves the part in front of a standard camera. This camera then takes close-up images of each of the three sections in the upper area of the injection molded part. Subsequently, computer vision is used to measure the distances between certain edges. The extracted features are listed below and can also be seen in the figure below.

Feature	Explanation	Unit	dtype
CV_Image1Name	File name of the image of the first (left) part area	-	str
CV_Image2Name	File name of the image of the first (mid) part area	-	str
CV_Image3Name	File name of the image of the first (right) part area	-	str
CV_Height1	Height of the first section	mm	float
CV_Width1	Width of the first section	mm	float
CV_Height2	Height of the second section	mm	float
CV_Width2	Width of the second section	mm	float
CV_Height2Small	Height of the quadratic recess in the second section	mm	float
CV_Width2Small	Width of the quadratic recess in the second section	mm	float
CV_Height3	Height of the third section	mm	float
CV_Width3	Width of the third section	mm	float
CV_Diameter3	Diameter of the dome in the third section	mm	float
CV_Warpage	Key indicator to describe the total warpage of the component	mm	float
CV_Width	Total width of the component measured in the lower area	mm	float

The parameter "CV_Warpage" is intended to describe the total warpage of the component and is calculated by the following equation:

$$CV_Warpage = |CV_Width1(target) - CV_Width1(actual)| + |CV_Width2(target) - CV_Width2(actual)| + |CV_Width3(target) - CV_Width3(actual)|.$$



DataXplorer (DXP)

The dataXplorer is a preconfigured data storage device for automatic recording of sensor and control data of an injection molding machine, in whose control cabinet the hardware and software are integrated. The naming of the parameters was done by the machine manufacturer KraussMaffei. A list to look up the parameter names (German and English) is appended to this data description.

Values are recorded for the parameters at a frequency of 0.005 seconds, i.e. the data are available here as time series. Since each row in the data set corresponds to one injection molding cycle, the time series associated with the various parameters were each packed into an array and stored in a cell. In addition to the classic parameters such as pressures or temperatures, there are also various triggers. These triggers are either true (= 1) or false (= 0). All the different triggers are listed below.

Feature	Explanation (English)	Explanation (German)
DXP_TrigClpCls	True while the clamping unit is closed	Wahr während Schließe öffnet
DXP_TrigClpOpn	True while the clamping unit is opened	Wahr während Schließe schließt
DXP_TrigInj1	True during the injection phase	Wahr während der Einspritzphase
DXP_TrigHld1	True during the holding pressure phase	Wahr während der Nachdruckphase
DXP_TrigPlst1	True during the plastification of the injection unit	Wahr während Einspritzeinheit plastifiziert
DXP_TrigInj1Dcmp1	True while decompression 1 of injection unit	Wahr während Dekompression 1 Einspritzeinheit
DXP_TrigInj1Dcmp2	True while decompression 2 of injection unit	Wahr während Dekompression 2 Einspritzeinheit

Feature	Explanation (English)	Explanation (German)
DXP_TrigCool	True during the cooling phase	Wahr während Kühlphase
DXP_TrigClpCfr	True while clamping force is released	Wahr während Schließe Schließkraftabbau
DXP_TrigClpCfb	True while clamping force is built up	Wahr während Schließe Schließkraftaufbau
DXP_TrigEje1Fwd	True while the ejector is moved forwards	Wahr während Auswerfer vorfahren
DXP_TrigEje1Rew	True while the ejector is moved rearwards	Wahr während Auswerfer zurückfahren
DXP_TrigInju1Fwd	True while the injection unit is moved forwards	Wahr während Einspritzeinheit vorfährt
DXP_TrigInju1Rew	True while the injection unit is moved rearwards	Wahr während Einspritzeinheit zurückfährt

Temperature Control Units (TCE/TCN)

Temperature control units are used to control the temperature of the injection mold. An injection mold consists of two halves, one on the ejector side, the other on the nozzle side. A separate temperature control unit is used for each mold half (TCE = Temperature control unit ejector side, TCN = Temperature control unit nozzle side). The data is acquired using EUROMAP 82.1, which is equivalent to OPC-UA Companion Specification 40082-1. Check out the documentation [here](#) for more details about the parameters. The data here are available as time series again. Therefore, the time series data have been packed into arrays cycle-wise.

EUROMAP77 (E77)

The EUROMAP77 is equivalent to the OPC-UA 40077 Companion Specification. Check out the documentation [here](#) for more details about the parameters. Also the EUROMAP77 is built on top of EUROMAP83, so some parameter descriptions can be found [here](#). Some example parameters are listed below. All parameters with prefix E77 are single values, i.e. there is exactly one value for each cycle.

Feature	Explanation	Unit	dtype
E77_CycleTime	Duration of the injection molding cycle	s	float
E77_InjectionTime	Duration of the injection phase	s	float
E77_CylinderTemperature01	Temperature of the cylinder at position 1	°C	float
E77_InjectionPressureMax	Maximum injection pressure	bar	float
E77_CavityPressureMax	Maximum cavity pressure	bar	float

Dosing (DOS) and Drying System (DRY)

The drying and dosing system from [Motan](#) consists of a dry air generator, two drying hoppers, a dosing device and a moisture measuring device. They communicate internally and share their data via a proprietary OPC-UA server, since there is no OPC-UA Companion Specification for this yet (EUROMAP86 is still under development). Dosing related parameters share the prefix DOS and drying related parameters the prefix DRY. Just like with the dataXplorer and temperature control unit data the dosing and drying data are available as time series data and stored in arrays.

Scale (SCA)

Before weighing, the sprue is manually clipped off the cooled plastic part using pliers. The part is then placed manually on a scale, the weight is read off and written in a table.


Feature	Unit	Explanation	dtype
SCA_PartWeight	g	Weight of the manufactured plastic part	float


Manual Visual Defect Inspection (LBL)

After weighing the parts, they were visually inspected to identify typical defect types. A list of the possible defects is given below.

Feature	Explanation
LBL_SinkMarks	("Einfallstellen") - Defect description
LBL_SprueCircle	("Kreis um Anguss")
LBL_Underfilled	("Unterfüllt") - Defect description
LBL_OldGranulate	("Altes Granulat") - Granulate from previous product
LBL_StreaksLevel1	("Schlieren Stufe 1")
LBL_StreaksLevel2	("Schlieren Stufe 2")
LBL_StreaksLevel3	("Schlieren Stufe 3")
LBL_NOK	("Teil ist n.i.O.") - Part is not OK

LBL_NOK is basically a summarization of the two most drastic defect types (LBL_Underfilled and LBL_SinkMarks). As soon as at least one of them is present (= 1), LBL_NOK is "1" as well which means that the part is not OK (= NOK). If none of these two defects is present its value is 0 meaning it is OK. Some of the component defects can be seen in the following pictures.

LBL_SprueCircle	LBL_StreaksLevel3
	
LBL_SinkMarks	LBL_Underfilled



LBL_OldGranulate



Simulation data (SIM)

To generate additional data from simulation, Moldex3D 2021 (a plastic injection molding simulation software) was used. The same test series were carried out in the simulation environment as on the real injection molding machine. The simulated data contains the part weight, geometrical dimensions of the part (corresponding to the real parameters with prefix "CV"), temperatures of the demolded part (corresponding to the real parameters with prefix "IR") and some process parameters. It should be noted that the simulated dimensions correspond to those of the part cooled down to room temperature, while the real measured dimensions ("CV") are determined shortly after demolding on the still warm part. This influence must be taken into account, since even more warpage and shrinkage can take place until the part has cooled down to room temperature. Some of the simulated parameters are listed below. Please note that certain simulation data are missing for some test series.

Feature	Explanation	Unit	dtype
---------	-------------	------	-------

Feature	Explanation	Unit	dtype
SIM_PartWeight	Weight of the injection molded part without sprue (corresponds to SCA_PartWeight)	g	float
SIM_TotalWeight	Weight of the part including the sprue residue (no equivalent in real data)	g	float
SIM_InjectionPressureMax	Max. injection pressure (corresponds to E77_InjectionPressureMax)	bar	float
SIM_InjectionPressureArea	Integral of the injection pressure curve (no equivalent in real data)	bar	float
SIM_FlowRateMax	Max. flow rate (no equivalent real data)	cm ³	float
SIM_FlowRateArea	Integral of flow rate curve (no equivalent in real data)	cm ³	float
SIM_Height1	Height of the first section (corresponds to CV_Height1)	mm	float
SIM_Width1	Width of the first section (corresponds to CV_Width1)	mm	float
SIM_TempSprue	Average temperature of the area around the sprue	°C	float
SIM_TempDome	Average temperature of the area around the dome	mm	float

Machine settings (SET)


Some of the machine settings changed in the tests (see tables [here](#)) are included in the data set as parameters with the prefix "SET_" (see the following table).

Feature	Explanation	Unit	dtype
SET_CylinderTemperature	Temperature of a specific cylinder zone (the temperatures of the other zones were changed in the same ratio)	°C	float
SET_ToolTemperature	Temperature of the tool/mold	°C	float
SET_HoldingPressure1	Holding pressure in first phase	bar	float
SET_HoldingPressure2	Holding pressure in second phase	bar	float

Extracted Features

Thermal / IR camera (IR)

The thermal camera images were analyzed to identify areas where temperatures varied widely between different test series and components. As a result, the mean temperatures of four areas are extracted: sprue, dome, horizontal edge and vertical edge (see figure below). In addition, the average temperature of the complete component is extracted, excluding the area around the cutout.



The following table lists some of the extracted features including a short description. Each of these features is extracted for all three images of each component, identifiable by "Img1", "Img2" and "Img3" respectively.

Feature	Explanation	Unit	dtype
IR_Img1TempSprue	Average temperature of the area around the sprue in the first image	°C	float
IR_Img2TempSprue	Average temperature of the area around the sprue in the second image	°C	float
IR_Img3TempSprue	Average temperature of the area around the sprue in the third image	°C	float
IR_Img1TempDome	Average temperature of the area around the dome in the first image	°C	float
IR_Img1TempEdgeHor	Average temperature of the area around the horizontal edge in the first image	°C	float
IR_Img1TempEdgeVer	Average temperature of the area around the vertical edge in the first image	°C	float
IR_Img1TempFull	Average temperature of the complete component in the first image	°C	float
IR_Img1TempGradHorStd	Standard deviation of the gradient of the temperature profile in the first image	°C	float
IR_Img1TempGradHorRng	Range from min to max value of the gradient of the temperature profile in the first image	°C	float
IR_Img1TempHorStd	Standard deviation of the temperature profile in the first image	°C	float

Feature	Explanation	Unit	dtype
IR_Img1TempHorRng	Range from min to max value of the temperature profile in the first image	°C	float

In addition, a reference image was subtracted from all images taken during the experiments on 07.12.2021 (material used: PP). This reference image is an averaged image from the first images of each component of the test series "Z01" (central point). From the generated difference images, the same features as in the original images were then extracted again, indicated by the suffix "Diff" (see table below for some examples).

Feature	Explanation	Unit	dtype
IR_Img1TempSprueDiff	Average temperature of the area around the sprue in the first difference image	°C	float
IR_Img2TempSprueDiff	Average temperature of the area around the sprue in the second difference image	°C	float
IR_Img3TempSprueDiff	Average temperature of the area around the sprue in the third difference image	°C	float

Datasets

Structure

Each row in the dataset represents one injection molding cycle and thus one produced part. The columns contain the various features mentioned above. In the case of numerical parameters, these are either stored as single values (i.e. a single number in a cell) or, in the case of time series, as an array in a cell. This means that the arrays each contain all the values of the time series associated with a particular cycle.

On the two test days in December 2021 a total of 408 injection molding cycles were carried out, half of which were from December 7, 2021, where polypropylene (PP) was used as plastic, and the other half from December 15, 2021, where acrylonitrile butadiene styrene (ABS) was used. Per test day, 17 test series (A01-A16 and Z01) with different machine settings were carried out. Within each test series, 12 parts were produced, resulting in a total of 204 cycles per test day. Test series Z01 represents the central point, i.e. optimum settings were used here to produce the part. The settings in the remaining rows were intentionally adjusted so that parts with poor quality could also be produced.

Further trials with PP were conducted in March 2022. This time, the basis for the experiments was a Taguchi plan. Furthermore, additional and other parameters were varied.

Data from December 7, 2021 (Material: PP)

The following table shows the machine and process settings used for the various test series on December 7, 2020. The plastic material used was Borealis HE125MO (PP).

Experiment Number	Cylinder Temperature [°C]	Tool Temperature [°C]	Injection Speed [ccm/s]	Holding Pressure 2 (for 18 s) [bar]	Holding Pressure 1 (for 7 s) [bar]	Cooling Time [s]	Transfer Volume [ccm]
A01	250	50	100	30	200	22.5	26.4
A02	250	50	100	30	60	22.5	26.8
A03	250	50	15	30	200	15.5	21.3

Experiment Number	Cylinder Temperature [°C]	Tool Temperature [°C]	Injection Speed [ccm/s]	Holding Pressure 2 (for 18 s) [bar]	Holding Pressure 1 (for 7 s) [bar]	Cooling Time [s]	Transfer Volume [ccm]
A04	250	50	15	30	60	15.5	21.3
A05	250	20	100	30	200	22.5	25.7
A06	250	20	100	30	60	22.5	25.7
A07	250	20	15	30	200	15.0	19.6
A08	250	20	15	30	60	15.0	19.6
A09	200	50	100	30	200	22.5	26.4
A10	200	50	100	30	60	22.5	26.4
A11	200	50	15	30	200	15.3	21.3
A12	200	50	15	30	60	15.3	21.3
A13	200	20	100	30	200	22.5	25.8
A14	200	20	100	30	60	22.5	25.8
A15	200	20	15	30	200	15.5	20.0
A16	200	20	15	30	60	15.5	20.0
Z01	225	35	58	30	130	21.5	24.9

Data from December 15, 2021 (Material: ABS)

Listed below are the machine and process settings used on the second test day on December 15, 2021. The plastic material used was INEOS Terluran ECO GP-22 MR70 (ABS), a mechanical post consumer recycling (PCR) grade, with a PCR content of 70%. Unlike the previous experiments with PP, no two-stage holding pressure was used.

Experiment Number	Cylinder Temperature [°C]	Tool Temperature [°C]	Injection Speed [ccm/s]	Holding Pressure (for 25 s) [bar]	Cooling Time [s]	Transfer Volume [ccm]
A01	260	80	80	350	23	25.50
A02	260	80	80	200	23	25.50
A03	260	80	20	350	18	22.75
A04	260	80	20	200	18	22.75
A05	260	30	80	350	23	25.00
A06	260	30	80	200	23	25.00
A07	260	30	20	350	18	20.50
A08	260	30	20	200	18	20.50
A09	220	80	80	350	23	24.50
A10	220	80	80	200	23	24.50

Experiment Number	Cylinder Temperature [°C]	Tool Temperature [°C]	Injection Speed [ccm/s]	Holding Pressure (for 25 s) [bar]	Cooling Time [s]	Transfer Volume [ccm]
A11	220	80	20	350	18	21.50
A12	220	80	20	200	18	21.50
A13	220	30	80	350	23	24.00
A14	220	30	80	200	23	24.00
A15	220	30	20	350	18	20.25
A16	220	30	20	200	18	20.25
Z01	240	55	50	275	22	24.00

Data from March 17, 2022 (Material: PP)

The basis for the March 2022 experiments was a Taguchi plan, shown in the following table. In these experiments, in contrast to the previous ones, both the holding pressure time and the dynamic pressure were varied. The A32 series corresponds to the A01 series of December 7, 2021. That's why two values are entered for the holding pressure and holding time. The plastic material used was Borealis HE125MO (PP).

Experiment Number	Cylinder Temperature [°C]	Tool Temperature [°C]	Injection Speed [ccm/s]	Holding Pressure [bar]	Holding Time [s]	Cooling Time [s]	Back Pressure [bar]	Transfer Volume [ccm]
A20	220	20	40	100	15	14	80	26.13
A21	220	20	40	100	15	14	80	24.00
A22	220	40	58	200	20	20	80	25.30
A23	220	60	104.5	300	25	26	80	26.50
A24	240	20	58	300	17.5	23	80	25.20
A25	240	40	104.5	150	22.5	14	80	26.10
A26	240	60	47.5	250	15	20	80	25.45
A27	260	20	104.5	250	20	17	80	25.40
A28	260	40	47.5	100	25	23	80	24.60
A29	260	60	74.5	200	17.5	14	80	25.70
A30	240	20	58	300	17.5	23	115	26.30
A31	240	20	58	300	17.5	23	150	27.70
A32	250	50	100	30 / 200	18 / 7	22.5	80	26.40