

SAMPLE DOCUMENT FOR A PRODUCT DEMO. NOT A REAL CERTIFICATE.

Shree Balaji Corrugators: in-house laboratory

Box compression and bursting strength test report

Test date: 12 Jun 2026

Samples: 5-ply BC, 180/120/120/120/150 GSM

Bursting strength: 14.2 kg/cm² (spec 12.0 min)

Box compression test: 412 kgf (spec 380 min)

Moisture: 7.8%

Fictional demo document. All companies, people, certificate numbers and prices are invented.