




6/19/25











① 대시라 2g 5g + 물 50g

② 미역 분말 5g + 물 50g

가죽 25g + 물 250g

가죽 25g + 물 250g

Mixed soap 6개

10mL

① 대시라

10mL

② 대시라 + 1g 젤라틴

10mL

③ 대시라 + 1g 감귤향분

10mL

④ 비액

10mL

⑤ 비액 + 1g 젤라틴

10mL

⑥ 비액 + 1g 감귤향분

*

대시라 액: Liquid phase

대시라 + 젤라틴: 시판의 젤라틴은 물에 용해될 때 상당히 많은 열을 발생시키므로, 시판의 젤라틴을 사용하기 전에 미리 물에 용해시켜야 합니다.

대시라 + 감귤향분: ~~대시라 + 감귤향분은 물에 용해될 때 상당히 많은 열을 발생시키므로, 시판의 감귤향분을 사용하기 전에 미리 물에 용해시켜야 합니다.~~

*

비액 액: Liquid phase

비액 + 젤라틴: 대시라 + 젤라틴과 마찬가지로 시판의 젤라틴은 물에 용해될 때 상당히 많은 열을 발생시키므로, 시판의 젤라틴을 사용하기 전에 미리 물에 용해시켜야 합니다.

비액 + 감귤향분: 대시라 액에 대시라 액을 혼합한 후, 감귤향분을 첨가하여 혼합합니다.

대시라 1. 젤라틴

젤라틴 10g

감귤향분 10g

1. 비액 100g

100g

2. 대시라 10g

10g

3. ~~비액~~ 대시라 10g

10g

4. 비액

75g

5. 대시라 젤라틴

10g

6. 비액 젤라틴

20g

6/24/25








- ① 미역 50mL
- ② 미역 50mL 10g 적당량
- ③ 미역 50mL 20g 적당량
- ④ 미역 50mL 10g 갈라
- ⑤ 미역 50mL 20g 갈라


et al 1971


6/26/25













6.26.25 48 hr.

- ① 10g 50mL Thick liquid consistency, not hardened
- ② 10g 50mL 10g 2 1/2 Liquid like, not hardened.
- ③ 10g 50mL 20g 2 1/2 Slight goo on top, but about to harden on bottom. Liquid-like, but slight solidifying on bottom.
- ④ " 10g 2 1/2 has quite small cracks, soft in feel
- ⑤ " 20g 2 1/2 Patch in texture, has several cracks throughout the surface, looks dry/ashy, soft ~~to~~ inside, firm underneath.
- ⑥ 20g 50mL Thicker than 10g 50mL, thick liquid
- ⑦ " 10g 2 1/2 Not hardened, liquid-like, bubbles present.
- ⑧ " 20g 2 1/2 Not ~~hardened~~ hardened, ~~solid~~ liquid-like, bubbles present.
- ⑨ " 10g 2 1/2 no cracks on surface, very smooth but very soft.
- ⑩ " 20g 2 1/2 small cracks present on surface, firmest of all 2 1/2s, but still soft in feel.


*Overall, the potato starch samples hardened faster than the gelatin samples

*Seaweed had more cracks and was drier than Kelp

8/6/25











Most success: Kelp + 20g Gelatin (2 day heating, 3 week air dry)



*Very firm, glass-like texture
Matte-like bottom

Top



Bottom



Side



Original mixture → too solid

After experimentation → heat Gel w/ 100mL
water + 5g Kelp



8/14/25








New Batch: 08/06 recipe w/
2% Glycerol



9/25/25



Cup




20g Gelatin,
**50mL water,
5g Kelp
no glycerol for
purposes of
cup



New cup
approach
after
failures
with
previous
mold



Mold



Top



Bottom

