

durabond®

Time Proven Quality Product

Technical
Specification
Data Sheet

****Original hard copy is available upon request.**

Issue 2 - 10
30.3.2010

Durabond HM 8811C

Base	Ethylene Vinyl Acetate Copolymer
Form	Pastilles
Colour	White
Viscosity	1,400 - 1,800 cps @ 170°C (Brookfield Thermosel 31/12)
Softening point	73 ± 2°C (Ring & Ball method)
Hot tack	Good
Operating temperature	165 - 175°C
Fill up	Maintain pre-melting tank at ¾ full. Avoid sudden addition of excessive solid hot melt as this will lower the tank temperature significantly.
Toxicity	This product does not contain any toxic materials.
Safety precaution	To minimise the risk of burns, use eye protection and protective clothing when working near a hot melt applicator.
Storage life	2 years in cool dry place.
Storage condition	When not in use, store hot melt in air tight container to prevent contamination such as dust, oil, etc. That could lead to blocking of nozzles and deterioration effects.
End use	Side glue.
Note	Do not mix with other adhesives.

We guarantee the consistent quality of this product which has been manufactured in accordance with ISO 9001, 14001 and OHSAS 18001 guidelines. The product has been found suitable for the applications and uses listed above. For other uses and application methods we strongly suggest to contact our technical support staff.

The information contained herein is true and accurate to the best of our knowledge. Revertex Finewaters Sdn. Bhd. make no warranty or guarantee of results and assumes no obligations or liabilities from the use of any products or processes mentioned herein. This publication is not to be taken as a licence to operate under or recommendation to infringe upon, any patents.



REVERTEX FINEWATERS SDN. BHD. (Company No. 265645-P)

P.O.Box 152, 41710 Klang, Selangor Darul Ehsan, Malaysia

Tel: 603-33428625 (Hunting Line) Fax: 603-33420658

Email: rfw@rfw.com.my

<http://www.revertexfinewaters.com>

