

Pavement Quality Indicator Data





1-800-724-6306

Diamond Materials LLC 924 South Heald Street Wilmington, DE 19801

PQI	Core	Delta PQI	Absolute Delta
148.6	150.1	-1.5	1.5
144.7	146.4	-1.7	1.7
152.8	153.5	-0.7	0.7
153.7	152.5	1.2	1.2
147.8	147.8	0.0	0.0
153.6	151.6	2.0	2.0
151.6	149.2	2.4	2.4
151.7	151.1	0.6	0.6
152.4	151.5	0.9	0.9
151.9	151.2	0.7	0.7
Correlation	0.90		
Average Delta	1.2		

