

Core Correlation

1. Once the peaked location on the mat cools, cut a core from the mat and determine the in place density at the lab.
2. Compare the core result to the PQI 380go measurement at that location and calculate the difference.
3. If there is a difference, follow the steps above to adjust the correlation offset one last time.

Now that the PQI 380go has been correlated to the core you should not need to change the offset for the rest of the job.

Other Helpful Hints


- Charge the PQI 380go after each use.
- Clean the sensor on the PQI 380go with WD-40 or citrus cleaner.
- Have a towel with the PQI 380go at all times to keep the sensor dry.



900 Albany Shaker Rd. Suite 2
Latham, NY 12110
+1-518-370-5558 - 1-800-724-6306
transtechsys.com



Rev-



PQI 380^{go}
Pavement Quality Indicator

**Non-Nuclear Asphalt
Density Gauge
Correlation Cheat Sheet**

Correlating the PQI 380go to the Mix

Correlate the PQI 380go during the first hours of paving to the screed and then peak out the mat with a roller.

Example:

Based on the MTD for the mix, estimate what the screed is providing as a percentage of compaction.
A good rule of thumb is 88%.

Use This Calculation:

$$\text{MTD} \times .88 = \text{Screed Density}$$

Therefore:

$$158.6 \times 0.88 = \mathbf{139.6 \text{ lbs/ft}^3}$$

If you are working in international units
 $2540 \times 0.88 = \mathbf{2236 \text{ kg/m}^3}$

Use the PQI 380go to measure five locations behind the screed before the break down roller, then write down the density value shown on the PQI 380go screen for each location.

Let's Say:

124.0, 124.1, 124.5, 124.0, 124.2 lbs/ft³ or
1987, 1988, 1995, 1987, 1990 kg/m³

Compute the average of the five readings behind the screed.

So That:

$$\text{Average} = \mathbf{124.1 \text{ lbs/ft}^3} \text{ or } \mathbf{1989 \text{ kg/m}^3}$$

Compute the difference between the estimated screed density and average PQI 380go reading behind the screed.

Finally:

$$139.6 - 124.1 = \mathbf{15.5 \text{ lbs/ft}^3} \text{ or}$$

$$2236 - 1989 = \mathbf{247 \text{ kg/m}^3}$$

15.5 lbs/ft³ is the correlation offset you need to enter into the PQI 380go to read **139.6 lbs/ft³**, or 88% behind the screed. If you are working in international units, your offset is 247 kg/m³ that makes the PQI 380go read 2236 kg/m³ or 88%.

Enter the correlation offset into the PQI 380go (Refer to the PQI 380go Quick Start Guide)

Now take the "Screed Correlated PQI" and work with a roller to "Peak the mat".

Peaking the Mat

1. Pick a location and measure the density with the PQI 380go.
2. Use the roller and roll that part of the mat.
3. Measure again with the PQI 380go and note the increase in density.
4. Continue this process until the density on the PQI 380go does not increase.
5. This peak or maximum value is the density you need to achieve on your finished mat.