# arXiv Report: Tailoring Corner States and Exceptional Points in Altermagnets

arXiv:2603.19378

Auto-generated report for arXiv reading group

March 23, 2026

**Paper:** X.-M. Zhao, C.-X. Guo, X.-R. Ma, X.-R. Wang, S.-P. Kou, "Tailoring Corner States and Exceptional Points in Altermagnets," arXiv:2603.19378 (2026).

## 1 Core Question

How does non-Hermitian (NH) physics—specifically symmetry-compliant dissipation—interact with the unique momentum-dependent spin splitting of *altermagnets* (AMs) to produce topological phase transitions, exceptional points (EPs), and hybrid skin-topological corner modes that are *absent* in conventional antiferromagnets?

## 2 Key Definitions and Setup

**Altermagnets (AMs).** A recently identified class of collinear magnets with *zero* net magnetization (like antiferromagnets) but possessing strong **momentum-dependent spin splitting** enforced by crystal symmetry. The splitting has $d_{x^2-y^2}$ symmetry and arises from anisotropic hopping, *not* spin–orbit coupling (SOC). Think of it as an antiferromagnet whose band structure "knows" about the sublattice, so spin-up and spin-down bands split except along high-symmetry diagonals $k_x = \pm k_y$.

**Non-Hermitian systems.** A Hamiltonian $H \neq H^\dagger$. Physically this models open systems with gain/loss (here: dissipation from coupling to an environment). Key consequences:

- Complex eigenvalues.
- Left and right eigenstates are distinct: $H\,|u_R\rangle = E\,|u_R\rangle$, $H^\dagger\,|u_L\rangle = E^*\,|u_L\rangle$.
- **Exceptional points (EPs):** parameter values where two eigenvalues *and* eigenvectors coalesce (the Hamiltonian becomes defective).
- **NH skin effect:** eigenstates pile up at boundaries.

**Model.** A 2D $d_{xy}$-type altermagnet on a Lieb-type lattice with sublattices $A$, $B$ (magnetic, opposite Néel vectors) and a nonmagnetic ligand site. After projecting out the ligand, the $4\times 4$ Bloch Hamiltonian is

$$H(\mathbf{k}) = \big(h_0\,\tau_0 + h_1\,\tau_x + h_3\,\tau_z\big)\sigma_0 \;+\; h_2\,\tau_y\sigma_z \;+\; (J + i\gamma)\,\tau_z\sigma_z, \tag{1}$$

where $\tau_{0,x,y,z}$ and $\sigma_{0,x,y,z}$ are Pauli matrices in sublattice and spin space respectively, and:

$$\begin{aligned} h_0(\mathbf{k}) &= -t_a(\cos k_x + \cos k_y), \\ h_1(\mathbf{k}) &= -4t_0 \cos\tfrac{k_x}{2}\cos\tfrac{k_y}{2}, \quad h_2(\mathbf{k}) = 4\lambda \sin\tfrac{k_x}{2}\sin\tfrac{k_y}{2}, \\ h_3(\mathbf{k}) &= -t_b(\cos k_x - \cos k_y). \end{aligned} \tag{2}$$

Here $t_0 = 1$ is the nearest-neighbor hopping, $t_a, t_b$ encode the anisotropic next-nearest-neighbor hoppings ($t_1 = (t_a + t_b)/2$, $t_2 = (t_a - t_b)/2$), $\lambda$ is SOC strength, $J$ is the *sd*-exchange coupling, and $\gamma > 0$ parameterizes dissipation.

The crucial NH term is $\boxed{H_{\mathrm{AM}} = (J + i\gamma)\,\tau_z\sigma_z}$. The imaginary part $i\gamma$ is *locked* to the staggered magnetization operator $\tau_z\sigma_z$; it arises microscopically from a spin-dependent self-energy $\Sigma_\mu \approx -i\gamma(\mathbf{S}_\mu \cdot \boldsymbol{\sigma})$ obtained by integrating out the bath.

**Mirror decoupling.** The system preserves $M_z$ ($z \to -z$), so $H$ block-diagonalises into spin-↑ and spin-↓ sectors. The spectrum is

$$E_\pm = h_0 \pm \sqrt{h_1^2 + h_2^2 + \left[h_3 + \epsilon(J + i\gamma)\right]^2}, \qquad \epsilon = \pm 1 \text{ for spin } \uparrow / \downarrow . \tag{3}$$

# 3 Concrete Example: Why Altermagnets Differ from Antiferromagnets

Set $t_b = 0$ (the **antiferromagnet limit**). Then $h_3(\mathbf{k}) \equiv 0$, and the mass term inside the square root becomes the constant $\epsilon(J+i\gamma)$—there is no $\mathbf{k}$-dependent competition, so *no band inversion is possible*, and the system is topologically trivial for all $\gamma$.

Now turn on $t_b \neq 0$ (altermagnet). The dispersive term $h_3(\mathbf{k}) = -t_b(\cos k_x - \cos k_y)$ varies over the Brillouin zone and can change sign. At certain momenta $h_3 + \epsilon J = 0$, so the real part of the mass vanishes while the imaginary part $i\gamma$ survives, enabling:

1. Band inversion ⇒ **NH topological phase** (non-zero Chern number).
2. Coalescence condition $h_3 + \epsilon J = 0$, $h_1^2 + h_2^2 = \gamma^2$ ⇒ **exceptional points**.

This cleanly shows that the AM anisotropy is the *prerequisite* for all non-trivial NH topology.

# 4 Main Results

- **NH topological phase transition.** The $(J, \gamma)$ parameter space splits into gapped topological (Chern insulator), gapped trivial, and gapless (EP-hosting) phases. The entire structure collapses to trivial in the AFM limit $t_b = 0$.

- **Biorthogonal Chern number.** Topology is diagnosed via the spin-resolved Chern number computed in the biorthogonal basis:

$$C_\sigma = \frac{i}{2\pi} \int_{\mathrm{BZ}} \epsilon_{ij} \, \langle \partial_{k_i} u_L^\sigma | \partial_{k_j} u_R^\sigma \rangle \, d^2k.$$

- **Exceptional point dynamics.** In the gapless phase, each spin sector hosts up to 8 EPs. Increasing $\gamma$ drives pairwise creation and annihilation of EPs. The spin-↑ and spin-↓ EP patterns are related by a $\pi/2$ rotation, reflecting the $C_{4z}$ symmetry of the altermagnet.

- **Hybrid skin-topological corner modes.** In the topological phase under full open boundary conditions (OBC), chiral edge states *do not* spread uniformly along edges. Instead, they accumulate at specific **corners** due to the NH skin effect. The number of corner modes scales as $O(L)$ (system size), intermediate between $O(1)$ second-order topological modes and $O(L^2)$ bulk skin modes.

- **Deterministic corner control via sublattice termination.** The corners at which modes localise are *analytically* determined by which sublattice ($A$ or $B$) terminates each edge. For example, "BBBB" termination traps states at bottom-right/top-left corners, while "ABAB" shifts them. This is proved via the transfer matrix method.

- **Analytical edge dispersion.** The complex edge spectrum is

$$E_{\text{edge}}(k_i) = \alpha(k_i) + i\gamma\,\beta(k_i),$$

where $\alpha$ is the Hermitian edge dispersion and $\gamma\beta$ acts as an effective NH potential controlling localisation via the *chiral skin effect* (CSE) criterion.

# 5 Proof Sketch

1. **Microscopic derivation of the NH term.** Start with itinerant electrons coupled to local Néel order $\mathbf{S}_\mu$ ($\mu \in \{A, B\}$) via *sd*-hybridisation, plus a dissipative bath. Integrate out bath $\Rightarrow$ spin-dependent self-energy $\Sigma_\mu = -i\gamma(\mathbf{S}_\mu \cdot \boldsymbol{\sigma})$. Because $\mathbf{S}_A = -\mathbf{S}_B$ (Néel order), the imaginary part is *staggered*: $+i\gamma$ on sublattice $A$, $-i\gamma$ on $B$, producing the $i\gamma\,\tau_z\sigma_z$ term.

2. **Effective Hamiltonian via ligand projection.** Project out the nonmagnetic ligand sites on the Lieb lattice using a Schrieffer–Wolff-type downfolding. This yields the $4 \times 4$ Bloch Hamiltonian (1) with the functions (2).

3. **Block diagonalisation.** Exploit $M_z$ symmetry to decouple into two $2 \times 2$ blocks (spin-↑, spin-↓), giving the spectrum (3).

4. **Topological classification.** Each $2 \times 2$ block is a NH Chern insulator. Compute the biorthogonal Berry curvature and integrate over the BZ. Band inversion occurs when $h_3(\mathbf{k}) + \epsilon J$ changes sign across the BZ, which requires $t_b \neq 0$.

5. **EP conditions.** The square root in (3) vanishes (EP) iff both real and imaginary parts vanish simultaneously:

$$h_3 + \epsilon J = 0 \quad \text{and} \quad h_1^2 + h_2^2 = \gamma^2.$$

The first fixes a curve in $\mathbf{k}$-space; the second selects discrete points on that curve. $C_{4z}$ symmetry then constrains the EP pattern.

6. **Transfer matrix for edge states.** Write the tight-binding equations row-by-row in the OBC direction as a transfer matrix $T(k_\parallel)$. Solve for decaying solutions $\Rightarrow$ edge dispersion $E_{\text{edge}}(k_\parallel) = \alpha + i\gamma\beta$.

7. **Chiral skin effect criterion.** Define a global dissipation potential $\Gamma_g(r)$ along each edge from the imaginary part of $E_{\text{edge}}$. Corner localisation at position $r_0$ occurs iff $\Gamma_g(r_0 - 0^+) > 0$ and $\Gamma_g(r_0 + 0^+) < 0$ (a "trap" or domain wall in the potential). The sign of $\Gamma_g$ depends on the sublattice termination, establishing the deterministic corner control.

8. **Verification.** Full numerical diagonalisation on finite $80 \times 80$ lattices with various edge terminations (BBBB, BABA, ABAB, AABB) confirms the analytical predictions: corner modes shift according to the sublattice boundary, and vanish in the AFM limit.

# References

X.-M. Zhao, C.-X. Guo, X.-R. Ma, X.-R. Wang, S.-P. Kou, *Tailoring Corner States and Exceptional Points in Altermagnets*, arXiv:2603.19378 (2026).
`https://arxiv.org/abs/2603.19378`