

# Test Report

Report No.:SIT251009560201CR

Date:October 16, 2025


Page 1 of 9

Applicant: Hangzhou Huikai Packaging Products Co., Ltd.  
Address: Room 506, Tongfang International Building, No. 257, North Qiutao Road,  
Shangcheng District, Hangzhou City, Zhejiang Province

The following sample(s) and information were submitted and identified by the applicant

Sample Name: PS Plastic Box  
Trade Mark:   
Report Number: SIT251009560201CR  
Model No.: HK-034  
Sub-Model No.: HK-21157, HK-28188, SSM-045, SSM-002, SSM-004, SSM-014, SSM-040, XYB1840, SSM-018, SSM-205, SSM-024, SSM-052  
Manufacturer: Zhejiang Jinkuang Packaging Products Co., Ltd.  
Manufacturer Address: No. 1, Yulong Road, Qujiang District, Quzhou City, Zhejiang Province  
Origin of the Product(s): China  
Main Substance: PS  
Sample Received Date: October 09, 2025  
Testing Period: October 09, 2025 to October 16, 2025  
Testing Requirements: Selected test(s) as requested by client  
Test Method: Please refer to next page(s)  
Test Results: Please refer to next page(s)

Reported by:



Signature / Vieky

Checked by:



Signature / Alex Peng

Approved by:



Signature / Kevin Sun

**Note:** This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. Any demurral to the content of test report, please propose in 15 days after the report's sending out, it will not be accepted after this date.

# Test Report

Report No.:SIT251009560201CR

Date:October 16, 2025

Page 2 of 9

## Summary of test results:

| Test Requested                                                                        | Conclusion  |
|---------------------------------------------------------------------------------------|-------------|
| Regulation (EC) No 1935/2004 & Regulation (EU) No 10/2011 and its amendment & AP(89)1 |             |
| Sensorial Examination Odour and Taste Test                                            | <b>PASS</b> |
| Specific Migration of 24 Heavy Metals                                                 | <b>PASS</b> |
| Overall Migration                                                                     | <b>PASS</b> |
| Specific migration of hexene in olive oil                                             | <b>PASS</b> |
| Specific migration of octene in olive oil                                             | <b>PASS</b> |

Remark: The client states that all the sample products are made of the same material.

# Test Report

Report No.:SIT251009560201CR

Date:October 16, 2025

Page 3 of 9

Test Result(s):

## Sensorial Examination Odour And Taste Test

Test Method: With reference to DIN10955:2024-01. No.of panelist: 6

| <u>Test Item(s)</u>                       | <u>Limit</u> | <u>Result</u>   |
|-------------------------------------------|--------------|-----------------|
|                                           |              | Entirety        |
| Test media                                | -            | Distilled water |
| Test temperature                          | -            | 23°C            |
| Test time                                 | -            | 24hr(s)         |
| Sensorial examination odour (Point scale) | 2.5          | 0.0             |
| Sensorial examination taste (Point scale) | 2.5          | 0.0             |

Remarks:

Intensity scale (rounded at 0.5):

- 0 - no perceptible difference
- 1 - just perceptible difference
- 2 - slight difference
- 3 - marked difference
- 4 - strong difference

# Test Report

Report No.:SIT251009560201CR

Date:October 16, 2025

Page 4 of 9

## Specific Migration of 24 Heavy Metals

Test Method:EN 13130-1:2004, the analysis was performed by ICP-OES.

Specimen No.1

Test media: 0.5% citric acid

Test temperature/ time: 100℃, 1hr(s)

| <u>Test Item(s)</u> | <u>Unit</u> | <u>MDL</u> | <u>1st+2nd Migration</u> |               | <u>3rd Migration</u> |               |
|---------------------|-------------|------------|--------------------------|---------------|----------------------|---------------|
|                     |             |            | <u>Limit</u>             | <u>Result</u> | <u>Limit</u>         | <u>Result</u> |
| Aluminum (Al)       | mg/kg       | 0.2        | 35                       | N.D.          | 5                    | N.D.          |
| Antimony (Sb)       | mg/kg       | 0.02       | 0.28                     | N.D.          | 0.04                 | N.D.          |
| Chromium (Cr)       | mg/kg       | 0.1        | 7                        | N.D.          | 1                    | N.D.          |
| Cobalt (Co)         | mg/kg       | 0.01       | 0.14                     | N.D.          | 0.02                 | N.D.          |
| Copper (Cu)         | mg/kg       | 0.1        | 28                       | N.D.          | 4                    | N.D.          |
| Iron (Fe)           | mg/kg       | 0.25       | 280                      | N.D.          | 40                   | N.D.          |
| Manganese (Mn)      | mg/kg       | 0.25       | 3.85                     | N.D.          | 0.55                 | N.D.          |
| Molybdenum (Mo)     | mg/kg       | 0.02       | 0.84                     | N.D.          | 0.12                 | N.D.          |
| Nickel (Ni)         | mg/kg       | 0.05       | 0.98                     | N.D.          | 0.14                 | N.D.          |
| Sliver (Ag)         | mg/kg       | 0.03       | 0.56                     | N.D.          | 0.08                 | N.D.          |
| Tin(Sn)             | mg/kg       | 5          | 700                      | N.D.          | 100                  | N.D.          |
| Vanadium(V)         | mg/kg       | 0.005      | 0.07                     | N.D.          | 0.01                 | N.D.          |
| Zinc (Zn)           | mg/kg       | 1          | 35                       | N.D.          | 5                    | N.D.          |
| Arsenic(As)         | mg/kg       | 0.001      | 0.014                    | N.D.          | 0.002                | N.D.          |
| Barium (Ba)         | mg/kg       | 0.25       | 8.4                      | N.D.          | 1.2                  | N.D.          |
| Beryllium(Be)       | mg/kg       | 0.005      | 0.07                     | N.D.          | 0.01                 | N.D.          |
| Cadmium (Cd)        | mg/kg       | 0.002      | 0.035                    | N.D.          | 0.005                | N.D.          |
| Lead (Pb)           | mg/kg       | 0.005      | 0.07                     | N.D.          | 0.01                 | N.D.          |
| Lithium (Li)        | mg/kg       | 0.02       | 0.336                    | N.D.          | 0.048                | N.D.          |
| Mercury (Hg)        | mg/kg       | 0.002      | 0.021                    | N.D.          | 0.003                | N.D.          |
| Thallium (Tl)       | mg/kg       | 0.001      | 0.007                    | N.D.          | 0.001                | N.D.          |
| Magnesium (Mg)      | mg/kg       | 0.05       | -                        | N.D.          | -                    | N.D.          |
| Titanium (Ti)       | mg/kg       | 0.05       | -                        | N.D.          | -                    | N.D.          |
| Zirconium (Zr)      | mg/kg       | 1          | 14                       | N.D.          | 2                    | N.D.          |

# Test Report

Report No.:SIT251009560201CR

Date:October 16, 2025

Page 5 of 9

Specimen No.1

Test media: Artificial tap water

Test temperature/ time: 100°C, 1hr(s)

| Test Item(s)    | Unit  | MDL   | 1st+2nd Migration |        | 3rd Migration |        |
|-----------------|-------|-------|-------------------|--------|---------------|--------|
|                 |       |       | Limit             | Result | Limit         | Result |
| Aluminum (Al)   | mg/kg | 0.2   | 35                | N.D.   | 5             | N.D.   |
| Antimony (Sb)   | mg/kg | 0.02  | 0.28              | N.D.   | 0.04          | N.D.   |
| Chromium (Cr)   | mg/kg | 0.1   | 7                 | N.D.   | 1             | N.D.   |
| Cobalt (Co)     | mg/kg | 0.01  | 0.14              | N.D.   | 0.02          | N.D.   |
| Copper (Cu)     | mg/kg | 0.1   | 28                | N.D.   | 4             | N.D.   |
| Iron (Fe)       | mg/kg | 0.25  | 280               | N.D.   | 40            | N.D.   |
| Manganese (Mn)  | mg/kg | 0.25  | 3.85              | N.D.   | 0.55          | N.D.   |
| Molybdenum (Mo) | mg/kg | 0.02  | 0.84              | N.D.   | 0.12          | N.D.   |
| Nickel (Ni)     | mg/kg | 0.05  | 0.98              | N.D.   | 0.14          | N.D.   |
| Sliver (Ag)     | mg/kg | 0.03  | 0.56              | N.D.   | 0.08          | N.D.   |
| Tin(Sn)         | mg/kg | 5     | 700               | N.D.   | 100           | N.D.   |
| Vanadium(V)     | mg/kg | 0.005 | 0.07              | N.D.   | 0.01          | N.D.   |
| Zinc (Zn)       | mg/kg | 1     | 35                | N.D.   | 5             | N.D.   |
| Arsenic(As)     | mg/kg | 0.001 | 0.014             | N.D.   | 0.002         | N.D.   |
| Barium (Ba)     | mg/kg | 0.25  | 8.4               | N.D.   | 1.2           | N.D.   |
| Beryllium(Be)   | mg/kg | 0.005 | 0.07              | N.D.   | 0.01          | N.D.   |
| Cadmium (Cd)    | mg/kg | 0.002 | 0.035             | N.D.   | 0.005         | N.D.   |
| Lead (Pb)       | mg/kg | 0.005 | 0.07              | N.D.   | 0.01          | N.D.   |
| Lithium (Li)    | mg/kg | 0.02  | 0.336             | N.D.   | 0.048         | N.D.   |
| Mercury (Hg)    | mg/kg | 0.002 | 0.021             | N.D.   | 0.003         | N.D.   |
| Thallium (Tl)   | mg/kg | 0.001 | 0.007             | N.D.   | 0.001         | N.D.   |
| Magnesium (Mg)  | mg/kg | 0.05  | -                 | N.D.   | -             | N.D.   |
| Titanium (Ti)   | mg/kg | 0.05  | -                 | N.D.   | -             | N.D.   |
| Zirconium (Zr)  | mg/kg | 1     | 14                | N.D.   | 2             | N.D.   |

Remarks:

1. mg/kg milligram per kilogram food simulants
2. MDL Method Detection Limit
3. N.D. Not Detected(less than MDL)
4. According to Council of Europe Resolution CM/Res(2020)9, the sum of the results of the first and second tests should not exceed an exposure equivalent to daily use for one week (i. e. 7\*SRL) and the results of the third migration should not exceed the SRL of the regulation.



# Test Report

Report No.:SIT251009560201CR

Date:October 16, 2025

Page 6 of 9

## Overall Migration

Test Method: EN 1186-1:2002 & EN 1186-3:2022

| <u>Test Item(s)</u> | <u>Test Condition</u>          | <u>Limit</u> | <u>Unit</u>        | <u>Result</u> |      |      |
|---------------------|--------------------------------|--------------|--------------------|---------------|------|------|
|                     |                                |              |                    | No.1          |      |      |
|                     |                                |              |                    | 1st           | 2nd  | 3rd  |
| Overall Migration   | 10% Ethyl alcohol<br>100°C, 4h | 10           | mg/dm <sup>2</sup> | <3.0          | <3.0 | <3.0 |
|                     | 3% Acetic acid<br>100°C, 4h    | 10           | mg/dm <sup>2</sup> | <3.0          | <3.0 | <3.0 |
|                     | 95% Ethyl alcohol<br>100°C, 4h | 10           | mg/dm <sup>2</sup> | <3.0          | <3.0 | <3.0 |
|                     | Isooctane<br>100°C, 4h         | 10           | mg/dm <sup>2</sup> | <3.0          | <3.0 | <3.0 |

Remarks:

1. mg/dm<sup>2</sup> = milligram per square decimeter
2. < = less than
3. Test condition was selected by client

# Test Report

Report No.:SIT251009560201CR

Date:October 16, 2025

Page 7 of 9

## Specific migration of hexene in olive oil

Test Method: XNO in-house method, analyzed by GC-MS.

| <u>Test Item(s)</u> | <u>Test Condition</u> | <u>Limit</u> | <u>Unit</u> | <u>Result</u> |     |     |
|---------------------|-----------------------|--------------|-------------|---------------|-----|-----|
|                     |                       |              |             | No.1          |     |     |
|                     |                       |              |             | 1st           | 2nd | 3rd |
| hexene              | olive oil<br>70°C, 1h | 3            | mg/kg       | <1            | <1  | <1  |

## Specific migration of octene in olive oil

Test Method: XNO in-house method, analyzed by GC-MS.

| <u>Test Item(s)</u> | <u>Test Condition</u> | <u>Limit</u> | <u>Unit</u> | <u>Result</u> |     |     |
|---------------------|-----------------------|--------------|-------------|---------------|-----|-----|
|                     |                       |              |             | No.1          |     |     |
|                     |                       |              |             | 1st           | 2nd | 3rd |
| octene              | olive oil<br>70°C, 1h | 15           | mg/kg       | <5            | <5  | <5  |

Remarks:

1. mg/kg = milligram per kilogram = ppm
2. < = less than

# Test Report

Report No.:SIT251009560201CR

Date:October 16, 2025

Page 8 of 9

According to Regulation (EU) No 10/2011 and its amendment (EU) 2020/1245, for repeated use materials and articles:

- 1) The applicable overall migration test shall be carried out three times on a single sample. The overall migration in the second test shall be lower than in the first test, and the overall migration in the third test shall be lower than in the second test. Compliance with the overall migration limit shall be verified on the basis of the level of the overall migration found in the third test.
- 2) Specific migration test(s) shall be carried out three times on a single sample. Compliance shall then be verified on the basis of the level of the migration found in the third test and on the basis of the stability of the material or article from the first to the third migration test. The stability of the material shall be considered insufficient if migration is observed above the level of detection in any of the three migration tests, and increases from the first migration test to the third migration test. In case of insufficient stability, compliance of the material shall not be established even in case the specific migration limit is not exceeded in any of the three tests. Irrespective of the above rules, a material or article shall never be considered to comply with the Regulation if in the first test a substance that is prohibited from migrating or from being released in detectable quantities.

**Note:** As specified by applicant, to test content in the selected materials of the submitted samples. Pic.1 to Pic.2 are the sample tested. The test results are only responsible for the submitted sample. The test report is only for customer research, teaching, internal quality control, product development and other purposes, for reference only.

# Test Report

Report No.:SIT251009560201CR


Date:October 16, 2025

Page 9 of 9

## Sample Description:

| Specimen No. | Description    | Material (claimed by the client) |
|--------------|----------------|----------------------------------|
| 1            | PS Plastic Box | PS                               |

## Sample Photo:



\*\*\* End of Report \*\*\*