



# Sensitivity Study of Battery Thermal Response to Cell Thermophysical Parameters

**Zeyu Sun** University of Birmingham

**Chongming Wang** Coventry University

**Quan Zhou and Hongming Xu** University of Birmingham

**Citation:** Sun, Z., Wang, C., Zhou, Q., and Xu, H., "Sensitivity Study of Battery Thermal Response to Cell Thermophysical Parameters," SAE Technical Paper 2021-01-0751, 2021, doi:10.4271/2021-01-0751.

## Abstract

Lithium-ion batteries (LiBs) have been widely used in electrified vehicles, and the battery thermal management (BTM) system is needed to maintain the temperature that is critical to battery performance, safety, and health. Conventionally, three-dimensional battery thermal models are developed at the early stage to guide the design of the BTM system, in which battery thermophysical parameters (radial thermal conductivity, axial thermal conductivity, and specific heat capacity) are required. However, in most literature, those parameters were estimated with greatly different values (up to one order of magnitude). In this paper, an investigation is carried out to evaluate the magnitude of the influence of those parameters on the battery simulation results. The study will determine if accurate measurements of battery thermophysical parameters are necessary. A unified method based on the


understanding of the sensitivity of the key battery thermophysical parameters is proposed to identify the impact of measurement accuracy of thermophysical parameter measurements in battery thermal modeling. Thermal simulations of battery thermal models at the cell level (cylindrical 18650) and module level are developed with COMSOL Multiphysics® to perform the sensitivity analysis. The simulation results indicate that the specific heat capacity is the most remarkable thermophysical parameter affecting the temperature rise, temperature difference between cells, and heat dissipation rate of the battery model. The temperature difference between cells in a module exhibits a high sensitivity to axial conductivity, up to 1.05. Therefore, the specific heat capacity of the battery and axial thermal conductivity needs to be accurately measured for battery thermal modeling, while the radial thermal conductivity can be measured with lower accuracies.

## Introduction


The technological innovation and development of the automobile industry face a tremendous challenge in preventing and reducing environmental damage. Powertrains electrification is regarded as an essential solution to address the challenge. Lithium-Ion batteries (LiBs) with a high specific power and energy density are the advanced energy storage technology for battery electric vehicles (BEV) and plug-in hybrid electric vehicles (PHEV) [23]. With the increase of the energy density and the expansion of applications of lithium-ion batteries, the problems of battery degradation and safety have become increasingly prominent. Battery performance is strongly dependent on temperature. The battery electrochemical reaction of the battery occurs faster as the temperature increases. Excessively temperature accelerates battery degradation, and even causes thermal runaway and fire in the worst scenario. It was reported that the lifespan of LiBs will be shortened by 60 days for every 1°C increase in temperature in the operating temperature range of 30–40°C [8]. The battery surface temperature exceeding 160°C will lead to electrolyte ignition [6]. Therefore, the temperature tolerance of lithium-ion batteries is narrowly limited. The optimal

operating temperature range for lithium-ion batteries is typically 15°C–35°C, and the temperature non-uniformity of batteries in a module/pack should be limited to below 5°C [9]. Consequently, LiBs in vehicles require a BTM system to maintain their performance and safe operation. Besides, numerical models are widely used to simulate the thermal behavior of LiBs during the charging/discharging when designing a battery thermal management system [7,25]. Depending on the simplification of the physical model, the dimension of the numerical model ranges from one dimension to three dimensions [26]. Smith et al. [24] developed a three-dimensional 18650 single-cell model and a battery module model with 16 parallel cells to evaluate the thermal safety margin. Research on the battery temperature distribution at the cell level and pack level demonstrates that the accuracy of underlying thermophysical properties (thermal conductivity, specific heat capacity, and density) are fundamental for developing numerical models to predict the thermal behavior of battery [9,20]. Bandhauer et al. [1] reviewed thermal phenomena related to LiBs and mentioned the lack of thermophysical properties data. They discovered that a limited number of papers measured the heat capacity of the battery

**FIGURE 14** Sensitive of the temperature difference between cells in a module.



**FIGURE 15** Sensitive of the heat dissipation rate of the module model.



- (1). The specific heat capacity is the most influencing thermophysical parameter on various simulation results of the battery thermal model. Therefore, accurate measurement of the specific heat capacity is important for battery thermal modeling.
- (2). The influences of radial thermal conductivity on battery thermal modeling are less prominent. The sensitivity of the max temperature of the cell model to radial thermal conductivity is only 0.2–0.38. Therefore, radial thermal conductivity values of the battery cell with lower measurement accuracy can be used in battery thermal modeling.
- (3). The sensitivity range of temperature difference between cells to axial thermal conductivity is 0.32–1.05 while that of the temperature difference between cells to radial thermal conductivity is 0.28–0.56. For the simulation of the temperature difference between battery cells, the axial thermal conductivity of the battery needs to be accurately measured.

## References

1. Bandhauer, T.M., Garimella, S., and Fuller, T.F., "A Critical Review of Thermal Issues in Lithium-Ion Batteries," *Journal of the Electrochemical Society* 158(3):R1-R25, 2011, doi:10.1149/1.3515880.
2. Barsoukov, E., Jang, J.H., and Lee, H., "Thermal Impedance Spectroscopy for Li-ion Batteries Using Heat-Pulse Response Analysis," *Journal of Power Sources* 109(2):313–320, 2002, doi:10.1016/S0378-7753(02)00080-0.
3. Chen, S.C., Wang, Y.Y., and Wan, C.C., "Thermal Analysis of Spirally Wound Lithium Batteries," *Journal of the Electrochemical Society* 153(4):A637-A648, 2006, doi:10.1149/1.2168051.
4. Comsol Multiphysics 5.3, <http://www.comsol.com>.
5. Drake, S.J., Wetz, D.A., Ostanek, J.K., Miller, S.P. et al., "Measurement of Anisotropic Thermophysical Properties of Cylindrical Li-Ion Cells," *Journal of Power Sources* 252:298–304, 2014, doi:10.1016/j.jpowsour.2013.11.107.
6. Esho, I., Shah, K., and Jain, A., "Measurements and Modeling to Determine the Critical Temperature for Preventing Thermal Runaway in Li-Ion Cells," *Applied Thermal Engineering* 145:287–294, 2018, doi:10.1016/j.applthermaleng.2018.09.016.
7. Jilte, R.D., and Kumar, R., "Numerical Investigation on Cooling Performance of Li-Ion Battery Thermal Management System at High Galvanostatic Discharge," *Engineering Science and Technology, An International Journal* 21(5):957–969, 2018, doi:10.1016/j.jestech.2018.07.015.
8. Jilte, R.D., Kumar, R., Ahmadi, M.H., and Chen, L., "Battery Thermal Management System Employing Phase Change Material with Cell-to-Cell Air Cooling," *Applied Thermal Engineering* 161:114199, 2019, doi:10.1016/j.applthermaleng.2019.114199.
9. Kim, J., Oh, J., and Lee, H., "Review on Battery Thermal Management System for Electric Vehicles," *Applied Thermal Engineering* 149:192–212, 2019, doi:10.1016/j.applthermaleng.2018.12.020.
10. Li, J., Cheng, Y., Jia, M., Tang, Y. et al., "An Electrochemical-Thermal Model Based on Dynamic Responses for Lithium Iron Phosphate Battery," *Journal of Power Sources* 255:130–143, 2014, doi:10.1016/j.jpowsour.2014.01.007.
11. Maleki, H., Al Hallaj, S., Selman, J.R., Dinwiddie, R.B. et al., "Thermal Properties of Lithium-Ion Battery and Components," *Journal of the Electrochemical Society* 146(3):947–954, 1999, doi:10.1149/1.1391704.
12. Maleki, H., and Shamsuri, A.K., "Thermal Analysis and Modeling of A Notebook Computer Battery," *Journal of Power Sources* 115(1):131–136, 2003, doi:10.1016/S0378-7753(02)00722-X.
13. Mills, A., and Al-Hallaj, S., "Simulation of Passive Thermal Management System for Lithium-Ion Battery Packs," *Journal of Power Sources* 141(2):307–315, 2005, doi:10.1016/j.jpowsour.2004.09.025.
14. Panasonic, "Panasonic NCR18650B," <http://www.panasonic.com/industrial/batteries-oem>, accessed Dec. 2020.
15. Pesaran, A.A., and Keyser, M., "Thermal Characteristics of Selected EV and HEV Batteries," in *presented at Sixteenth*

- Annual Battery Conference on Applications and Advances*, USA, January 12–12, 2001, doi:[10.1109/bcaa.2001.905129](https://doi.org/10.1109/bcaa.2001.905129).
16. Prada, E., Di Domenico, D., Creff, Y., Bernard, J. et al., “Simplified Electrochemical and Thermal Model of LiFePO<sub>4</sub>-Graphite Li-Ion Batteries for Fast Charge Applications,” *Journal of The Electrochemical Society* 159(9):A1508–A1519, 2012, doi:[10.1149/2.064209jes](https://doi.org/10.1149/2.064209jes).
  17. Sabbah, R., Kizilel, R., Selman, J.R., and Al-Hallaj, S., “Active (Air-Cooled) vs. Passive (Phase Change Material) Thermal Management of High Power Lithium-Ion Packs: Limitation of Temperature Rise and Uniformity of Temperature Distribution,” *Journal of Power Sources* 182(2):630–638, 2008, doi:[10.1016/j.jpowsour.2008.03.082](https://doi.org/10.1016/j.jpowsour.2008.03.082).
  18. Saw, L.H., Ye, Y., and Tay, A.A.O., “Electrochemical-Thermal Analysis of 18650 Lithium Iron Phosphate Cell,” *Energy Conversion and Management* 75:162–174, 2013, doi:[10.1016/j.enconman.2013.05.040](https://doi.org/10.1016/j.enconman.2013.05.040).
  19. Saw, L.H., Ye, Y., Tay, A.A., Chong, W.T. et al., “Computational Fluid Dynamic and Thermal Analysis of Lithium-Ion Battery Pack with Air Cooling,” *Applied Energy* 177:783–792, 2016, doi:[10.1016/j.apenergy.2016.05.122](https://doi.org/10.1016/j.apenergy.2016.05.122).
  20. Spinner, N.S., Hinnant, K.M., Mazurick, R., Brandon, A. et al., “Novel 18650 Lithium-Ion Battery Surrogate Cell Design with Anisotropic Thermophysical Properties for Studying Failure Events,” *Journal of Power Sources* 312:1–11, 2016, doi:[10.1016/j.jpowsour.2016.01.107](https://doi.org/10.1016/j.jpowsour.2016.01.107).
  21. Vadakkepatt, A., Trembacki, B., Mathur, S.R., and Murthy, J.Y., “Bruggeman’s Exponents for Effective Thermal Conductivity of Lithium-Ion Battery Electrodes,” *Journal of the Electrochemical Society* 163(2):A119–A130, 2015, doi:[10.1149/2.0151602jes](https://doi.org/10.1149/2.0151602jes).
  22. Wang, D., Bao, Y., and Shi, J., “Online Lithium-Ion Battery Internal Resistance Measurement Application in State-of-Charge Estimation Using the Extended Kalman Filter,” *Energies* 10(9):1284, 2017, doi:[10.3390/en10091284](https://doi.org/10.3390/en10091284).
  23. Wang, Y., Gao, Q., Wang, G., Lu, P. et al., “A Review on Research Status and Key Technologies of Battery Thermal Management and Its Enhanced Safety,” *International Journal of Energy Research* 42(13):4008–4033, 2018, doi:[10.1002/er.4158](https://doi.org/10.1002/er.4158).
  24. Xia, G., Cao, L., and Bi, G., “A Review on Battery Thermal Management in Electric Vehicle Application,” *Journal of Power Sources* 367:90–105, 2017, doi:[10.1016/j.jpowsour.2017.09.046](https://doi.org/10.1016/j.jpowsour.2017.09.046).
  25. Zhao, Y., Li, Q., Zou, B., Zhang, T. et al., “Performance of A Liquid Cooling-Based Battery Thermal Management System with A Composite Phase Change Material,” *International Journal of Energy Research* 44(6):4727–4742, 2020, doi:[10.1002/er.5254](https://doi.org/10.1002/er.5254).
  26. Zhu, D., Pritchard, E.G., and Silverberg, L.M., “A New System Development Framework Driven by A Model-Based Testing Approach Bridged by Information Flow,” *IEEE Systems Journal* 12(3):2917–2924, 2016, doi:[10.1109/JSYST.2016.2631142](https://doi.org/10.1109/JSYST.2016.2631142).

## Contact Information

**Zeyu Sun**

Ph.D. student

Department of Mechanical Engineering

University of Birmingham

Edgbaston Birmingham, B152TT

[ZXS994@student.bham.ac.uk](mailto:ZXS994@student.bham.ac.uk)