AKVA LINE™ 8000 Series White Acrylic Topcoat

EG8000011 / EG8000012 / EG8000013 / EG8000014 (10, 20, 30, 40 Sheen)

DESCRIPTION:

Akva Line™ 8000 Series White Acrylic Topcoat is a high-performance waterborne acrylic system for use on a wide range of wood substrates. The next generation waterborne system offers exceptional flow and leveling, and very good dry times. Designed as a self-seal topcoat, this system provides an extremely durable finish meeting KCMA test performance and chemical resistance requirements. A differentiating feature of ***Akva Line™ 8000 Series White Acrylic Topcoat*** is its ability to be applied over a broad range of ambient temperatures without the need for traditional accelerators or retarders, as it adapts to warm or cold climates, maintaining consistent viscosity.

PRODUCT DATA:

Color:	White	**VOC (as packaged / less exempts):**	0.49 lb/gal, 59 g/L
Solids % by Wt.:	38.4% ± 2 (Theoretical)	**Lbs. VHAPs / Lbs. Solids:**	0.09 lb/lb of solids
Solids % by Vol.:	27.0% ± 2 (Theoretical)	**Flash Point (PM/CC):**	N/A
Weight / Gal.:	9.76 lb	**Photo Chemically Reactive:**	No
Viscosity 25ºC / 77ºF:	**KU:** 81-89	**Shelf Life:**	1 year (at 15-25º C / 59º-77º F)
		Theo. Coverage@1mil dry	429 Sq. ft./gal. 100% Efficiency

MIXING / APPLICATION:

Working Temp: >18º C, 65º F substrate, coating and air

Catalyst: **EG8XA4081-14** AKVA LINE™ 8000 Crosslinker (aziridine)

Catalyzation: ***Optional:*** For increased film hardness and chemical resistance, mix 1% by volume with a 50/50 blend of Waterborne (aziridine) Crosslinker EG8XA4081-14 and deionized water.

Pot Life: If catalysation is required pot-life is 24 hrs. (23º C / 74º F)

Mixing: Mix thoroughly to ensure uniform consistency. Add Catalyst 50/50 water mixture under agitation.

Extending: ***Optional:*** You may carry over the catalyzed product overnight by adding 50% of the uncatalyzed AKVA LINE™ 8000 White Acrylic Topcoat at the end of the day. Catalyze the entire amount of material, not just the newly added material when ready to use. ***Catalyzed material must not be carried over the weekend and should be properly disposed of after the second 24-hour period.***

Reducer: Thinning is usually not required. If needed use Deionized water at up to 5%

Application: 100-125 (g/m²) Approx. 3.0 – 4.0 wet mils; @ 60%RH

Dry Film: Recommended dry film thickness per coat: 0.9 – 1.2 mils

Total System: Do not exceed 4.0 mils dry

Surface Prep: Substrate should be clean and free of grease and oil. Moisture content of the wood should be between 6%-8%. White wood sanding with 180 grit sandpaper. Sand the first coat (with 280 to 320 paper) in order to eliminate grain raising, if any, and improve adhesion of the subsequent coat. Topcoat within 8 hours of sanding.

Use Directions: For interior use only. Mix thoroughly before application. Stack only when the surface temperature is below 35ºC / 95 º F. Quicker stacking times are achievable relative to the amount of product that is applied.

App. Equip.: Conventional, HVLP Siphon Feed, Pressure Pot Systems, Airless Air Assist, and Flat Line Equipment.

Tinting: Can be tinted with **GIW** colorants to a maximum of 8% total colorant. Prior to application test a sample piece to assure proper color match.

System: **Seal Coat:** Apply first coat of AKVA LINE™ 8000 White Acrylic Topcoat at 3.0-4.0 mils wet. Allow to dry for 30 minutes. Sand with 320 grit sandpaper and remove sanding dust or debris. For best sanding results, use stearated sandpaper

Topcoat: Apply second coat AKVA LINE™ 8000 White Acrylic Topcoat at 3.0-4.0 mils wet. Allow to dry for 30-45 minutes.

Ind. Standards: Exceeds KCMA test requirements for finishes.

AKVA LINE™ 8000 Series White Acrylic Topcoat

EG8000015 / EG8000011 / EG8000012 / EG8000013 / EG8000014 / EG8000016 (05, 10, 20, 30, 40, 60 Sheen)

DRYING TIMES TO SAND / STACK:

Method	Drying Temp.	Drying Time (@ 60 % RH and thickness @ 1 mil dry)
Air Drying	20º C / 68º F	10-20 min. dry to **Touch** / 30 min. dry to **Handle & Sand** / 24 hrs to **stack**
Force Dry	49º C / 120º F 66º C / 140º F	10-15 min. **Flash-off** / 10-20 min. **Air Introduction /** 10-15 min. **Cooling**

APPLICATION RECOMMENDATIONS:

APPLICATION EQUIPMENT SETTINGS

Method of Application	Wet Film Mils / g/m²	Dry Film Mils / Microns
Conventional – Siphon Fed	4 – 5 mils / 100-125 g/m²	2.4-3.0 mils / 61-76 microns
Conventional – Pressure Pot	4 – 5 mils / 100-125 g/m²	2.4-3.0 mils / 61-76 microns
Airless Air Assist	4 – 5 mils / 100-125 g/m²	2.4-3.0 mils / 61-76 microns
HVLP - Siphon Fed	4 – 5 mils / 100-125 g/m²	2.4-3.0 mils / 61-76 microns
HVLP - Pressure Pot	4 – 5 mils / 100-125 g/m²	2.4-3.0 mils / 61-76 microns

All measurements and application equipment settings are based on application at temperature of 68°F. Viscosity will vary depending on the temperature of the liquid. The application equipment setting recommendations are guidelines only. The settings are starting point recommendations and adjustments to the equipment settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

REDUCTION – TIP SIZE – PSI SETTINGS

CONVENTIONAL:
Air Pressure: 45-55 psi
Fluid Pressure: 10-12 psi
Cap / Tip Size: .055 (1.4mm) – .070 (1.8 mm)

AIRLESS:
Pressure: 1600-2000 psi
Cap / Tip Size: .011-.013

AIR ASSISTED AIRLESS:
Air Pressure: 15-25 psi
Fluid Pressure: 600-900 psi
Cap / Tip Size: .011-.013

HVLP:
Air Pressure: 6-7 psi
Fluid Pressure: 5-10 psi
Cap / Tip Size: .055 (1.4mm) – .070 (1.8 mm)

CONTACTS:
PH: AcromaPro USA and Canada / 1-888-277-1448
www.AcromaPro.com

PRODUCT NOTES

- Keep from freezing. Do not store at temperature below 41°F.
- Do not apply at temperature below 55°F.
- Stir the product well before application to disperse any possible sedimentation. This operation is essential to ensure even matting on the substrate.
- Akva Line 8000 WB Crosslinker (**EG8XA4081-14**) is an aziridne based product. Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using these products. Using crosslinker is **Optional.**
- The use of equipment not in perfect order (defective gaskets, too high pressures) or of pumps with low capacity may cause major defects in the coating film (air bubbles).
- Once the can has been opened, the coating may rot because of the attack of bacteria commonly present in the air. This phenomenon is easily detectable because of the bad smell and by an increase of viscosity of the product stored in the can. Avoid leaving containers open for long periods of time and reclaiming used coating into fresh product.