LAQVA PRIME™ WHITE

ED5562001

DESCRIPTION:

Laqva Prime™ White is a fast drying, high solids waterborne primer for interior woodwork.This primer dries fast and sands easily, making it an easy tranisiton from traditional solvent-based products.This HAPS free and extremely low VOC primer is easy to apply and has good adhesion and good sandability with minimal grain raise. Laqva Prime™ White can be topcoated with Akvatopp™ Precatalyzed W/B and Laqva Top™ W/B Topcoats.

PRODUCT DATA:

Color:	White	**VOC (as packaged, maximum, less water and exempt solvents):**	0.29 lb/gal, 34 g/l
Solids % by Vol.:	45 % (Theoretical)	**VOC (emitted):**	0.13 lb/gal, 16 g/l
Solids % by Wt.:	61 % (Theoretical)	**Lbs. VHAPs / Lbs. Solids:**	0.00
Weight / Gal.:	12.16 lb	**Flash Point (PMCC):**	Does not flash
Viscosity 23ºC / 73ºF:	**Zahn #2 sig.**: 58-70 sec.	**Photo Chemically Reactive:**	No
Viscosity 23ºC / 73ºF:	**DIN 4**: 35-40 sec.	**Shelf Life:**	1 year (at 15-25º C / 59º-77º F)
		Theo. Coverage @ 1 mil dry	722 Sq. Ft./Gal. 100% Efficiency

MIXING / APPLICATION:

Working Temp: >20º C, 68º F substrate, coating and air
Hardener: N/A
Catalyzation: N/A
Pot Life: N/A
Mixing: Mix thoroughly to ensure uniform consistency.
Sealer: N/A
Reducer: May be reduced with water if desired.
Application: Can be hand sprayed or automatically applied.
Surface Prep: Substrate should be clean and free of grease and oil. Moisture content of the wood should be between 6%-8%. Sand 150 grit on open grain and 180 grit on closed grain wood.
Use Directions: For interior use only. Mix thoroughly before application. Dry time can be directly impacted by many factors, including film thickness. Users are urged to test the system under shop conditions.
App. Equip.: Conventional & HVLP Siphon Feed and Pressure Pot Systems and Airless Air Assist Equipment.
Tinting: Can be used with Chroma-Chem 896 pigments, and Aqualux H pigments, at up to 10% by weight.

DRYING TIMES:

Method	Drying Temp.	Drying Time (@ 60 % RH)
Air Drying	20º C / 68º F	30 to 45 minutes sandable; 3-4 hrs stackable

LAQVA PRIME™ WHITE
ED5562001

APPLICATION RECOMMENDATIONS:

APPLICATION EQUIPMENT SETTINGS

Method of Application	Wet Film Mils / g/m²	Dry Film Mils / Microns
Conventional – Siphon Fed	3 – 4 mils / 110 - 150 g/m²	1.4 – 1.9 mils / 35 – 47 microns
Conventional – Pressure Pot	3 – 4 mils / 110 - 150 g/m²	1.4 – 1.9 mils / 35 – 47 microns
Airless Air Assist	3 – 4 mils / 110 - 150 g/m²	1.4 – 1.9 mils / 35 – 47 microns
HVLP - Siphon Fed	3 – 4 mils / 110 - 150 g/m²	1.4 – 1.9 mils / 35 – 47 microns
HVLP - Pressure Pot	3 – 4 mils / 110 - 150 g/m²	1.4 – 1.9 mils / 35 – 47 microns

All measurements and application equipment settings are based on application at temperature of 68°F. Viscosity will vary depending on the temperature of the liquid. The application equipment setting recommendations are guidelines only. The settings are starting point recommendations and adjustments to the equipment settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

REDUCTION – TIP SIZE – PSI SETTINGS

Conventional Equipment Siphon Feed:
Us as is or reduce with water, nozzle size 0.070 inches (1.8mm) – 0.080 inches (2.0 mm), atomizing air 25 psi (1.7 bar)–40 psi (2.8 bar).
Conventional Equipment Pressure Pot:
Use as is or reduce with water, nozzle size 0.070 inches (1.8mm) – 0.080 inches (2 mm), atomizing air 25 psi(1.7 bar)–40 psi (2.8 bar), Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar)
Airless Air Assist Equipment:
Use as is or reduce with water, tip size 0.015 inches (0.38mm) - .016 inches (0.4mm), fluid pressure 300 psi – 550psi, atomizing air 15 psi (1 bar) to 29psi (2 bar).
HVLP Equipment Siphon Feed:
Use as is or reduce with water. Nozzle size .070 inch (1.8mm) -0.080 inch (2mm) nozzle, atomizing air 29 psi (2 bar) -44 psi (2.8 bar).
HVLP Equipment Pressure Pot:
Use as is or reduce with water, nozzle size .070 inches (1.8mm)-.080 inches (2 mm) nozzle, atomizing air 29psi (2 bar) - 39 psi (2 bar). Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar)

CONTACTS:
PH: AcromaPro USA and Canada / 1-888-277-1448

www.AcromaPro.com

PRODUCT NOTES

- Like most water based products, Laqva Prime™ should not be force dried with high speed air for the first couple of minutes to avoid mud-cracking.
- It is not recommended to topcoat Laqva Prime™ with acid cure finishes.