

371-1900 Series

SUPERLAC ELITE™ Pre-Catalyzed Lacquers

Date: October 31, 2017 (supersedes all previous revisions)



GENERAL INFORMATION

Axalta's SUPERLAC ELITE™ is the highest solids product in the SUPERLAC™ family. It offers superior build and unmatched versatility for a wide range of end-uses. ELITE™ offers excellent mar, solvent, and chemical resistance and passes all KCMA performance standards when applied properly. It is available in a wide range of gloss levels and is good for all wood species.



1. PRODUCTS

- 371-1972-90 371-1990-50
- 371-1975-35 371-1982-25
- 371-1973-10



2. MIXING RATIO

- All products should be stirred well before use and, for best results, continuously agitated while in use.



3. SHELF LIFE @ 77°F (25°C)

- 6 months from manufacturing date



4. CLEAN UP

- Dispose of dirty solvent and cleaning rags in a safe and compliant manner. Solvent or lacquer soaked rags should be stored in water-filled, closed containers prior to disposal.



5. ADDITIVES

- In the event of blushing or blistering, add Axalta 390-9303-00 Lacquer Retarder to extend dry time.



6. SURFACE PREPARATION

- Surface must be clean and dust free with a moisture content of 6-8% prior to finishing. Remove all dust, dirt, wax and wood marks. Proper sanding and preparation of the wood is critical to achieving consistent results.
- On new wood, finish sand surface with 150-180 grit sandpaper
- On previously finished wood, remove all old paint or varnish and follow new wood procedure.



7. COMPANION PRODUCTS

- 371-1946-00 & 371-1970-00 Pre-Catalyzed Sealers
- NAS4000, AVS4690, 378-2020 & UAC0004 Vinyl Sealers
- 383-1902-00 & 383-9905-00 SUPERLAC™ Basecoats



9. SUBSTRATES

- Commonly used furniture and cabinetry woods
- MDF/HDF

NOTE: Not to be used on exterior applications



10. APPLICATION

- See application notes for full details.



11. FLASH / DRY TIMES

AIR DRY @ 77°F (25°C)

Dry to touch	20 - 25 Minutes
Flash between coats	35 - 45 Minutes
To Stack	12 - 24 Hours



12. FORCE DRY

Flash	10 Minutes
Bake	5 Minutes @ 125°F
Cool Down	10 Minutes ambient
Stack	After cool down



13. GUN SET UP

Gravity Feed	1.6 mm - 1.8 mm
Siphon Feed	1.8 mm - 2.0 mm
Airless	10 - 15 thousandths
Air-Assisted Airless	11 - 15 thousandths

AIR PRESSURES

Gravity Feed	30-35 psi (2.0-2.4 bar)
Siphon Feed	35-40 psi (2.4-2.8 bar)
Air-Assisted Airless	10-20 psi (0.7-1.4 bar)
See spray gun manufacturer data for more information	



14. PHYSICAL DATA

Viscosity	24±2" #2 Zahn at 25°C (~77°F)
Weight Solids %	30±2%
Volume Solids %	22±2%
Actual VOC	4.46lbs/gal of Product
VOC Ratio (lb.voc/lb.solids)	2.27lb VOC/lb solid
Regulatory VOC (less water and exempt solvents)	651g/l
Weight Per Gallon	7.6lbs/gal
Flash Point	Tag Open Cup (TOC): -4°C (~25°F)
Theoretical Coverage	302 ft/gal @ 1 mil dry
VHAP (lb.HAP/lb.solids)	1.01lb VHAP/lb solid
Coating Category	Clear

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Axalta assumes no obligation or liability for use of this information. **UNLESS AXALTA AGREES OTHERWISE IN WRITING, AXALTA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. AXALTA WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. The information in this sheet, as well as the products referenced herein, shall be considered "Confidential Information". Wet samples and uncured samples of these products shall be maintained as confidential and shall not be disclosed to any third party without the prior written permission of Axalta. IU-COR-00047

371-1900 Series

SUPERLAC ELITE™ Pre-Catalyzed Lacquers

Date: October 31, 2017 (supersedes all previous revisions)



Application Notes:

All products should be stirred well before use and, for best results, continuously agitated while in use. Do not mix with other finishing systems or deviate from these finishing recommendations. Axalta will not be held liable for finish failures resulting from the mixing of products or deviations from finishing recommendations. Sanding should be completed immediately prior to the application of any additional coats.

1) **Stain:** If desired, stain substrate with Axalta GRAINTONE PLUS™ Wiping Stain, or other approved Axalta colour system. Refer to Technical Data Sheet for detailed use instructions.

2) **Seal:** 371-1900 Series lacquers are self-sealing. If a sealer is desired, use 371-1970-00 or other approved sealer. Refer to Technical Data Sheet for detailed use instructions. Sand with 240–320 grit steared, silicon carbide sandpaper.

3) **Finish:** Choose the appropriate sheen from the series, and agitate well before applying. Verify the surface is clean and dust free, and apply an even coat at 3–4 wet mils using conventional, airless, air-assisted or HVLP spray equipment.

If additional coats are required, wait a minimum of 30 minutes between applications. Sand with 280–320 grit steared, silicon carbide sandpaper before recoating.

If reduction is necessary, use Axalta 390-7001-00 Lacquer Thinner. See Physical Properties portion of this document for additional details. In the event of blushing or blistering, add Axalta 390-9303-00 Lacquer Retarder to extend dry time. See Physical Properties portion of this document for additional details.

IMPORTANT NOTE: System's total dry film build should not exceed **4 mils**. A higher build may result in a film breakdown or reduction in performance.

Clean Up:

Use lacquer thinner to clean equipment. Refer to your local regulations for compliance requirements for cleaning thinners, or use recommended Axalta Lacquer Thinner. Dispose of dirty solvent and cleaning rags in a safe and compliant manner. Solvent or lacquer soaked rags should be stored in water-filled, closed containers prior to disposal.

Precautions:

These products are recommended for professional application and are designed for interior use only. Always pre-test the system on your substrate and under your line conditions to verify suitability to the application and to avoid potential need for costly refinishing. Axalta Industrial Wood Coatings are designed to protect and enhance the natural beauty of wood, but cannot eliminate natural discoloration or deterioration of wood as it ages.

Additional notes:

Do not mix with other finishing systems or deviate from these finishing recommendations. Axalta will not be held liable for finish failures resulting from the mixing of products or deviations from finishing recommendations.

Storage:

Store in a cool, dry place. DO NOT FREEZE! Product should be stored in temperatures between 50°–110°F. Close all containers after use. Do not store near heat or sparks. Spills should be cleaned up with non-sparking tools. [See the product SDS for complete safety information.](#)

Warning:

Always pre-test the system on your substrate and under your line conditions to verify suitability to the application and avoid potential need for costly refinishing. All dry times listed are as tested under ideal indoor environmental conditions of 78°F (26°C) with relative humidity not exceeding 50%. These products are recommended for use under temperature conditions of 60–100°F (16–38°C) and when relative humidity is below 50% during application and drying time. Low temperatures, poor air circulation or high humidity will extend dry times. **Axalta strongly recommends against use of these products if temperatures of air, material, or surface to be coated are below 60°F (16°C) or below the dew point. Abnormal conditions of temperature or humidity may adversely affect product performance.** Please contact your authorized Axalta Industrial Wood Coatings distributor for additional product use recommendations and finishing guidance.