

TECHNICAL DATA SHEET

AT95W00XX
EA HYDROPLUS™ WATERBORNE WHITE TOPCOAT

 10 Sheen White..... AT95W0010
 30 Sheen White..... AT95W0030

 20 Sheen White..... AT95W0020
 40 Sheen White.....AT95W0040

Gloss level:	10, 20, 30, 40 units
Area of use:	Interior wood products such as residential furniture, cabinetry, architectural woodworking
Method of use:	Conventional, Airless, Air Assisted Airless, HVLP
Mixing procedure:	Reduce up to 10% with deionized water.
Clean up:	Clean tools/equipment immediately after use with water. Flush equipment with solvent to prevent corrosion.

Technical characteristics

Theoretical Solids content (%) White & Neutral Bases:	Wt. Solids: 37%-38% Vol. Solids: 25%-28%
Viscosity KU Viscometer(77°F):	81-89 KU
Recommended wet film thickness per coat:	3.0 – 4.0 mils
Recommended dry film thickness per coat:	0.9 – 1.2 mils
Recommended total system dry film thickness:	Do not exceed 4.0 mils dry
Spread rate:	429 sq. ft/gal @ 1.0 mil dft, no loss
Drying time (at 77°F):	Touch dry 10-20 minutes To handle 30 minutes Sand 30 minutes Recoat 30 – 45 minutes Stackable 24 hours
Forced drying:	Flash off 10-15 minutes (<50% RH) Hot air @ 120 - 140°F 10-20 minutes Cooling 15 minutes
Shelf-life:	12 months, unopened After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.
VOC (Theoretical as packaged, maximum):	1.49 lb/gal, 178 g/L (less exempt solvents)
VHAPS (as packaged):	0.09 lb/lb of solids
Flash Point:	N.A.

 An Environmental Data Sheet is available from your local servicing facility, or at www.paintdocs.com.

General Characteristics

Hydroplus™ EA White Topcoat is a high quality water reducible acrylic system for use on a wide variety of wood species. This quality topcoat dries rapidly and provides an excellent appearance over wood. May tint using GIW or Kem Aqua Colorants. This waterborne topcoat is designed for use as a self-sealing topcoat. It has good build and provides a durable finish with very good hardness and good chemical resistance compared to traditional acrylic latex and nitrocellulose finishes. Properly applied, this finish meets or exceeds KCMA test requirements for finishes. EA HYDROPLUS™ Waterborne White Topcoat is low VOC and UL GREENGUARD Gold certified for low chemical emissions.

TECHNICAL DATA SHEET

AT95W00XX**EA HYDROPLUS™ WATERBORNE WHITE TOPCOAT****Catalyzing**

For increased film hardness and chemical resistance, EA Hydroplus™ Waterborne White may be catalyzed at 1% by volume with a 50/50 blend of Waterborne (aziridine) Crosslinker XA4081000 and deionized water. Stir the blend well. Additional catalyst volumes will not improve performance properties. When catalyzed, the EA Hydroplus™ White Topcoat has a 24 hour pot-life. You may carry over the catalyzed product overnight by adding 50% of the uncatalyzed Hydroplus™ at the end of the day. Catalyze the entire amount of material, not just the newly added material when ready to use the following day. Catalyzed material must not be carried over the weekend and should be properly disposed of after the second 24 hour period.

Tinting

Can be tinted using KEM AQUA® Colorants. The EA Hydroplus™ AT95F00xx Clears are designed to be blended with the white bases to expand color capability. These clear bases can also be used as a stand alone, self-sealing clear topcoat or as a protective clear coat or “scratch” coat over the pigmented AT95W00xx series products.

Tint Code	Blend Code
CE100AT85	A95XX

Substrate preparation

Wood – New Work (interior only): Must be clean, dry and finish sanded. Substrate should be free of grease, oil, dirt, fingerprints and any contamination. Moisture content of wood should be 6-8%.

Previously finished wood (interior only): Strip old finishes completely and remove all contaminants from the surface. Make sure surface is dry. Finish as new work.

Wood Finishing System

1. **Seal** – Apply first coat of EA Hydroplus™ Waterborne White Topcoat at 3.0-4.0 mils wet. Allow to dry for 30 minutes. Sand with 320 grit sand paper and remove sanding dust or debris. For best sanding results, use steared sand paper.
2. **Topcoat** – Apply second coat of EA Hydroplus™ Waterborne White Topcoat at 3.0-4.0 mils wet. Allow to dry for 30-45 minutes.
3. **Topcoat** – Apply additional coat of EA Hydroplus™ Waterborne White Topcoat to achieve build or depth. Do not exceed 4.0 mils total dry film thickness for the complete finishing system.

Special instructions:

- Keep from freezing. Do not store at temperature below 41°F.
- Do not apply at temperature below 55°F.
- Stir the product well before application in order to disperse any possible sedimentation. This operation is essential to ensure even matting on the substrate.
- Because of the variety of materials used to manufacture wood furniture, when moving to a waterborne system from a solvent based system, it is very important to check with the supplier the suitability of equipment and components used, with particular attention to electrostatic guns, pumps, seals, silicones, glues, products for booth water treatment, packing materials, sanding papers, putties, etc.
- The use of coating devices not in perfect order (defective gaskets, too high pressures) or of pumps with low capacity may cause major defects in the coating film (air bubbles).
- Waterborne Crosslinker (XA4081000) is a aziridine product. Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using these products.
- Once the can has been opened, the coating may rot because of the attack of bacteria commonly present in the air. This phenomenon is easily detectable because of the bad smell and by an increase of viscosity of the product stored in the can. Avoid leaving containers open for long periods of time and reclaiming used coating into fresh product.

TECHNICAL DATA SHEET

AT95W00XX

EA HYDROPLUS™ WATERBORNE WHITE TOPCOAT

Application Equipment Settings

<u>Conventional</u>		<u>Air Assisted Airless</u>	
Air Pressure:	45-55 psi	Air Pressure:	15-25 psi
Fluid Pressure:	10-12 psi	Fluid Pressure:	600-900 psi
Cap/Tip Size:	.055 (1.4mm) – .070 (1.8 mm)	Cap/Tip Size:	.011 - .013
<u>Airless</u>		<u>HVLP</u>	
Pressure:	1600-2000 psi	Air Pressure:	6-7 psi
Tip Size:	.011 - .013	Fluid Pressure:	5-10 psi
		Cap/Tip Size:	.055 (1.4mm) – .070 (1.8 mm)

For airless and air assisted airless application, box coating technique may be required to achieve desired appearance.

Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product.

To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or www.paintdocs.com.

Please direct any questions or comments to your local Sherwin-Williams facility.

Note: All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found at www.sherwin.com. Please review these terms and conditions prior to the purchase of the products. Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.