



MATADOR™ PLUS WHITE TINT BASE

DH5760011 / DH5760012 / DH5760014 (10, 20, 40 Gloss)

DESCRIPTION:

Matador™ Plus White Tint Base is a high solids pigmented topcoat with exceptional hang and fast dry time. This product offers very good vertical build and is recommended for a variety of interior woodworking applications. Matador Plus White Tint Base has very high solids content and very quick build in which a primer is not usually required. With its excellent filling and sanding properties, Matador Plus will improve process efficiencies. Excellent chemical and moisture resistance characteristics make it an ideal finishing system for kitchen cabinets, bath vanities and furniture. Matador™ Plus White Tint Base allows for custom color matching of lighter colors and is a low HAPS solvent system that meets KCMA

PRODUCT DATA:

Color:	White	VOC (as packaged, maximum, less water and exempt solvents):	2.39-2.47 lb/gal, 286-296 g/l
Solids % by Vol.:	63-65 % (Theoretical)	VOC (emitted):	2.39-2.47 lb/gal, 286-296 g/l
Solids % by Wt.:	77-79 % (Theoretical)	Lbs. VHAPs / Lbs. Solids:	0.06-0.08
Weight / Gal.:	11.15 lb	Flash Point (PM/CC):	13° C / 55° F
Viscosity 25°C / 77°F:	KU: 80-88	Photo Chemically Reactive:	Yes
		Shelf Life:	1 year (at 15-25° C / 59°-77° F)
		Theo. Coverage@1mil dry	950 Sq. Ft./Gal. 100% Efficiency

MIXING / APPLICATION:

Working Temp: >18° C, 65° F substrate, coating and air
Catalyst: 2750 Standard; 494 Slow; 309 Haps Free Fast
Catalyzation: 16 % Parts by volume
Pot Life: 8 hrs. (23° C / 74° F)
Mixing: Mix thoroughly to ensure uniform consistency. Add Catalyst under Agitation then add solvent to adjust viscosity if necessary.
Reducer: Thinner 219 - Regular; Thinner OC 140 - Fast; Thinner 309 - Haps Free, Thinner 419 – Slow, Haps Free
Application: 100-125 (g/m²) Approx. 4-5 wet mils; Min 3 mil wet –Max 6 mil wet @ 60%RH
Surface Prep: Substrate should be clean and free of grease and oil. Moisture content of the wood should be between 6%-8%. White wood sanding with 180 grit sandpaper. Sand the first coat (with 280 to 320 paper) in order to eliminate grain raising, if any, and improve adhesion of the subsequent coat. Topcoat within 8 hours of sanding.
Use Directions: For interior use only. Mix thoroughly before application. Stack only when the surface temperature is below 35°C / 95 ° F. Quicker stacking times are achievable relative to the amount of product that is applied.
App. Equip.: Conventional & HVLP Siphon Feed and Pressure Pot Systems and Airless Air Assist Equipment.
Tinting: Can be tinted with OptiColor XP colorants to a maximum of 9% total colorant. Prior to application test a sample piece to assure proper color match.
Ind. Standards: This product meets the quality standard System - 5 - Conversion Varnish, Transparent, for AWI.

DRYING TIMES TO SAND / STACK:

Method	Drying Temp.	Drying Time (@ 60 % RH and thickness @ 1 mil dry)
Air Drying	20° C / 68° F	25-30 min. dry to handle / 60-90 min. dry to sand / 2-4 hrs to stack
Force Dry	49° C / 120° F	30 min.
	66° C / 150° F	10 min

MATADOR™ PLUS WHITE TINT BASE

DH5760012 / DH5760014 (20, 40 Gloss)

APPLICATION RECOMMENDATIONS:

APPLICATION EQUIPMENT SETTINGS

Method of Application	Wet Film		Dry Film	
	Mils	g/m ²	Mils	Microns
Conventional – Siphon Fed	4 – 5 mils	100-125 g/m ²	2.4-3.0 mils	61-76 microns
Conventional – Pressure Pot	4 – 5 mils	100-125 g/m ²	2.4-3.0 mils	61-76 microns
Airless Air Assist	4 – 5 mils	100-125 g/m ²	2.4-3.0 mils	61-76 microns
HVLP - Siphon Fed	4 – 5 mils	100-125 g/m ²	2.4-3.0 mils	61-76 microns
HVLP - Pressure Pot	4 – 5 mils	100-125 g/m ²	2.4-3.0 mils	61-76 microns

All measurements and application equipment settings are based on application at temperature of 68°F. Viscosity will vary depending on the temperature of the liquid. The application equipment setting recommendations are guidelines only. The settings are starting point recommendations and adjustments to the equipment settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

REDUCTION – TIP SIZE – PSI SETTINGS

Conventional Equipment Siphon Feed:

Reduce to 18-21 sec. #4 Ford viscosity cup (20-22 sec Sig. Zahn 2 cup), nozzle size 0.070 inches (1.8 mm) to 0.080 inches (2.0 mm), atomizing air 40 psi (2.8 bar) to 50 psi (3.5 bar).

Conventional Equipment Pressure Pot:

Reduce to 18-21 sec. #4 Ford viscosity cup (20-22 sec Sig. Zahn 2 cup), nozzle size 0.070 inches (1.8 mm) to 0.080 inches (2.0 mm), atomizing air 40 psi (2.8 bar) to 50 psi (3.5 bar), Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar)

Airless Air Assist Equipment:

Reduce to 18-25 sec. #4 Ford viscosity cup (20-25 sec Sig. Zahn 2 cup), tip size 0.013 inches (0.33 mm) to 0.016 inches (0.41 mm), fluid pressure 290 psi (20 bar) to 580 psi (40 bar), atomizing air 11 psi (0.8 bar) to 17 psi (1.2 bar).

HVLP Equipment Siphon Feed:

Reduce to 17-21 sec. #4 Ford viscosity cup (19-22 sec Sig. Zahn 2 cup), nozzle size 0.070 inches (1.8 mm) to 0.080 inches (2.0 mm), atomizing air 35 psi (2.4 bar) to 45 psi (3.1 bar).

HVLP Equipment Pressure Pot:

Reduce to 17-21 sec. #4 Ford viscosity cup (19-22 sec Sig. Zahn 2 cup), nozzle size 0.070 inches (1.8 mm) to 0.080 inches (2.0 mm), atomizing air 20 psi (1.37 bar) to 25 psi (1.72 bar). Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar)

PRODUCT NOTES

- Matador™ Plus can be custom color matched and is available in 20 and 40 gloss ranges.
- Matador™ Plus has excellent application properties with very good vertical hang.
- To improve the flow 3%-5% Thinner 419 can be added.
- Maximum recommended dry film thickness for total coating system is 7 dry mils. Heavier film build may cause cracking.
- Always test for adhesion and compatibility when top coating Matador™ Plus with alkyd paints.
- This product is thixotropic, and apparent viscosity may be higher than actual viscosity. It is recommended to mix product for 5 to 10 minutes before taking viscosity measurements.
- Temperatures must be above 68°F during application and cure to ensure acceptable coating properties.
- Matador™ Plus must be catalyzed 16% by volume with the recommended catalyst. Do not over catalyze as this may cause cracking over time.

CONTACTS:

PH: AcromaPro USA and Canada / 1-888-277-1448

www.AcromaPro.com



TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Material Safety Data Sheet (MSDS) for safety information and cautions prior to using this product. For Regulatory compliance data (i.e. VOC, HAPS, etc.), obtain an Environmental Data Sheet (EDS) prior to using the product. A MSDS and/or EDS is available from your local distributor or representative. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, AcromaPro cannot make any warranties as to the end result.