

Water White “C” Conversion Varnish

DM5381005.....5 Gloss

DV5380000.....Catalyst

DESCRIPTION:

Water White “C” Conversion Varnish is a low sheen penetrating type conversion varnish for that close to the grain look and feel designed for the general interior wood finishing market. This conversion varnish is water white in appearance with excellent clarity and contains UV absorbers for added protection from incidental UV. This finish is intended for use as a multi-coat, self-sealing system. Water White “C” Conversion Varnish has a 24 hour pot-life after catalyzation. This finishing system is designed to meet KCMA test requirements for finishes, providing a finishing system that has excellent chemical and moisture resistance. Typical end use applications include kitchen cabinetry, residential furniture and other types of interior wood products.

PRODUCT DATA:

Color:	Water White	VOC theoretical, as packaged:	5.10 lbs. / gal or 611 g/L less exempts
Solids % by Vol.:	29% (Theoretical as packaged)	VOC (catalyzed, no reduction):	5.09 lbs. / gal or 610 g/L less exempts
Solids % by Wt.:	35% (Theoretical as packaged)	Lbs. VHAPs / Lbs. Solids:	0.11
Weight / Gal.:	7.88 lbs.	Flash Point (PMCC) packaged:	10° C / 50° F
Viscosity 25°C / 77°F:	#2 Zahn: 19-25 secs.(packaged)	Photo Chemically Reactive:	No
		Shelf Life:	12 months (at 15-25° C / 59-77° F)
		Coverage @ 1 mil dry (admixed)	455 Sq. Ft./Gal. @ 100% Efficiency

MIXING / APPLICATION:

Working Temp: >25° C, 77° F substrate, coating and air
Hardener: Catalyst, DV5380000
Catalyzation: 5 ounces of catalyst (by volume) to one gallon of Conversion Varnish
Pot Life: 24 hours
Mixing: Mix thoroughly to ensure uniform consistency.
Reducer: Not required. May be reduced with Butyl Acetate or Acetone at 5-10% by volume. MAK may be used to retard the dry time by adding 5-10% by volume.
Application: Spray apply 3 - 5 wet mils per coat. Maximum total system dry film thickness should not exceed 4.0 mils.
Surface Prep: Substrate should be clean and free of grease and oil. Moisture content of the wood should be between 6%-8%. Using a denibber will eliminate some grain-raising and smooth the edges.
Use Directions: **Self-sealing system:** Apply first coat at 3-5 mils wet. Allow 40 minutes air dry. Sand with 320 grit and remove dust or debris. Apply an additional 1-2 coats depending film build. Do not exceed 4.0 mils dry for total system film build. Users are urged to test the system under shop conditions.
App. Equip.: Conventional & HVLP Siphon (Gravity) Feed and Pressure Pot Systems, Airless and Airless Air Assist Equipment.
Ind. Standards: This product meets KCMA test requirements for finishes.

AIR DRYING / FORCED DRYING:

Method	Drying Temp.	Drying Time (@ 60 % RH and thickness @ 1 mil dry)
Air Drying	25° C / 77° F	15 min. dry to touch, 40 min. to sand and topcoat
Forced Drying	25° C / 77° F	Flash-off for 10 minutes after application
Forced Drying	52° C / 125° F	15 minutes

Water White “C” Conversion Varnish

DM5381005.....5 Gloss

DV5380000.....Catalyst

APPLICATION RECOMMENDATIONS:

APPLICATION EQUIPMENT SETTINGS

Method of Application	Wet Film		Dry Film	
	Mils	/ g/m ²	Mils	/ Microns
Conventional – Siphon Fed	3 – 5	/ 75 - 125	0.90 – 1.4	/ 23 – 36
Conventional – Pressure Pot	3 – 5	/ 75 - 125	0.90 – 1.4	/ 23 – 36
Airless Air Assist	3 – 5	/ 75 - 125	0.90 – 1.4	/ 23 – 36
HVLP - Siphon Fed	3 – 5	/ 75 - 125	0.90 – 1.4	/ 23 – 36
HVLP - Pressure Pot	3 – 5	/ 75 - 125	0.90 – 1.4	/ 23 – 36

All measurements and application equipment settings are based on application at a temperature of 68°F. Viscosity will vary depending on the temperature of the liquid. The application equipment setting recommendations are guidelines only. The settings are starting point recommendations and adjustments to the equipment settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

REDUCTION – TIP SIZE – PSI SETTINGS

Conventional Equipment Siphon Feed:

Reduce to 18-21 seconds #4 ford viscosity cup, nozzle size 0.070 inches (1.8mm) – 0.0 inches (2.0 mm), atomizing air 40 psi (2.8bar)–50 psi (3.5 bar).

Conventional Equipment Pressure Pot:

Reduce to 18-21 seconds #4 ford viscosity cup, nozzle size 0.472 inches (1.2mm) – 0.055 inches (1.4 mm), atomizing air 40 psi(2.8 bar)–50 psi (3.5 bar), Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar).

Airless Air Assist Equipment:

Reduce to 18-25 seconds #4 ford viscosity cup, tip size.011inches (0.28mm) - .013 inches (0.33mm), fluid pressure 290 psi (20 bar) – 580psi(40 bar), atomizing air 11psi (0.8 bar) to 17psi (1.2 bar).

HVLP Equipment Siphon Feed:

Reduce to 17-21 seconds #4 ford viscosity cup,.061inch (1.5mm) -.072inch (1.8MM) nozzle, atomizing air 35psi (2.4bar) -45 psi (3.1bar).

HVLP Equipment Pressure Pot:

Reduce to 17-21 seconds #4 ford viscosity cup,0.472 inches (1.2mm) – 0.055 inches (1.4 mm) nozzle, atomizing air 20psi (1.37 bar) -25 psi (1.72 bar). Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar).

Clean tools/equipment immediately after use with Lacquer Thinner. Follow manufacturer's safety recommendations when using any solvent.

CONTACTS:

PH: AcromaPro USA and Canada / 1-888-277-1448

www.AcromaPro.com



PRODUCT NOTES

- It is recommended to apply no less than 2.0 mils dry of Water White “C” Conversion Varnish for adequate performance. Do not exceed 4.0 mils dry for the total system film build.

TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. For Regulatory compliance data (i.e. VOC, HAPS, etc.), obtain an Environmental Data Sheet (EDS) prior to using the product. Regulatory documents are available from your local distributor or at www.paintdocs.com. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, AcromaPro cannot make any warranties as to the end result.