



LAQVA™ PRIME UNIVERSAL

ED6000202

DESCRIPTION:

LAQVA™ Prime Universal is a fast drying waterborne acrylic primer designed for spray application for use on interior wood products such as kitchen cabinets, residential furniture and architectural millwork. This high solids primer is designed to be topcoated with waterborne, solvent borne, and waterborne pigmented UV cure technologies. LAQVA™ Prime Universal is a lower VOC alternative to traditional solventborne catalyzed primers without pot-life concerns or the need for additional reducers for application. This high performance primer has no reportable VHAPS and is UL GREENGUARD Gold Certified for low chemical emissions.

PRODUCT DATA:

Color:	White	VOC theoretical as packaged:	0.00 lbs./gal or 0.00 g/L less exempts
Solids % by Vol.:	48% (Theoretical)	Lbs. VHAPS / Lbs. Solids:	0.00
Solids % by Wt.:	62% (Theoretical)	Flash Point (PMCC):	N/A
Weight / Gal.:	11.4 lbs.	Photo Chemically Reactive:	No
Viscosity 23°C / 73°F:	#3 Zahn: 15-19 secs.	Shelf Life:	12 months (at 15-25° C / 59-77°)
		Theo. Coverage @ 1 mil dry	770 Sq. Ft./Gal. @ 100% Efficiency

MIXING / APPLICATION:

Working Temp: >16° C, 60° F substrate, coating and air
Hardener: N/A
Catalyzation: N/A
Pot Life: N/A
Mixing: Mix thoroughly to ensure uniform consistency.
Reducer: May be reduced with water as needed.
Application: 110 - 150 (g/m²) Approx. 4 - 5 wet mils. Do not exceed 4 dry mils total system thickness.
Surfacer Prep: Substrate should be clean and free of grease and oil. Moisture content of the wood should be between 6%-8%. Using a denibber will eliminate some grain-raising and smooth the edges. Always sand the primer within 8 hours prior to top-coating to improve adhesion. Users are urged to test the system under shop conditions.
Use Directions: To be used as a surfacer with one or two coats on wood or MDF. Sand with 240-320 grit to improve adhesion. For optimal sanding, DA sanding equipment should be set approximately to 8,000 - 9,000 rpm. Always sand the primer within 8 hours prior to top-coating to improve adhesion. Users are urged to test the system under shop conditions.
App. Equip.: Conventional & HVLP Siphon (Gravity) Feed and Pressure Pot Systems, Airless and Airless Air Assist Equipment.

DRYING TIMES:

Method	Drying Temp.	Drying Time (@ 60 % RH and thickness @ 1 mil dry)
Air Drying	68°F / 20°C	10-15 min. dry to touch, 45-60 min. dry to sand a recoat
Force Drying	110°F / 43°C - 140°F / 60°C	After 10 minute flash off, force dry @ 10-20 minutes

APPLICATION RECOMMENDATIONS:

APPLICATION EQUIPMENT SETTINGS

Method of Application	Wet Film		Dry Film	
	Mils	/ g/m ²	Mils	/ Microns
Conventional – Siphon Fed	4 – 5	/ 100 - 120 g/m ²	1.9 – 2.4	/ 48 – 61 microns
Conventional – Pressure Pot	4 – 5	/ 100 - 120 g/m ²	1.9 – 2.4	/ 48 – 61 microns
Airless Air Assist	4 – 5	/ 100 - 120 g/m ²	1.9 – 2.4	/ 48 – 61 microns
HVLP - Siphon Fed	4 – 5	/ 100 - 120 g/m ²	1.9 – 2.4	/ 48 – 61 microns
HVLP - Pressure Pot	4 – 5	/ 100 - 120 g/m ²	1.9 – 2.4	/ 48 – 61 microns

All measurements and application equipment settings are based on application at a temperature of 68°F. Viscosity will vary depending on the temperature of the liquid. The application equipment setting recommendations are guidelines only. The settings are starting point recommendations and adjustments to the equipment settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

REDUCTION – TIP SIZE – PSI SETTINGS

Conventional Equipment Pressure Pot:

If needed, reduce with deionized water up to 5% maximum. Nozzle size 0.055 inches (1.4mm) – 0.070 inches (1.8 mm), atomizing air 40 psi (2.8 bar)–45 psi (3.1 bar), Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar).

Airless Equipment:

If needed, reduce with deionized water up to 5% maximum. Tip size .011 - .013

Pressure: 1800 psi (124 bar) – 2400 psi (165 bar)

Airless Air Assist Equipment:

If needed, reduce with deionized water up to 5% maximum. Tip size .011 - .013 inches, fluid pressure 600 (41 bar) -800 psi (55 bar), atomizing air 20 psi (1.3 bar) to 25 psi (1.7 bar).

HVLP Equipment Pressure Pot:

If needed, reduce with deionized water up to 5% maximum. Nozzle size 0.055 inches (1.4mm) – 0.070 inches (1.8 mm) nozzle, atomizing air 10 psi (0.70 bar).

Vacuum Coat: Consult your technical representative for recommendations during line evaluation.

Cleanup: Clean tools/equipment immediately after use with water. Flush equipment with water followed by flushing with 2 parts water and 1 part Butyl Cellosolve or Acetone.

CONTACTS:

PH: AcromaPro USA and Canada / 1-888-277-1448

www.AcromaPro.com



PRODUCT NOTES

- For interior use only.
- Protect from freezing.
- Mix thoroughly before use. Avoid vigorous agitation which may cause foaming.
- Paint, substrate and ambient conditions must be above 60°F / 16°C. During high humidity use force dry up to 140°F / 60°C with good air movement.
- Tank, piping and containers should be lined or plastic.
- When using this primer under a clear topcoat, it is recommended to use Akva Line™ 814 Clear Topcoat or a water white conversion varnish to minimize yellowing. Other clear topcoat technologies may be acceptable, but should be evaluated and approved prior to use.
- LAQVA™ PRIME UNIVERSAL is designed for use as a primer for the following topcoat technologies:
 - o Akvatopp™ 814 WB White Topcoat
 - o Bernyl™ FF Hi-Bild Precat Lacquer
 - o Bernyl™ FF Hi-Bild Precat White Lacquer
 - o Bernyl™ FF Conversion varnish
 - o Bernyl™ FF Plus Conversion Varnish
 - o Forté Clear Polyurethane Topcoat
 - o Waterborne Pigmented UV Cure Topcoat
- UL GREENGUARD Gold Certified for low chemical emissions.



TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. For Regulatory compliance data (i.e. VOC, HAPS, etc.), obtain an Environmental Data Sheet (EDS) prior to using the product. Regulatory documents are available from your local distributor or at www.paintdocs.com. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, AcromaPro cannot make any warranties as to the end result.