



AKVATOPP™ 814 WB WHITE TOPCOAT

White: EG55814xx (15, 30,50 Gloss)

Neutral: EG5381430 (30 Gloss)

DESCRIPTION:

AKVATOPP™ 814 WB White Topcoat is a one component acrylic/polyurethane topcoat with optional cross linker designed for use on interior wood products as a self-sealing system or applied over Laqva™ Prime Universal. This waterborne topcoat builds quickly and has very good film hardness and resistance to common household chemicals and moisture. The neutral base can be used to develop darker colors. Typical end use applications include kitchen cabinets, residential furniture and architectural woodworking. AKVATOPP™ 814 WB Topcoat is low in VOC and is UL GREENGUARD Gold certified for low chemical emissions.

PRODUCT DATA:

Color:	White & Neutral (clear)	VOC theoretical as packaged:	1.66 lbs./gal or 199 g/L less exempts
Gloss @ 60 ° angle:	15,30,50 units	Lbs. VHAPs / Lbs. Solids:	0.09
Solids % by Vol.:	27% (Theoretical)	Flash Point (PMCC):	N/A
Solids % by Wt.:	37% (Theoretical)	Photo Chemically Reactive:	No
Weight / Gal.:	9.60 lbs.	Shelf Life:	12 months (at 15-25° C / 59-77°)
Viscosity 23°C / 73°F:	#5 Zahn: 19-24 secs.	Theo. Coverage@1 mil dry	436 Sq. Ft./Gal. @ 100% Efficiency

MIXING / APPLICATION:

Working Temp:	>18° C, 65° F substrate, coating and air
Hardener:	For improved hardness, abrasion resistance and chemical resistance ZZ0XTA004, WB Cross Linker (Aziridine) can be mixed in @ 1.0% by volume with a 50/50 blend of deionized water. Stir this mix well before adding to the coating while under agitation.
Pot Life:	24 hours – After 24 hours, you may carry over the catalyzed product overnight by adding 50% of uncatalyzed coating at the end of the day. Catalyze the entire amount of material (not just the newly added material) when ready to use the following day. Catalyzed material must not be carried over the weekend and should be properly disposed of after the second 24 hour period.
Mixing:	Mix thoroughly to ensure uniform consistency.
Reducer:	May be reduced with deionized water up to 5%.
Application:	Spray apply at 3.0 – 4.0 wet mils per coat. Air dry for 30-45 minutes, sand with 320 grit between coats. Do not exceed 4.0 dry mils total system thickness.
Surface Prep:	Substrate should be clean and free of grease and oil. Moisture content of the wood should be between 6%-8%. Using a denibber will eliminate some grain-raising and smooth the edges. Always finish sand bare wood with 180-220 grit paper. If primer is used, sand the primer with 240 grit paper within 8 hours prior to top-coating to improve adhesion. Users are urged to test the system under shop conditions.
Use Directions:	To be used as a self-sealing topcoat or over Laqva™ Prime Universal primer on interior wood and MDF surfaces. MDF substrate may require a second coat of primer for better filling. Always test in customer's shop setting prior to any large scale application.
App. Equip.:	Conventional & HVLP Siphon (Gravity) Feed and Pressure Pot Systems and Airless Air Assist Equipment.
Tinting:	Can be tinted with Chroma-Chem® 896 colorants up to 4 ounces per gallon.
Ind. Standards:	This product meets the quality standard Water Acrylic Opaque for AWI.

DRYING TIMES:

Method	Drying Temp.	Drying Time (@ 60 % RH and thickness @ 1 mil dry)
Air Drying	20° C / 68° F	20-30 min. dry to touch, 30-45 min. dry to sand and recoat

AKVATOPP™ 814 WB WHITE TOPCOAT

White: EG55814xx (15, 30,50 Gloss)

Neutral: EG5381430 (30 Gloss)

APPLICATION RECOMMENDATIONS:

APPLICATION EQUIPMENT SETTINGS

Method of Application	Wet Film Mils	Dry Film Mils / Microns
Conventional – Siphon Fed	3-4 mils / 75 - 100 g/m ²	0.8 – 1.0 mils / 20 – 25 microns
Conventional – Pressure Pot	3-4 mils / 75 - 100 g/m ²	0.8 – 1.0 mils / 20 – 25 microns
Airless Air Assist	3-4 mils / 75 - 100 g/m ²	0.8 – 1.0 mils / 20 – 25 microns
HVLP - Siphon Fed	3-4 mils / 75 - 100 g/m ²	0.8 – 1.0 mils / 20 – 25 microns
HVLP - Pressure Pot	3-4 mils / 75 - 100 g/m ²	0.8 – 1.0 mils / 20 – 25 microns

All measurements and application equipment settings are based on application at a temperature of 68°F. Viscosity will vary depending on the temperature of the liquid. The application equipment setting recommendations are guidelines only. The settings are starting point recommendations and adjustments to the equipment settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

REDUCTION – TIP SIZE – PSI SETTINGS

Conventional Equipment Pressure Pot:

Nozzle size 0.055 inches (1.4mm) – 0.070 inches (1.8 mm), atomizing air 25 psi (1.7 bar)–40 psi (2.8 bar), Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar).

HVLP Equipment Pressure Pot:

Nozzle size 0.055 inches (1.4mm) – 0.070 inches (1.8 mm) nozzle, atomizing air 10 psi (0.70 bar) .

Airless Air Assist Equipment:

Nozzle size, tip size .011 - .013 inches, fluid pressure 400 psi (27 bar) – 600 psi (41 bar), atomizing air 15psi (1.0 bar) to 20psi (1.5 bar).

Reduction: Reducing is not normally required. If needed reduce up to 5% by volume using deionized water.

Cleanup: Cleanup parts and equipment with a mixture of 2 parts water to 1 part Butyl Cellosolve.

PRODUCT NOTES

- For interior use only.
- Protect from freezing.
- For MDF board, Laqva™ Prime Universal primer is recommended. Machined edges may require additional coat of primer. Sand with 240 grit paper between coats.
- Tank, piping and containers should be lined or plastic.
- Akatopp™ 814 WB White Topcoat can be catalyzed to enhance through dry times and performance with ZZ0XTA004, WB Cross Linker (Aziridine). After 24 hours of being catalyzed, the cross-linker will lose it's effectiveness, becoming inert. You may extend the "pot-life" per instruction one cycle only.
- UL GREENGUARD Gold certified for low chemical emissions.



CONTACTS:

PH: AcromaPro USA and Canada / 1-888-277-1448

www.AcromaPro.com



TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. For Regulatory compliance data (i.e. VOC, HAPS, etc.), obtain an Environmental Data Sheet (EDS) prior to using the product. Regulatory documents are available from your local distributor or at www.paintdocs.com. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, AcromaPro cannot make any warranties as to the end result.