



**AKVATOPP™ WHITE PRECATALYZED
W/B TOPCOAT**
EG570001X (20,35,50,80 Gloss)

DESCRIPTION:

Akvatopp™ White Precatlyzed W/B Topcoat is a high solids, waterborne acrylic, pigmented topcoat suitable for many interior woodworking applications. Akvatopp™ is fast drying with a silky feel that develops a durable finish with good non-yellowing performance. It provides excellent block resistance and good hide. Akvatopp™ provides a totally formaldehyde and HAPs free coating.

PRODUCT DATA:

Colour:	Wet: Clear Dry: Clear	VOC (as packaged, maximum, less water and exempt solvents):	2.05 lbs/gal or 246 g/l
Solids % by Vol.:	33% (Theoretical)	VOC (emitted):	0.93 lbs/gal or 112 g/l
Solids % by Wt.:	44 % (Theoretical)	Lbs. VHAPs / Lbs. Solids:	0.00
Weight / Gal.:	9.79 lb	Flash Point (PMCC):	Does Not Flash
Viscosity 25°C / 77°F:	#4 Ford: 65-73 Sec.	Photo Chemically Reactive:	No
Viscosity 25°C / 77°F:	DIN 4: 55-65 Sec.	Shelf Life:	12 months (15-25° C / 59-77° F)
Viscosity 25°C / 77°F:	Zahn #2 sig.: N/A Sec.	Theo. Coverage@1mil dry	528 Sq. Ft./Gal. 100% Efficiency

MIXING / APPLICATION:

Working Temp: >20° C, 68° F substrate, coating and air
Hardener: N/A
Catalyzation: N/A
Pot Life: N/A
Mixing: Mix thoroughly to ensure uniform consistency.
Reducer: May be reduced with water as needed.
Application: 100 - 140 (g/m²) Approx. 4 – 5 wet mils. Min 1 mil wet –Max 5 mil wet @ 60%RH
Surfacer/Primer: Akvasurf™ Precatalyzed, Laqva Prime™
Surface Prep: Always sand the primer-coat within 8 hours prior to top-coating to improve adhesion.
Use Directions: For interior use only. Stir thoroughly before application to avoid variations in gloss. Stack only when the surface temperature is below 25°C / 75 ° F. Dry time can be directly impacted by many factors, including film thickness. Users are urged to test the system under shop conditions.
App. Equip.: Conventional & HVLP Siphon (Gravity) Feed and Pressure Pot Systems and Airless Air Assist Equipment.
Tinting: Can be tinted with 896 tinters up to a maximum of 5%. Prior to application test a sample piece to assure proper colour match.

DRYING TIMES TO SAND / STACK / RECOAT WINDOW:

Method	Drying Temp.	Drying Time (@ 60 % RH and thickness @ 1 mil dry)
Air Drying	20° C / 68° F	1 – 2 hours dry to sand / overnight. dry to stack / recoat window: within 8 hours

**AKVATOPP™ WHITE PRECATALYZED
W/B TOPCOAT**
EG570001X (20,35,50,80 Gloss)

APPLICATION RECOMMENDATIONS:

APPLICATION EQUIPMENT SETTINGS

Method of Application	Wet Film		Dry Film	
	Mils	g/m ²	Mils	Microns
Conventional – Siphon Fed	4 – 5 mils	100 - 140 g/m ²	1.3 – 1.6 mils	32 - 40 microns
Conventional – Pressure Pot	4 - 5 mils	100 - 140 g/m ²	1.3 – 1.6 mils	32 – 40 microns
Airless Air Assist	4 – 5 mils	100 - 140 g/m ²	1.3 – 1.6 mils	32 – 40 microns
HVLP - Siphon Fed	4 – 5 mils	100 - 140 g/m ²	1.3 – 1.6 mils	32 - 40 microns
HVLP - Pressure Pot	4 – 5 mils	100 - 140 g/m ²	1.3 – 1.6 mils	32 – 40 microns

All measurements and application equipment settings are based on application at temperature of 68°F. Viscosity will vary depending on the temperature of the liquid. The application equipment setting recommendations are guidelines only. The settings are starting point recommendations and adjustments to the equipment settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

REDUCTION – TIP SIZE – PSI SETTINGS

Conventional Equipment Siphon Feed:

To be used as is, if needed, reduce with water. Nozzle size 0.060 inches (1.5mm) – 0.070 inches (1.8 mm), atomizing air 25 psi (1.7bar)–40 psi (2.8 bar).

Conventional Equipment Pressure Pot:

To be used as is, if needed, reduce with water. Nozzle size 0.060 inches (1.5mm) – 0.070 inches (1.8 mm), atomizing air 25 psi(1.7 bar)–40 psi (2.8 bar), Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar).

Airless Air Assist Equipment:

To be used as is, if needed, reduce with water. Tip size.015 inches (0.33mm) - .016 inches (0.41mm), fluid pressure 290 psi (20 bar) – 580psi(40 bar), atomizing air 15psi (1 bar) to 20psi (1.5 bar).

HVLP Equipment Siphon Feed:

To be used as is, if needed, reduce with water. Nozzle size - .060inch (1.5mm) -.080inch (2MM) nozzle, atomizing air 29 psi (2 bar) -40 psi (2.8bar).

HVLP Equipment Pressure Pot:

To be used as is, if needed, reduce with water. Nozzle 0.060 inches (1.5mm) – 0.08 inches (2 mm) nozzle, atomizing air 20psi (1.37 bar) -29 psi (2 bar). Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar).

CONTACTS:

PH: AcromaPro USA and Canada / 1-888-277-1448

www.AcromaPro.com



PRODUCT NOTES

- Like most water based products, Akvatopp™ should not be force dried with high speed air for the first couple of minutes to avoid mud-cracking.
- Maximum recommended dry film thickness for total coating system is 5 mils.

TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. For Regulatory compliance data (i.e. VOC, HAPS, etc.), obtain an Environmental Data Sheet (EDS) prior to using the product. Regulatory documents are available from your local distributor or representative. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, AcromaPro cannot make any warranties as to the end result.