



CARE SEAL™ PRECATALYZED SEALER

FL5312000

DESCRIPTION:

Care Seal™ Precatalyzed Sealer is a precatalyzed, nitrocellulose, vinyl modified, clear sealer for interior woodwork. This sealer has added U.V. absorber, making it a great option for light colored wood substrates. Care Seal™ Precatalyzed Sealer is fast drying and has excellent sandability. It is a HAPS free sealer for use under recommended AcromaPro acid cured, precatalyzed clear topcoats.

PRODUCT DATA:

Color:	Wet: Translucent Dry: Clear	VOC (as packaged, maximum, less exempt solvents):	5.44 lbs/gal or 652 g/l
Solids % by Vol.:	18 % (Theoretical)	VOC (emitted):	4.95 lbs/gal or 593 g/l
Solids % by Wt.:	26 % (Theoretical)	Lbs. VHAPs / Lbs. Solids:	0 before catalyzed
Weight / Gal.:	7.48 lb	Flash Point (PMCC):	-18° C / -0.4° F
Viscosity 23°C / 73°F:	#4 Ford: 25-30 Sec.	Photo Chemically Reactive:	No
Viscosity 23°C / 73°F:	DIN 4: 18-22 Sec.	Shelf Life:	6 months (at 15-25° C / 59°-77° F)
Viscosity 23°C / 73°F:	Zahn #2 sig.: 16-20 Sec.	Theo. Coverage @ 1mil dry	290 Sq. Ft./Gal. 100% Efficiency

MIXING / APPLICATION:

Working Temp: >18° C, 65° F substrate, coating and air
Catalyst: N/A
Catalyzation: N/A
Pot Life: N/A
Mixing: Mix thoroughly to ensure uniform consistency.
Reducer: Thinner 219 (regular), Thinner OC 140 (fast), Thinner 309 (fast, HAPS free), Thinner 419 (slow, HAPS free)
Application: 70-100 (g/m²) Approx. 4 wet mils; Min 1 mil wet –Max 5 mil wet @ 60%RH
Surface Prep: Substrate should be clean and free of grease and oil. Moisture content of the wood should be between 6%-8%. Sand the first coat in order to eliminate grain raising and to improve the adhesion of the subsequent coat. Sand with 150 grit on open grain wood and 180 grit on closed grain wood. Always sand the sealer-coat within 8 hours prior to top-coating to improve adhesion.
Use Directions: For interior use only. Mix thoroughly before application. Stack only when the surface temperature is below 35°C / 95° F. Dry time can be directly impacted by many factors, including film thickness. Users are urged to test the system under shop conditions.
App. Equip.: Conventional & HVLP Siphon Feed and Pressure Pot Systems and Airless Air Assist Equipment.
Tinting: Can be tinted with Chroma Chem 866 colorants to a maximum of 5% total colorant. Prior to application, test a sample piece to ensure proper color match.
Ind. Standards: This product meets KCMA and CKCA standards.

DRYING TIMES TO SAND:

Method	Drying Temp.	Drying Time (@ 60 % RH and thickness @ 1 mil dry)
Air Drying	20° C / 68° F	15-30 min. dry to sand
*Forced Drying	70° C / 158° F	5-10 min. dry to sand

CARE SEAL™ PRECATALYZED SEALER

FL5312000

APPLICATION RECOMMENDATIONS:

APPLICATION EQUIPMENT SETTINGS

Method of Application	Wet Film Mils / g/m ²	Dry Film Mils / Microns
Conventional – Siphon Fed	3 – 5 mils / 75-125 g/m ²	0.57-0.95 mils / 14-23 microns
Conventional – Pressure Pot	3 – 5 mils / 75-125 g/m ²	0.57-0.95 mils / 14-23 microns
Airless Air Assist	3 – 5 mils / 75-125 g/m ²	0.57-0.95 mils / 14-23 microns
HVLP - Siphon Fed	3 – 5 mils / 75-125 g/m ²	0.57-0.95 mils / 14-23 microns
HVLP - Pressure Pot	3 – 5 mils / 75-125 g/m ²	0.57-0.95 mils / 14-23 microns

All measurements recommended are based on results at a temperature of 68°F. Viscosity will vary depending on the temperature of the liquid. The above mentioned application equipment recommendations are guidelines only. The noted settings are starting point recommendations and that adjustment to the settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set up.

REDUCTION – TIP SIZE – PSI SETTINGS

Conventional Equipment Siphon Feed:

Reduce to 18-21 seconds #4 ford viscosity cup, nozzle size 0.070 inches (1.8mm) – 0.0 inches (2.0 mm), atomizing air 30 psi (2.0)–40 psi (2.8 bar)

Conventional Equipment Pressure Pot:

Reduce to 18-21 seconds #4 ford viscosity cup, nozzle size 0.472 inches (1.2mm) – 0.055 inches (1.4 mm), atomizing air 30 psi(2.0 bar)–40 psi (2.8 bar), Pot pressure 10 psi (0.60 bar) to 15 psi (0.75 bar)

Airless Air Assist Equipment:

Reduce to 18-25 seconds #4 ford viscosity cup, tip size.011inches (0.28mm) - .013 inches (0.33mm), fluid pressure 290 psi (20 bar) – 580psi(40 bar), atomizing air 11psi (0.8 bar) to 17psi (1.2 bar).

HVLP Equipment Siphon Feed:

Reduce to 17-21 seconds #4 ford viscosity cup,.061inch (1.5mm) -.072inch (1.8MM) nozzle, atomizing air 35psi (2.4bar) -45 psi (3.1bar).

HVLP Equipment Pressure Pot:

Reduce to 17-21 seconds #4 ford viscosity cup,0.472 inches (1.2mm) – 0.055 inches (1.4 mm) nozzle, atomizing air 20psi (1.37 bar) -25 psi (1.72 bar). Pot pressure 10 psi (0.60 bar) to 15 psi (0.75 bar)

CONTACTS:

PH: AcromaPro USA and Canada / 1-888-277-1448

www.AcromaPro.com



PRODUCT NOTES

- Maximum recommended dry film thickness for total coating system is dependent on the topcoats used.
- This sealer has added UV absorber providing very good light resistance performance. This helps to slow down the natural discoloration of the wood substrate.

TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Material Safety Data Sheet (MSDS) for safety information and cautions prior to using this product. For Regulatory compliance data (i.e. VOC, HAPS, etc.), obtain an Environmental Data Sheet (EDS) prior to using the product. A MSDS and/or EDS is available from your local distributor or representative. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, AcromaPro cannot make any warranties as to the end result.