



AccuStain™ STAIN SYSTEM

Colorants and Clear Bases

DESCRIPTION:

AccuStain™ Stain System offers a combination of high strength alkyd dispersions with clear solvent stain bases providing a customizable stain platform for interior woodwork products. This stain mixing system provides dark, clean colors and has very good soft-settling properties. AccuStain™ Colorants are formulated specifically for coloring wiping stains, spray stains, glazes, and fillers. AccuStain™ Wipe Base and Concentrate Base are clear wiping stain bases specifically formulated to work with the AccuStain™ Stain Colorants. AccuStain™ Wipe Base is a low solids clear stain base. AccuStain™ Concentrate Base is a high solids clear stain base designed for making custom stain bases. AccuStain Clear Base is a lower VOC version of the Wipe Base.

Black.....ZZ00B7000	Red Oxide.....ZZ00R7500	Yellow Oxide.....ZZ00Y8100
Burnt Umber.....ZZ00N7100	Transoxide Red.....ZZ00R7600	TransoxideYellow.....ZZ00Y8200
Raw Umber.....ZZ00N7200	Brite Red.....ZZ00R7700	Raw Sienna.....ZZ00Y8300
Van Dyke Brown.....ZZ00N7300	Deep Red.....ZZ00R7800	Brite Yellow.....ZZ00Y8400
Burnt Sienna.....ZZ00N7400	Magenta.....ZZ00R7900	White.....ZZ00W8500
	Blue.....ZZ00L8600	Wipe Base.....HS5170000
	Clear Base.....HS5172000	Concentrate Base.....HS5178000

PRODUCT DATA:

AccuStain™ Colorants	AccuStain™ Wipe Base	AccuStain™ Concentrate Base
Solids % by Vol.: 50-72%	Solids % by Vol.: 9.1%	Solids % by Vol.:47.8%
Solids % by Wt.: 60-87%	Solids % by Wt.: 12%	Solids % by Wt.: 54.4%
Photochemically reactive: No	Photochemically reactive: No	Photochemically reactive: Yes
Theoretical VOC: 1.8-3.1 lb/gal, 220-373 g/L	Theoretical VOC: 5.87 lb/gal, 703 g/L	Theoretical VOC: 3.36 lb/gal, 403 g/L
Flash Point: 88°F-105°F PMCC	Flash Point: 100°F PMCC	Flash Point: 80°F PMCC
Package Life: 2 years, unopened	Package Life: 2 years, unopened	Package Life: 2 years, unopened

*For a lower VOC stain base, see HS5172000 Clear Base. See EDS and SDS for details.

MIXING / APPLICATION:

Working Temp:	77° F, 50% RH
Mixing:	Agitate materials before and while using. Avoid vigorous agitation, which can cause bubbling or foaming.
Reducer:	VM&P Naphtha (fast), Mineral Spirits (medium), 140 Flash (slow) Toluene (fast), Xylene (medium), 100 Flash, (slow). These solvents are completely compatible with the AccuStain™ Colorants and bases. These solvents can be blended and used in all proportions.
Application:	Can be formulated and applied as a wiping stain or spray stain. See next page for details.
Surface Prep:	Interior wood only. Substrate should be clean, dry and finish sanded. Moisture content of the wood should be between 6%-8%.
Use Directions:	For interior use only. Mix thoroughly before application. Spray or wipe on wood substrate, wipe clean within 5 minutes or before stain flashes off. Dry time may be extended due to high humidity, low temperatures, or inadequate ventilation. AccuStain is compatible with other AcromaPro solvent based products: KV Natural Glaze – HS5961000. For use under AcromaPro solvent based sealer and topcoat systems. Do not use under UV products. Consult local AcromaPro sales representative for system recommendations. Users are urged to test the system under shop conditions.
App. Equip.:	Can be applied as a wipe or spray stain. For spray stain, use HVLP application equipment. See back page for details.

DRYING TIMES TO SEAL / FINISH:

Method	Drying Temp.	Drying Time (@ 77° F, 50% RH)
Air Drying	77° F	30-60 min. dry to seal coat – Unless formulated as a no wipe stain, wipe stain clean within 5 minutes after stain application or before stain flashes off.

AccuStain™ STAIN SYSTEM

Colorants and Clear Bases

PRODUCT DATA CTD.:

Mixing and Application:

Wiping Stain formulations made with HS5170000 or HS5172000 – Wipe Base and Clear Base

- Agitate the colorants and clear to uniform consistency prior to using.
- Add AccuStain™ Colorants to HS5170000 or HS5172000 to make or match a color.
- Average wiping stains will contain 0-10% AccuStain™ Colorants by weight.
- Heavier, stronger wiping stains may contain 10-30% AccuStain™ Colorants by weight.
- Most wiping stains can be made by blending AccuStain™ Colorants with the HS5170000 or HS5172000 only.
- As required the HS5170000 + AccuStain™ Colorant blend can be adjusted with solvent to modify drying and wiping. For example: Add VM&P at 5-10% to make a faster drying stain, or 140 Flash at 5-10% to make a slower drying stain.
- Test the total system to make sure the stain and clear coats meet the customer's requirements for drying and adhesion.
- Highly pigmented stains require longer dry times than those with low pigment levels.

Wiping Stain formulations made with HS5178000 – Concentrate Base

- HS5178000 allows for customizing the composition of the solvent blend and the vehicle solids of the wiping stain base.
- Reduce HS5178000 with 200-400% solvent by weight. Add up to 30% AccuStain™ Colorants by weight to the reduced concentrate.

Application as a Wiping Stain: Agitate the stain before and during use for color consistency. Apply a full wet coat of the stain by spray, brush or lint free rag. Work the stain into the wood using a circular motion. Open time is 1-5 minutes. Working time will vary depending on the formulation, application and shop conditions. Cleanly wipe excess stain off the surface with the grain. If wiping becomes difficult due to drying of the stain, rewet with a cloth dipped in stain, then wipe again. Multiple coats of wiping stain are not recommended, this will cause adhesion problems.

Application as a Spray Stain (No Wipe): Spray stain formulas can be made using 0-15% AccuStain™ Colorants by weight or 1 part AccuStain™ Colorants to 10 parts solvent by volume. Mineral Spirits is a good starting point solvent for a spray stain. Blending with faster solvents will adjust the drying and penetration. This will create a low to moderately strong stain formulation. This technique is for staining, not painting the wood. This type of formulation can also be used for making shade stains. **Always check adhesion of the total system to see that it meets customer expectations.**

Considerations on total system adhesion: Best results are achieved by using stains with lower pigment concentrations under lacquers and precatalyzed lacquers. Stronger, more highly pigmented stains can be used under conversion varnish systems. For very strong or highly colored systems, it may be better to two step the coloring process. This could mean dye staining, or the application of a pigmented toner prior to wipe staining.

REDUCTION – TIP SIZE – PSI SETTINGS

HVLP Equipment:

BINKS® Trophy™ Series Gun
Atomizing Air Pressure10-20 psi
Fluid Pressure5-10 psi
Cap/TipHVLP 32-H/45-11050-1.2

CONTACTS:

PH: AcromaPro Canada / 519-758-1508
PH: AcromaPro USA / 812-288-0712

www.AcromaPro.com



PRODUCT NOTES

Reducing Options:

HAPS Compliant
VM&P Naphtha – Fast
Mineral Spirits – Medium
140 Flash – Slow

Non-Compliant

Toluene – Fast
Xylene – Medium
100 Flash – Slow

- HS5172000 is a lower VOC version of HS5170000

TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. For Regulatory compliance data (i.e. VOC, HAPS, etc.), obtain an Environmental Data Sheet (EDS) prior to using the product. Regulatory documents are available from your local distributor or representative. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, AcromaPro cannot make any warranties as to the end result.