

WHITE PRECAT LAC

NG504001X (15, 25, 40 Gloss)

DESCRIPTION:

White Precat Lac is a precatalysed white top coat with fast drying properties and excellent filling characteristics. This product has improved hiding power compared with the standard product. White Precat Lac also has low VOC's and is suitable for on-site application under Canadian VOC regulations for Architectural Coatings. This high solids product has low HAPs and low formaldehyde.

PRODUCT DATA:

Color:	Wet: White Dry: White	VOC (theoretical as packaged, maximum, less exempt solvents):	539 g/l or 4.49 lbs/gal
Solids % by Vol.:	28 % (Theoretical)	Lbs. VOC / Lbs. Solids:	1.15
Solids % by Wt.:	44 % (Theoretical)	Lbs. VHAPs / Lbs. Solids:	0.51
Weight / Gal.:	8.93 lb/gal	Flash Point (PMCC):	-18 ° C / -28 ° F
Spec. Gravity:	1.07	Frost Sensitivity	No
Viscosity 23°C / 73°F:	#4 Ford: 60-70 Sec.	Photo Chemically Reactive:	Yes
Viscosity 23°C / 73°F:	DIN 4: 50-60 Sec.	Shelf Life:	12 months (at 15-25°C / 59°-77°F)
Viscosity 23°C / 73°F:	Zahn #2 sig.: N/A Sec.	Theo. Coverage@1mil dry	450 Sq. Ft./Gal. 100% Efficiency mixed

NOTE: An Environmental Data Sheet is available from your nearest AcromaPro distributor

MIXING / APPLICATION:

Working Temp: >18° C, 65° F substrate, coating and air
Pot Life: N/A
Mixing: Mix thoroughly to ensure uniform consistency.
Sealer: Use over Ultra Hide Precat Primer, or self-sealing
Reducer: Thinner 219 - Regular; Thinner OC 140 - Fast; Thinner 309 - Haps Free, Thinner 419 – Slow, Haps Free
Application: 75 - 100 (g/m²) Approx. 4 wet mils; Min 1 mil wet –Max 4 mil wet @ 60%RH
Surface Prep: Substrate should be clean and free of grease and oil. Moisture content of the wood should be between 6%-8%. White wood sanding with 180 grit sandpaper. Sand the first coat (with 220 to 320 paper) in order to eliminate grain raising, if any, and improve adhesion of the subsequent coat. Topcoat within 8 hours of sanding.
Use Directions: For interior use only. Mix thoroughly before application reduce with Thinner 309 to spray viscosity. Stack only when the surface temperature is below 35°C / 95 ° F. Quicker stacking times are achievable relative to the amount of product that is applied.
App. Equip.: Conventional & HVLP Siphon Feed and Pressure Pot Systems and Airless Air Assist Equipment.
Tinting: Can be tinted with 844 Tinters. Prior to application test a sample piece to assure proper color match.
Ind. Standards: This product meets the Precatalysed Lacquer Opaque quality standard for AWI.

DRYING TIMES TO SAND / STACK / RECOAT WINDOW:

Method	Drying Temp.	Drying Time (@ 60 % RH and thickness @ 1 mil dry)
Air Drying	20° C / 68° F	30-60 min. dry to sand / 30-60 min. dry to stack / recoat window: within 8 hours

WHITE PRECAT LAC

NG504001X (15, 25, 40 Gloss)

APPLICATION RECOMMENDATIONS:

APPLICATION EQUIPMENT SETTINGS

Method of Application	Wet Film		Dry Film	
	Mils	/ g/m ²	Mils	/ Microns
Conventional – Siphon Fed	3 – 5 mils	/ 80-125g/m ²	0.8-1.4 mils	/ 20-36 microns
Conventional – Pressure Pot	3 – 5 mils	/ 80-125 g/m ²	0.8-1.4 mils	/ 20-36 microns
Airless Air Assist	3 – 5 mils	/ 80-125 g/m ²	0.8-1.4 mils	/ 20-36 microns
HVLP - Siphon Fed	3 – 5 mils	/ 80-125 g/m ²	0.8-1.4 mils	/ 20-36 microns
HVLP - Pressure Pot	3 – 5 mils	/ 80-125 g/m ²	0.8-1.4 mils	/ 20-36 microns

All measurements recommended are based on results at temperatures of 23°C/ 73°F. Viscosity will vary depending on the temperature of the liquid. The above mentioned application equipment recommendations are guidelines only. The noted settings are starting point recommendations and that adjustment to the settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set up.

REDUCTION – TIP SIZE – PSI SETTINGS

Conventional Equipment Siphon Feed:

Reduce to 28-32 seconds #4 ford viscosity cup, nozzle size 0.070 inches (1.8mm) – 0.0 inches (2.0 mm), atomizing air 25psi (1.7bar)–40 psi (2.8 bar).

Conventional Equipment Pressure Pot:

Reduce to 28-32 seconds #4 ford viscosity cup, nozzle size 0.472 inches (1.2mm) – 0.055 inches (1.4 mm), atomizing air 25 psi (1.7 bar)–40 psi (2.8 bar), Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar)

Airless Air Assist Equipment:

Reduce to 31-34 seconds #4 ford viscosity cup, tip size .011inches (0.28mm) - .013 inches (0.33mm), fluid pressure 290 psi (20 bar) – 580psi(40 bar), atomizing air 20psi (1.5 bar) to 30psi (2 bar).

HVLP Equipment Siphon Feed:

Reduce to 28-32 seconds #4 ford viscosity cup, .061inch (1.5mm) -.072inch (1.8MM) nozzle, atomizing air 25psi (1.7bar) -40 psi (2.8bar).

HVLP Equipment Pressure Pot:

Reduce to 28-32 seconds #4 ford viscosity cup, 0.472 inches (1.2mm) – 0.055 inches (1.4 mm) nozzle, atomizing air 25psi (1.7 bar) -40 psi (2.8 bar). Pot pressure 7 psi (0.48 bar) to 10 psi (0.68 bar)

CONTACTS:

PH: AcromaPro USA and Canada / 1-888-277-1448

www.AcromaPro.com



PRODUCT NOTES

- White Precat Lac is a furniture quality lacquer designed for use on kitchen and bathroom cabinets, dormitory, household, office or laboratory furniture, display fixtures. Due to its low VOC content, it is also suitable for on-site application under Canadian VOC regulations.
- Maximum recommended dry film thickness for total coating system is 5 dry mils.

TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. For Regulatory compliance data (i.e. VOC, HAPS, etc.), obtain an Environmental Data Sheet (EDS) prior to using the product. Regulatory documents are available from your local distributor or representative. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, AcromaPro cannot make any warranties as to the end result.