

OXP P-CAT WHITE & CLEAR LACQUER

NG507W025.....**White Base / 25 Gloss**

NG507W035.....**White Base / 35 Gloss**

NG507W080.....**White Base / 80 Gloss**

DV507WC00.....**OXP P-CAT CATALYST**

NG507C025.....**Clear Base / 25 Sheen**

NG507C035.....**Clear Base / 35 Sheen**

DESCRIPTION:

NG507 OXP P-CAT LACQUER is a white & clear tint-able pre-catalyzed lacquer platform designed for general wood markets such as the furniture and kitchen cabinet industries. **NG507** offers fast dry, high solids and build, with good early hardness characteristics. **NG507** has Low VHAPS, VOC and provides a broad, stable, and consistent color space by leveraging the Opti-Color® XP Solvent-Based Colorant Platform

HIGHLIGHTS:

» **Tight Color Space Control** » **Fast Dry to Sand** » **HAPS Compliant**
 » **Good Moisture Resistance** » **Self-Seal** » **Contains UV Absorbers**

PRODUCT DATA:

Colors:	White & Clear	VOC (as packaged, maximum, less water and exempt solvents):	White: 5.06 lb/gal, 609 g/l Clear: 5.26 lb/gal, 630 g/l
Solids % by Wt.: (Theoretical)	White: 41.7% Clear: 33.1%	Spreading Rate (No Loss)	407 sq ft/gal @ 1.0 mils DFT
Solids % by Vol.: (Theoretical)	White: 27.7% Clear: 25.2%	Lbs. VHAPS / Lbs. Solids:	None
Weight / Gal.:	White: 8.71 lb/gal Clear: 7.86 lb/gal	Flash Point (PMCC):	-5.6° C / 22° F
Viscosity 23°C / 73°F:	#2 Zahn: 23 – 28 sec.	Photo Chemically Reactive:	No
Rec. Film Thickness	Wet: 3-5 / Dry: 0.8 – 1.3 mils	Shelf Life: Unopened / Uncatalyzed:	2 year (at 15-25° C / 59°-77° F)

MIXING / APPLICATION:

Working Temp: >18° C, 65° F substrate, coating and air
Hardener: **DV507WC00 OPTI P-CAT CATALYST**
Catalyzation: 2.3% (3 oz. per gallon) Parts by volume
Pot Life: 3 months. (23° C / 73° F) after catalysation
Mixing: Add Catalyst under agitation. Use proper graduated cup for measuring. Be attentive to the correct ratio. Add thinner after catalyst. Add thinner to desired viscosity, typically about 20 %.
Sealer: Can be self-sealed or used as a topcoat.
Reducer: **Reduce** as needed for application up to 20% with Butyl Acetate or HAPS Compliant Lacquer Thinner
Retarder: **Retard** as needed for application with MAK or EEP) up to 5%
Application: 100-125 (g/m²) Approx. 3-5 wet mils; Min 3 mil wet – Max 5 mil wet @ 60%RH
Surface Prep: Sand well with 320-400 grit sandpaper. Topcoat within 8 hours of sanding.
Use Directions: For interior use only. Add hardener and reducer then mix thoroughly before application. Stack only when the surface temperature is below 35°C / 95 ° F. Quicker stacking times are achievable relative to the amount of product that is applied.
App. Equip.: Conventional & HVLP Siphon and Gravity Feed and Pressure Pot Systems and Airless Air Assist Equipment.
Tinting: Can be tinted with Opticolor XP tinters to a maximum of 10 oz per gallon. Prior to application, test a sample piece to ensure proper color match
Ind. Standards: Meets KCMA specifications as a self-sealed system.

DRYING TIMES:

Method	Drying Temp.	Drying Time (@ 60 % RH)
Air Drying	20° C / 68° F	Dry to Touch: 15-20 min. Dry to sand 40-50 min. Overnight to stack / Recoat window: No Critical Window Flash Dry: Flash off 5 min. Force Dry: 5 min @ 110F -140F.

TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Material Safety Data Sheet (MSDS) for safety information and cautions prior to using this product. For Regulatory compliance data (i.e. VOC, HAPS, etc.), obtain an Environmental Data Sheet (EDS) prior to using the product. A MSDS and/or EDS is available from your local distributor or representative. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, AcromaPro cannot make any warranties as to the end result.